

# 60-001

## Baseline Alkyd Undercoat



### INTENDED USES:

A multi-purpose, fast drying, interior / exterior primer for blocking stains. Ideal for spot priming or can be used as an undercoat for previously painted surfaces or uncoated wood. Contains a fungicidal agent and stain controlling compounds.

### PRODUCT DESCRIPTION

Alkyd resin containing high opacity pigments. Also contains a fungicidal agent and stain controlling compounds.

---

### TECHNICAL INFORMATION:

**Finish:**

Flat

**Tint Range:**

Light Colours

**Theoretical Coverage:**

41-55 m<sup>2</sup>/3.7L (450-600 ft<sup>2</sup>/3.7L)

**Typical Specific Gravity:**

1.3

**Application Thinner:**

DO NOT THIN

**Standard Colours:**

White

**Recommended # of coats:**

1-2 at recommended coverage

**Typical Volume Solids:**

56%

**Flash point:**

41°C (105°F)

**Clean-up Thinner:**

Mineral Spirits

---

### SURFACE PREPARATION:

Surfaces must be clean, dry and free from dust, grease, mildew and wax. Remove any loose and peeling paint and repair with patching compound. Ensure all joints and seams are filled with a paintable caulking to prevent moisture ingress.

Previously Painted Surfaces: Glossy surfaces should be sanded to a dull finish to provide good adhesion.

### APPLICATION:

Brush (preferred\*), Roller or Spray

Airless Tips: .013" - .017"

Dry times at 21°C / 70°F and 40%-60% R.H.:

To Touch:	2-4 hours
To Handle:	8-12 hours
To Overcoat:	16 hours minimum

### PRODUCT HAZARDS AND SAFETY INFORMATION:

See Material Safety Data Sheet for complete Health and Safety information.

### ADDITIONAL DATA:

May be used on new exterior wood, (other than plywood or siding) where a fast drying primer is required. Plywood and siding should be primed with 60-002 Latex Wood Primer. \*Brushing recommended for new wood because the brushing action will promote penetration of the product into the wood. If mildew is present, the surface should be washed with a chlorine bleach solution (20% household bleach and 1% liquid detergent in warm water) and thoroughly rinsed prior to painting. For optimum adhesion and application performance, ensure that the temperature and relative humidity

### Legal Details

The information contained herein is true and accurate to the best of our knowledge. However, no guarantee or warranty of any kind, express or implied, is given with respect to the accuracy or completeness of the said information and data or to the products described herein and we assume no risk or liability for the performance or coverage of or for injury resulting from the handling, use or application of the said information, data or products.

are between 10-25°C and 40-60% respectively, at the time of application and for four hours afterward. Complies with the requirements of MPI #5.

#### **Legal Details**

The information contained herein is true and accurate to the best of our knowledge. However, no guarantee or warranty of any kind, express or implied, is given with respect to the accuracy or completeness of the said information and data or to the products described herein and we assume no risk or liability for the performance or coverage of or for injury resulting from the handling, use or application of the said information, data or products.

**60001**

**DATE OF ISSUE: Nov 2, 2016.**