# 60-002

## **Baseline Wood Primer**



## **INTENDED USES:**

A fast drying latex primer for use on new or previously painted interior and exterior wood surfaces prior to applying either alkyd-based or latex topcoats. Its fast dry time makes it an ideal choice for spot priming when repainting. Contains tannin blocking pigments.

## PRODUCT DESCRIPTION:

Acrylic latex with unique penetrating properties. Contains stain blocking pigments and a fungicidal agent.

**TECHNICAL INFORMATION:** 

Finish: Standard Colours:

Flat White

Tint Range: Recommended # of coats:

Light Colours 1-2 at recommended coverage

Theoretical Coverage: Typical Volume Solids:

33-44 m<sup>2</sup>/3.7L (350-470 ft<sup>2</sup>/3.7L) 44%

Typical Specific Gravity: Flash point: 1.3 Not Applicable

Application Thinner: Clean-up

Application Thinner:

Not normally required. Up to 10% water if

Clean-up Thinner:

Water

Not normally required. Op to 10% water if

necessary.

# **SURFACE PREPARATION:**

Surfaces must be clean, dry and free from dust, grease, mildew and wax. Remove any loose and peeling paint and repair with patching compound.

Ensure all joints and seams are filled with a paintable caulking to prevent moisture ingress.

## **APPLICATION:**

Brush (preferred\*), Roller or Spray

Airless Tips: .011" - .015"

Dry times at 21°C / 70°F and 40%-60% R.H.:

To Touch: 15-30 minutes

To Handle: 2 hours

To Overcoat: 4 hours minimum

# PRODUCT HAZARDS AND SAFETY INFORMATION:

See Material Safety Data Sheet for complete Health and Safety information.

# **ADDITIONAL DATA:**

If mildew is present, the surface should be washed with a chlorine bleach solution (20% household bleach and 1% liquid detergent in warm water) and thoroughly rinsed prior to painting.

For optimum adhesion and application performance, ensure that the temperature and relative humidity are between 15-25°C and 40-60% respectively, at the time of application and for four hours afterward.

Complies with the requirements of MPI #6 and #39.

## **Legal Details**

The information contained herein is true and accurate to the best of our knowledge. However, no guarantee or warranty of any kind, express or implied, is given with respect to the accuracy or completeness of the said information and data or to the products described herein and we assume no risk or liability for the performance or coverage of or for injury resulting from the handling, use or application of the said information, data or products.

60002 DATE OF ISSUE: Nov 2, 2016.