



VERSABOND™

VersaBond™ Modified Alkyd Enamel bonds to tough surfaces, including a variety of plastics and provides premium rust protection. VersaBond features the EZ TOUCH® FANSPRAY® nozzle for better coverage and less finger fatigue.

- ✓ Bonds to tough surfaces
- ✓ Premium rust protection
- ✓ No sanding or priming necessary

INDUSTRIAL USE ONLY!

krylonindustrial.com
1-800-247-3266

RECOMMENDED USES

- TPO
- PVC
- Plexiglass
- Laminates
- PPO
- ABS
- PP
- Concrete
- Metals
- Wood
- Masonry
- Glass

SURFACE PREPARATION

WARNING! If you scrape, sand or remove old paint, you may release lead dust. LEAD IS TOXIC. For more information, contact your local health authority. Prepare surface by removing dirt, grease, wax, moisture, rust and loose paint.

CLEAN-UP

Clean spray valve immediately after use by turning can upside-down and spraying until only clear gas comes out. Dispose of in accordance with local, state or federal regulations.

TECHNICAL DATA

Vehicle	Modified Alkyd Enamel
Finish	Flat, Gloss
Flash Point	-20°
Volume Solids	11-13%
Weight Solids	17-24%
Weight/Gallon	7.08 lb/gal
MIR	1.07
Spread Rate	25 sq. feet
Shelf life	60 months
Drying Time	To Touch: 25 mins To Recoat: Within 2 hrs or after 48 hrs To Handle: 2 hrs
Clean-up	Mineral spirits, Please follow suppliers safety instructions
Net Weight/Can Size	12 oz./16 oz.

APPLICATION

APPLICATION CONDITIONS

Use at 70°F for best operation. Shake can for 2 minutes after ball within begins to rattle. Repeat for 10 seconds after each minute of use. Test spray on inconspicuous area or scrap piece to check compatibility. For a smooth, professional finish, spray 6" to 8" from surface in a sweeping motion. Avoid runs and drips by applying several thin coats, rather than one heavy coat. Dries to touch in 25 minutes. Can be handled in 2 hours. Can be recoated within 2 hours or after 48 hours. EZTOUCH® FANSPRAY® nozzle: You get professional-looking results with half as much finger pressure. The fanspray covers better with less overspray. Change spray direction just by turning the square insert.

CAUTIONS

FOR INDUSTRIAL USE ONLY. Thoroughly review product label and SDS for safety and cautions prior to using this product. Please direct any questions or comments to your local Krylon Industrial Representative.

Note: The information, rating, and opinions stated here pertain to the material currently offered and represent the results of tests believed to be reliable. However, due to variations in customer handling and methods of application which are not known or under our control, Krylon Products Group cannot make any warranties as to the end result. Please direct any questions or comments to 1-800-247-3266.

The information and recommendations set forth in the Product Data Sheet are based upon tests conducted by or on behalf of Krylon® Industrial. Such information and recommendations set forth herein are subject to change and pertain to the product offered at the time of publication. Consult your Krylon® Industrial dealer or representative to obtain the most recent Product Data Sheet.