

# Pro Industrial™ Multi-Surface Acrylic Semi-Gloss

B66-1550 Series


**SHERWIN  
WILLIAMS®**

## CHARACTERISTICS

**Pro Industrial Multi-Surface Acrylic** is a waterborne acrylic for interior and exterior use on marginally prepared metal or masonry surfaces. Features multiple sheens, fast dry, easy application and dry fall properties.

### Features:

- Self-priming directly to multiple surfaces
- Excellent one-coat hide and stain blocking
- Abrasion resistant
- Optimized for spray application
- Good exterior color and gloss retention
- Dries fast and dry falls in 10-15 feet
- Suitable for use in USDA inspected facilities

### For use on properly prepared:

Steel, Galvanized & Aluminum, Concrete and Masonry.

**Finish:** 35-45° @60°

**Color:** Most colors

### Recommended Spreading Rate per coat:

Wet mils: 3.75-6.0

Dry mils: 1.4-2.3

Coverage: 264-435 sq.ft. per gallon

**Theoretical Coverage:** 609 sq. ft. per gallon  
@ 1 mil dry

Approximate spreading rates are calculated on volume solids and do not include any application loss.

**Note:** Brush or roll application may require multiple coats to achieve maximum film thickness and uniformity of appearance.

### Drying Schedule @ 5.0 mils wet, @ 50% RH:

Drying, and recoat times are temperature, humidity, and film thickness dependent. Dry fall characteristics will be affected at temperatures below 77°F(25°C) or above 50% RH.

	@50°F	@77°F	@100°F
To touch	1 hour	30 minutes	15 minutes
To handle	2 hours	1 hour	30 minutes
To recoat	4 hours	2 hours	1 hour
To dryfall	10-15 ft.	10 ft.	10 ft.

### Tinting with CCE only:

Tinting will affect dryfall characteristics.

Base	oz. per gallon	Strength
Extra White	0-6	SherColor
Ultradeep Base	10-14	SherColor

### Extra White B66W01551

(may vary by color)

### V.O.C. (less exempt solvents):

less than 50 grams per litre; 0.42 lbs. per gallon  
As per 40 CFR 59.406

**Volume Solids:** 38 ± 2%

**Weight Solids:** 50 ± 2%

**Weight per Gallon:** 10.25 lb

**Flash Point:** N/A

**Vehicle Type:** Acrylic

**Shelf Life:** 24 months, unopened

## COMPLIANCE

As of 11/18/2021, Complies with:

OTC	Yes
OTC Phase II	Yes
S.C.A.Q.M.D.	Yes
CARB	Yes
CARB SCM 2007	Yes
CARB SCM 2020	Yes
Canada	Yes
LEED® v4 & v4.1 Emissions	No
LEED® v4 & v4.1 V.O.C.	Yes
EPD-NSF® Certified	No
MIR-Manufacturer Inventory	No
MPI®	Yes

## APPLICATION

### Temperature:

minimum	50°F
maximum	100°F
air, surface, and material	
At least 5°F above dew point	

**Relative humidity:** 85% maximum

The following is a guide. Changes in pressures and tip sizes may be needed for proper spray characteristics. Always purge spray equipment before use with listed reducer. Any reduction must be compatible with the existing environmental and application conditions.

**Reducer:** Water

### Airless Spray:

Pressure	2000 p.s.i.
Hose	1/4 inch I.D.
Tip	.013 - .017 inch
Filter	60 mesh

### Conventional Spray:

Gun	Binks 95
Fluid Nozzle	63 C
Air Nozzle	63 FB
Atomization Pressure	60 p.s.i.
Fluid Pressure	50 p.s.i.

Reduction: Not recommended

**Brush** Nylon-polyester

**Roller Cover** 1/4 inch woven

If specific application equipment is listed above, equivalent equipment may be substituted.

Apply paint at the recommended film thickness and spreading rate as indicated. Application of coating above maximum or below minimum recommended spreading rate may adversely affect coating performance.

When using spray application, use a 50% overlap with each pass of the gun to avoid holidays, bare areas, and pinholes. If necessary, cross spray at a right angle.

Overspray landing on hot surfaces may adhere to these surfaces. Immediately remove overspray from hot surfaces before adhesion occurs.

No painting should be done immediately after a rain or during foggy weather.

Do not paint on wet surfaces.  
Check adhesion by applying a test strip to determine the readiness for painting.

## SPECIFICATIONS

### Steel\*

2 coats Pro Industrial Multi-Surface Acrylic

### Steel:

1 coat Pro Industrial Pro-Cryl Primer  
or Pro Industrial DTM Primer/Finish  
or Kem Bonds HS  
or Zinc Clad Primer  
1-2 coats Pro Industrial Multi-Surface Acrylic

### Aluminum:

1-2 coats Pro Industrial Multi-Surface Acrylic

### Aluminum (Water Based Primer):

1 coat Pro Industrial Pro-Cryl Primer  
1-2 coats Pro Industrial Multi-Surface Acrylic

### Concrete Block (CMU):

1 coat Pro Industrial Heavy Duty Blockfiller  
or Loxon Acrylic Block Surfer  
1-2 coats Pro Industrial Multi-Surface Acrylic

### Concrete/Masonry:

1 coat Loxon Concrete & Masonry Primer (if needed)  
or Loxon Conditioner (if needed)  
2 coats Pro Industrial Multi-Surface Acrylic

### Drywall:

1 coat ProMar 200 Zero V.O.C. Primer  
1-2 coats Pro Industrial Multi-Surface Acrylic

### Galvanizing:

2 coats Pro Industrial Multi-Surface Acrylic

### Pre-Finished Siding: (Baked-on finishes)

1 coat Bond-Plex Waterbased Acrylic  
or DTM Bonding Primer  
1-2 coats Pro Industrial Multi-Surface Acrylic

### Wood, exterior:

1 coat Exterior Wood Primer  
1-2 coats Pro Industrial Multi-Surface Acrylic

### Wood, interior:

1 coat Premium Wall & Wood Primer  
1-2 coats Pro Industrial Multi-Surface Acrylic

\*Primer recommended for best performance

# Pro Industrial™

## Multi-Surface Acrylic Semi-Gloss

### SURFACE PREPARATION

**WARNING!** Removal of old paint by sanding, scraping or other means may generate dust or fumes that contain lead. Exposure to lead dust or fumes may cause brain damage or other adverse health effects, especially in children or pregnant women. Controlling exposure to lead or other hazardous substances requires the use of proper protective equipment, such as a properly fitted respirator (NIOSH approved) and proper containment and cleanup. For more information, call the National Lead Information Center at 1-800-424-LEAD (in US) or contact your local health authority.

#### **Do not use hydrocarbon solvents for cleaning.**

Remove all surface contamination by washing with an appropriate cleaner, rinse thoroughly and allow to dry. Existing peeled or checked paint should be scraped and sanded to a sound surface. Glossy surfaces should be sanded dull. Stains from water, smoke, ink, pencil, grease, etc. should be sealed with the appropriate primer/sealer. Recognize that any surface preparation short of total removal of the old coating may compromise the service length of the system.

**Iron & Steel** - Minimum surface preparation is Hand Tool Clean per SSPC-SP2. Remove all oil and grease from surface per SSPC-SP1. For better performance, use Commercial Blast Cleaning per SSPC-SP6. Primer recommended for best performance

**Aluminum** - Remove all oil, grease, dirt, oxide and other foreign material per SSPC-SP1.

**Galvanizing** - Allow to weather a minimum of six months prior to coating. Solvent Clean per SSPC-SP1. When weathering is not possible, or the surface has been treated with chromates or silicates, first Solvent Clean per SSPC-SP1 and apply a test patch. Allow paint to dry at least one week before testing adhesion. If adhesion is poor, brush blasting per SSPC-SP16 is necessary to remove these treatments. Rusty galvanizing requires a minimum of Hand Tool Cleaning per SSPC-SP2, prime the area the same day as cleaned.

**Concrete Block** - Surface should be thoroughly clean and dry. Air, material and surface temperatures must be at least 55°F (13°C) before filling. Use Pro Industrial Heavy Duty Block Filler or Loxon Acrylic Block Surface. The filler must be thoroughly dry before topcoating.

**Masonry** - All masonry must be free of dirt, oil, grease, loose paint, mortar, masonry dust, etc. Clean per SSPC-SP13/Nace 6/ ICRI No. 310.2R, CSP 1-3. Poured, troweled, or tilt-up concrete, plaster, mortar, etc. must be thoroughly cured at least 30 days at 75°F. Form release compounds and curing membranes must be removed by brush blasting. Brick must be allowed to weather for one year prior to surface preparation and painting. Prime the area the same day as cleaned. Weathered masonry and soft or porous cement board must be brush blasted or power tool cleaned to remove loosely adhering contamination and to get to a hard, firm surface. Apply one coat Loxon Conditioner, following label recommendations.

**Wood** - Surface must be clean, dry, and sound. Prime with recommended primer. No painting should be done immediately after a rain or during foggy weather. Knots and pitch streaks must be scraped, sanded and spot primed before full coat of primer is applied. All nail holes or small openings must be properly caulked. Sand to remove any loose or deteriorated surface wood and to obtain a proper surface profile.

### SURFACE PREPARATION

**Previously Painted Surface** - If in sound condition, clean the surface of all foreign material. Smooth, hard or glossy coatings and surfaces should be dulled by abrading the surface. Apply a test area, allowing paint to dry one week before testing adhesion. If adhesion is poor, additional abrasion of the surface and/or removal of the previous coating may be necessary. Retest surface for adhesion. If paint is peeling or badly weathered, clean surface to sound substrate and treat as a new surface as above. Recognize that any surface preparation short of total removal of the old coating may compromise the service length of the system.

**Mildew**- Prior to attempting to remove mildew, it is always recommended to test any cleaner on a small, inconspicuous area prior to use. Bleach and bleaching type cleaners may damage or discolor existing paint films. Bleach alternative cleaning solutions may be advised.

Mildew may be removed before painting by washing with a solution of 1 part liquid bleach and 3 parts water. Apply the solution and scrub the mildewed area. Allow the solution to remain on the surface for 10 minutes. Rinse thoroughly with water and allow the surface to dry before painting. Wear protective eyewear, waterproof gloves, and protective clothing. Quickly wash off any of the mixture that comes in contact with your skin. Do not add detergents or ammonia to the bleach/water solution.

### PERFORMANCE

**System Tested:** (unless otherwise indicated)

**Substrate:** Steel

**Surface Preparation:** SSPC-SP10

**Finish:** 2 coats Pro Industrial Multi-Surface Acrylic B66W01551, 2.5 DFT per coat

#### **Adhesion:**

Method: ASTM D4541

Result: 1385 p.s.i.

#### **Abrasion Resistance:**

Method: ASTM D4060, CS17 wheel, 1000 cycles, 1000 mg load

Result: 52.7 mg loss

#### **Corrosion Weathering\*:**

Method: ASTM D5894, 5 cycles

Result: Rating 10, per ASTM D714 for Blistering. Rating 8 per ASTM D1654 for corrosion

#### **Direct Impact Resistance:**

Method: ASTM D2794

Result: 30 inch lb.

#### **Dry Heat Resistance:**

Method: ASTM D2485

Result: 300°F

#### **Flexibility:**

Method: ASTM D522, 1/8 inch mandrel

Result: Pass

#### **Pencil Hardness:**

Method: 30 days ASTM D3363

Result: 4H

**Water Vapor Permeance (US) :** 24.77 Perms

Method: ASTM D1653 grains/(hr ft<sup>2</sup> in Hg)

\*over Pro Industrial Pro-Cryl Primer

### SAFETY PRECAUTIONS

Before using, carefully read **CAUTIONS** on label.

Refer to the Safety Data Sheets (SDS) before use.

#### **FOR PROFESSIONAL USE ONLY.**

Published technical data and instructions are subject to change without notice. Contact your Sherwin-Williams representative for additional technical data and instructions.

### CLEANUP INFORMATION

Clean spills, spatters, hands and tools immediately after use with soap and warm water. After cleaning, flush spray equipment with compliant cleanup solvent to prevent rusting of the equipment. Follow manufacturer's safety recommendations when using solvents.

HOTW 11/18/2021 B66W01551 08 44  
FRC