

TECHNICAL INFORMATION POWDURA® HYBRID POWDER COATING

CHEMICAL COATINGS

HHF2-C0004 CHAMPANGE METALLIC Bonded Metallic

POWDURA® Hybrid Powder Coating is recommended for a broad range of interior functional and decorative applications.

Performance Tests:

Impact Resistance (ASTM D-2794)	100 Dir./ 100 Rev
Adhesion (ASTM D-3359)	No failure with 1/8" squares
Flexibility (ASTM D-522)	Pass ¼" mandrel bend
Pencil Hardness (ASTM D-3363)	2H

CHARACTERISTICS

60° Gloss	20- 30
Cure Schedule	10 Min @ 400F
Film Thickness Range:	2.0-3.0 Mils
Specific Gravity:	1.46 ± .05
Coverage @ 1.0 mil	131.71 sq. ft /lb

Typical Environmental Properties: On B1000 Panels

Salt Fog (ASTM B-117)	1000 hours
Humidity (ASTM D-4585)	1000 hours

Storage:

Powdura® Hybrid Powder Coatings should be kept in a dry and cool area at temperatures below 75°F (24° C). Shelf life ranges from 6 months to over 1 year. When not in use, store powder in sealed containers: fine powders are hygroscopic.

SPECIFICATIONS

General: Substrate should be free of grease, oil, dirt, fingerprints, drawing compounds, any contamination, and surface preparation treatments to ensure optimum adhesion and coating performance properties. The use of a chemical conversion coating prior to the application of a powder coating is strongly recommended. Consult Metal Preparation Brochure CC-T1 for additional details.

Aluminum: A minimum of a 5-stage chrome phosphate metal treatment, or equivalent, is required for good adhesion and optimum coating performance properties.

Testing: Due to the wide variety of substrates, surface preparation methods, application methods, and environments, the customer should test the complete system for adhesion and compatibility prior to full-scale application.

Product Limitations:

- For interior applications only.
- Contact your Sherwin-Williams
- Representative where use of this product at higher than recommended film thickness may be required.

APPLICATION

Powder coatings must be applied using suitable electrostatic equipment. Consult your Sherwin-Williams Representative regarding unique applications.

CAUTIONS

Thoroughly review product label for safety and cautions prior to using this product. Please direct any questions or comments to your local Sherwin-Williams facility.

CAUTION! Causes eye irritation, causes skin irritation, may cause allergic skin reaction, respiratory irritant, dust may cause eye and respiratory irritation, dust may form an explosive mixture in air. Avoid breathing dust. Avoid contact with eyes and prolonged or repeated contact with skin. Use protective clothing and NIOSH approved respirator. Do not use near sparks or open flame or any type of ignition source. Wash thoroughly after handling, and use only with adequate ventilation.

FIRST AID:

If on SKIN: Wash thoroughly with soap and water.

If in EYES: Flush with water immediately and procure medical attention. The area adjacent to the coating operation should be properly ventilated. Cure ovens must be exhausted to the outside atmosphere. All dusts are respiratory irritants; inhalation of the dust should be avoided. To avoid static electricity build-up, properly ground all equipment. Provide dust collection equipment with adequate explosion venting; dust clouds of any finely divided organic material can be ignited by open flame or electrical sparks.

DO NOT TAKE INTERNALLY.

KEEP OUT OF REACH OF CHILDREN.

FOR INDUSTRIAL USE ONLY.

REFER TO MATERIAL SAFETY DATA SHEET FOR ADDITIONAL INFORMATION.

Note:

Product Data Sheets are periodically updated to reflect new information relating to the product. It is important that the customer obtain the most recent Product Data Sheet for the product being used. The information, rating and opinions stated above pertain to the material currently offered and represent the results of tests believed to be reliable. However, due to variations in customer handling and methods of application, which are not known, or under our control, The Sherwin-Williams Company cannot make any warranties or guaranties as to the end results.

Arlington, TX November 16, 2004