



# TECHNICAL INFORMATION

## POWDURA® RAL SERIES SUPERDURABLE POLYESTER TGIC-FREE POWDER COATING

### PRODUCT DESCRIPTION

RWS8-00006

RAL 9003 GL SD

**POWDURA® RAL series Superdurable Polyester TGIC-Free powder coatings** are recommended for a broad range of interior / exterior decorative applications. They are designed to meet AAMA 2603 and provide superior weatherability compared to standard polyester powder coatings.

#### Advantages:

- Excellent exterior color and gloss retention
- Excellent overbake resistance
- Good chemical resistance

Many applications, including:

Windows

Doors

Frames

Railings

Fencing

Heavy Equipment

#### Storage: Powdura® Powder Coatings

should be kept in a dry and cool area at temperatures below 80°F (27°C). When not in use, store powder in sealed containers: fine powders are hygroscopic.

**Substrate Preparation:** Substrate should be free of grease, oil, dirt, fingerprints, drawing compounds, any contamination, and surface preparation treatments to ensure optimum adhesion and coating performance properties. The use of a chemical conversion coating prior to the application of a powder coating is strongly recommended.

**Testing:** Due to the wide variety of substrates, surface preparation methods, application methods, and environments, the customer should test the complete system for adhesion, compatibility and performance prior to full-scale application.

### CAUTIONS

Thoroughly review product SDS prior to using this product. Please consult your local sales representative or your local Sherwin-Williams facility for additional information.

### APPLICATION

**Cure Schedule:** 10 min. @ 400°F  
10 min. @ 204°C

**Film Thickness Range(mils):** 2.0-3.0 MILS

### ATTRIBUTES

**Specific Gravity(g/ml):** 1.66

**Coverage at 1.0 Mil(ft<sup>2</sup>/lb):** 116.1

**60° Gloss:** 83-100  
(ASTM D-523)

**Adhesion:** 5B  
(ASTM D-3359)

**Flexibility:** Pass 1/8"  
(ASTM D-522)

**Pencil Hardness:** H-2H  
(ASTM D-3363)

**Impact Resistance(in.lb):** Dir 80 in-lbs  
(ASTM D-2794) Rev 80 in-lbs

**Salt Spray(ASTM B-117)**  
max 1/8" Creepage 1000 hours

**Note:** Performance measured using  
24-gauge Bonderite® 1000 test panels.

**Shelf Life:** 24 Months

Sherwin-Williams recommends that all material be used in FIFO order ( first in - first out). Materials that exceed the recommended shelf life should be tested prior to use.

#### Note:

Product Data Sheets are periodically updated to reflect new information relating to the product. It is important that the customer obtain the most recent Product Data Sheet for the product being used. The information, rating and opinions stated above pertain to the material currently offered and represent the results of tests believed to be reliable. However, due to variations in customer handling and methods of application, which are not known, or under our control, The Sherwin-Williams Company cannot make any warranties or guaranties as to the end results.

24 00

Grove City Powder R&D

12-Dec-2023



SHERWIN WILLIAMS POWDURA  
POWDER. THIS PRODUCT IS A  
RECOGNIZED COMPONENT, BY  
UNDERWRITERS LABORATORIES  
FILE NUMBER: MH26239