



111.16

# H&C® PAVER SEALER GLOSS WATER BASED

## PRODUCT DESCRIPTION

H&C® Gloss Paver Sealer is a premium quality 100% acrylic sealer that penetrates and protects all types of porous decorative pavers. This single component, solvent free, VOC compliant penetrating sealer will enhance the appearance of pavers while providing excellent weather and water resistance. H&C® Gloss Paver Sealer will apply milky white to ensure complete coverage, but dries to a clear transparent finish.

### Where to use:

- Patios
- Lanai
- Driveways
- Walkways
- Pool Decks
- Brick and Concrete Retaining Walls

Note: This product is intended for use on bare unsealed pavers and masonry surfaces. To determine porosity, splash water on the surface to be protected. If the water rapidly absorbs and darkens the surface, the surface is porous and can be sealed after following complete surface preparation. If the surface does not darken with water this means the surface has been treated and the H&C® Gloss Paver Sealer may not be compatible with a previous treatment. A test area should be coated before complete application is done. Please contact 1-800-TO STAIN (867-8246) for further assistance.

## CHARACTERISTICS

**Color:** Applies Milky White Dries Clear

**Coverage** **sq ft/gal**  
Standard Brick Paver 100-150

**Drying Time, @ 77°F, 50% RH:**  
temperature and humidity dependent  
To Touch: 1 hour  
Recoat: 4 hours  
Light traffic: 24 hours  
Heavy traffic: 72 hours

\*NOTE: High humidity and /or low temperatures will affect drying time.

**Finish:** Gloss  
**Vehicle Type:** Acrylic

**VOC (less exempt solvents):** 98 g/L

**Volume Solids:** 26% +/-2%

### Coefficient of Friction

Without Slip Resistant: .7  
With Slip Resistant: .85

## SURFACE PREPARATION

**WARNING!** Removal of old paint by sanding, scraping or other means may generate dust or fumes that contain lead. Exposure to lead dust or fumes may cause brain damage or other adverse health effects, especially in children or pregnant women. Controlling exposure to lead or other hazardous substances requires the use of proper protective equipment, such as a properly fitted respirator (NIOSH approved) and proper containment and cleanup. For more information, call the National Lead Information Center at 1-800-424-LEAD (in US) or contact your local health authority.

**Testing: Due** to the wide variety of substrates, preparation methods, application methods and environments, the customer should test the product in an inconspicuous spot for penetration and compatibility **prior to full scale application.**

### Bare Brick Pavers:

This product should be applied to a clean surface free of oil, grease and mildew. H&C® Cleaner Degreaser mixed 50% with water will remove light soil from the surface. H&C® Cleaner Degreaser should be used full strength on heavy oil and grease stains. Refer to the H&C® Cleaner Degreaser label for specific instructions. All excess joint sand should be swept off the surface prior to application of the sealer. Do not apply H&C® Gloss Paver Sealer if rain is imminent or expect within 12 hours of application.



# H&C® PAVER SEALER GLOSS WATER BASED

## APPLICATION

**Determine if conditions are proper for application:**

For best results, surface and air temperature should be above 50°F and below 95°F. Temperature should not fall below 40°F for 24 hours following application. This product can be applied with a brush and roller or airless spray equipment. Brushes and Rollers should be of synthetic material and nap thickness should not exceed ¾". If airless spraying, tip orifice should not exceed .017". When spraying, back roll sealer to ensure an even finish.

Newly installed pavers should weather a minimum of 60 days before sealing and one coat of sealer is normally sufficient. Older and more weathered surfaces may require a second coat of sealer to improve final appearance. Allow 4 hours minimum dry time between coats. Do not over apply as blushing may result. Contact H&C Technical Services if blushing persists (800-867-8246). Approximate coverage is 100-150 square feet per gallon. The coverage will vary depending on the texture and density of the concrete or clay pavers. The H&C® Gloss Paver Sealer will apply milky white and dry clear in approximately 1 hour.

Vertical surfaces, such as retaining walls, should be coated in the same manner as described above.

### **Slip Resistance**

Some surfaces may require a slip-resistant additive for safety. Add **H&C® SharkGrip Slip Resistant Additive** to the final coat, following label directions. **H&C® SharkGrip Slip Resistant Additive** should not be used in place of a non-skid finish.

## CLEANUP INFORMATION

Clean sprayer and tools with soap and water immediately after use. Spray clear water through the line of the sprayer until the water runs clear.

## MAINTENANCE

Clean light to medium soiled surfaces with a 50/50 solution of H&C® Cleaner Degreaser to water. Use H&C® Cleaner Degreaser at full strength for heavy soiled areas, such as oil and grease stains. If H&C® Cleaner Degreaser is not available, use a good quality neutral based cleaner degreaser following manufacturer's directions for use.

## WARNING

- Use with adequate ventilation
- Keep out of the reach of children
- Use a NOISH approved respirator, when necessary
- Do not take internally
- In case of ingestion, CALL A PHYSICIAN immediately. DO NOT induce vomiting

## TECHNICAL SERVICES

1-800-TO STAIN(867-8246)  
www.hc-concrete.com

## ORDERING INFORMATION

### **Part Numbers**

Gallon 50.047054-16  
Five 50.047055-20

### **SMIS Numbers**

Gallon 155-6513  
Five 155-6521

The information and recommendations set forth in this Product Data Sheet are based upon tests conducted by or on behalf of H&C concrete coatings and The Sherwin-Williams Company. Such information and recommendations set forth herein are subject to change and pertain to the product offered at the time of publication. Consult your H&C or Sherwin-Williams representative to obtain the most recent Product Data sheet.