



**Protective
&
Marine
Coatings**



MACROPOXY® 846 PW WINTER GRADE EPOXY

PART A
PART A
PART A
PART B

B58H710
B58W710
B58L700
B58V700

BUFF
OFF WHITE
LIGHT BLUE
HARDENER

Revised: July 24, 2014

PRODUCT INFORMATION

4.54

PRODUCT DESCRIPTION

MACROPOXY 846 PW WINTER GRADE EPOXY is a high solids, fast drying polyamide epoxy classified by UL to NSF Standard 61 as a tank lining for potable water storage tanks. Recommended for use at temperatures as low 35°F (1.6°C). Ideal for maintenance painting and fabrication shops when minimum downtime and short handling times are required.

- Low odor
- Abrasion and chemical resistant
- Outstanding application properties

PRODUCT CHARACTERISTICS

Finish: Semi-Gloss
Color: Buff, Off White and Light Blue
Volume Solids: 68% ± 2%, mixed
Weight Solids: 82% ± 2%, mixed
VOC (EPA Method 24): Unreduced: <300g/L; 2.50 lb/gal
Mix Ratio: 1:1 by volume

Recommended Spreading Rate per coat:

	Standard		AWWA	
	Min.	Max.	Min.	Max.
Wet mils (microns)	6.0	150	12.0	300
Dry mils (microns)	4.0	100	8.0*	200*
~Coverage sq ft/gal (m ² /L)	136	3.3	272	6.6
Theoretical coverage sq ft/gal (m ² /L) @ 1 mil/25 micron dft	1088 (26.6)			

*NOTE: Brush or roll application may require multiple coats to achieve maximum film thickness and uniformity of appearance.
See Recommended Systems on reverse side

Drying Schedule @ 6.0 mils wet (150 microns):

	@ 40°F/4.5°C	@ 75°F/24°C 50% RH
To touch:	1 hour	45 minutes
To handle:	8 hours	4 hours
To recoat:		
minimum:	8 hours	4 hours
maximum:	30 days	30 days
Cure for		
immersion:	14 days	7 days

*If maximum recoat time is exceeded, abrade surface before recoating.
Drying time is temperature, humidity, and film thickness dependent.*

Pot Life: 3 hours 2 hours
Sweat-in-Time: 30 minutes 15 minutes
 For Potable Water Service, allow a minimum cure time of 7 days at 77°F (25°C) prior to placing in service. Sterilize and rinse per AWWA C652.

Shelf Life: 36 months, unopened
Store indoors at 40°F (4.5°C) to 100°F (38°C).
Flash Point: 80°F (27°C) TCC, mixed
Reducer/Clean Up: Reducer R7K15

RECOMMENDED USES

Potable Water Tank Restrictions

Water Contact Temp: 23°C
 Standard Cure; Tanks >=1,500 gal: 2 cts
 Maximum DFT: 8 mils/ct, 2 cts

- Not recommended for use at temperatures above 75°F (24°C)
- For use over prepared steel surfaces in other industrial exposures.
- Conforms to AWWA D102 ICS #1, #2, and #5, and OCS #5.***

PERFORMANCE CHARACTERISTICS

Substrate*: Steel

Surface Preparation*: SSPC-SP10/NACE 2

System Tested*:

1 ct. Macropoxy 846 PW Winter Grade @ 6.0 mils (150 microns) dft
 *unless otherwise noted below

Test Name	Test Method	Results
Abrasion Resistance	ASTM D4060, CS17 wheel, 1000 cycles, 1 kg load	100 mg loss
Adhesion	ASTM D4541	710 psi
Direct Impact Resistance	ASTM G14	25 in. lb.
Dry Heat Resistance	ASTM D2485	250°F (121°C)
Flexibility	ASTM D522, 180° bend, 1¼" mandrel	Passes
Immersion¹	5 year potable water	Rating 10 per ASTM D610 for Rusting; Rating 10 per ASTM D714 for Blistering
Immersion	18 months fresh and salt water	Passes, no rusting, blistering, or loss of adhesion
Pencil Hardness	ASTM D3363	3H
Salt Fog Resistance	ASTM B117, 1000 hours	Passes

Epoxy coatings may darken or discolor following application and curing.

Footnotes:

¹ Galvapak/2 cts. Macropoxy 646 PW



Protective & Marine Coatings



MACROPOXY® 846 PW WINTER GRADE EPOXY

PART A
PART A
PART A
PART B

B58H710
B58W710
B58L700
B58V700

BUFF
OFF WHITE
LIGHT BLUE
HARDENER

Revised: July 24, 2014

PRODUCT INFORMATION

4.54

RECOMMENDED SYSTEMS

Dry Film Thickness / ct.

Mils (Microns)

Immersion, *Steel:

*AWWA D102: Inside Coating System No. 1

minimum AWWA	8.0	(200)
1 ct. Macropoxy 846 PW	3.0	(75)
1 ct. Macropoxy 846 PW	5.0	(125)

*AWWA D102: Inside Coating System No. 2

minimum AWWA	12.0	(300)
1 ct. Macropoxy 846 PW	3.0	(75)
1 ct. Macropoxy 846 PW	4.0	(100)
1 ct. Macropoxy 846 PW	5.0	(125)

*AWWA D102: Inside Coating System No. 5

minimum AWWA	10.0	(250)
1 ct. Corothane I – Galvapac NSF	2.0	(50)
1 ct. Macropoxy 846 PW	4.0	(100)
1 ct. Macropoxy 846 PW	4.0	(100)

Concrete/ Masonry, Smooth:

2 cts. Macropoxy 846 PW	4.0-8.0	(100-200)
-------------------------	---------	-----------

Atmospheric, Steel:

*AWWA D102: Outside Coating System No. 5

minimum AWWA	6.0	(150)
1 ct. Macropoxy 846 PW	2.0	(50)
1 ct. Macropoxy 846 PW	2.0	(50)
1 ct. Acrolon 218HS	2.0	(50)

*AWWA D102: Outside Coating System No. 6

minimum AWWA	6.0	(150)
1 ct. Corothane I – Galvapac NSF	2.0	(50)
1 ct. Macropoxy 846 PW	2.0	(50)
1 ct. Acrolon 218HS	2.0	(50)

The systems listed above are representative of the product's use, other systems may be appropriate.

DISCLAIMER

The information and recommendations set forth in this Product Data Sheet are based upon tests conducted by or on behalf of The Sherwin-Williams Company. Such information and recommendations set forth herein are subject to change and pertain to the product offered at the time of publication. Consult your Sherwin-Williams representative to obtain the most recent Product Data Information and Application Bulletin.

SURFACE PREPARATION

Surface must be clean, dry, and in sound condition. Remove all oil, dust, grease, dirt, loose rust, and other foreign material to ensure adequate adhesion.

Refer to product Application Bulletin for detailed surface preparation information.

Minimum recommended surface preparation:

Iron & Steel
Atmospheric: SSPC-SP2/3
Immersion: SSPC-SP10/NACE 2, 2-3 mil (50-75 micron) profile

Concrete & Masonry
Immersion: SSPC-SP13/NACE 6-4.3.1 or 4.3.2, or ICRI No. 310.2R, CSP1-3

Surface Preparation Standards

Condition of Surface	ISO 8501-1 BS7079:A1	Swedish Std. SIS055900	SSPC	NACE
White Metal	Sa 3	Sa 3	SP 5	1
Near White Metal	Sa 2.5	Sa 2.5	SP 10	2
Commercial Blast	Sa 2	Sa 2	SP 6	3
Brush-Off Blast	Sa 1	Sa 1	SP 7	4
Hand Tool Cleaning	C St 2	C St 2	SP 2	-
Pitted & Rusted	D St 2	D St 2	SP 2	-
Rusted	C St 3	C St 3	SP 3	-
Power Tool Cleaning	Pitted & Rusted D St 3	D St 3	SP 3	-

TINTING

Tint with Maxitones colorants at 75% tint strength into Part A. Tinted colors will be slightly darker than the standards. Five minutes minimum mixing on a mechanical shaker is required for complete mixing of color.

Do not tint for Immersion Service.

APPLICATION CONDITIONS

Temperature: 35°F (1.6°C) minimum, 75°F (24°C) maximum (air, surface, and material)
Surface temperature must be at least 5°F (2.8°C) above dew point
Relative humidity: 85% maximum

Refer to product Application Bulletin for detailed application information.

ORDERING INFORMATION

Packaging:
Part A: 1 gallon (3.78L) and 5 gallon (18.9L) container
Part B: 1 gallon (3.78L) and 5 gallon (18.9L) container

Weight: 12.3 ± 0.2 lb/gal ; 1.48 Kg/L, mixed

SAFETY PRECAUTIONS

Refer to the MSDS sheet before use.

Published technical data and instructions are subject to change without notice. Contact your Sherwin-Williams representative for additional technical data and instructions.

WARRANTY

The Sherwin-Williams Company warrants our products to be free of manufacturing defects in accord with applicable Sherwin-Williams quality control procedures. Liability for products proven defective, if any, is limited to replacement of the defective product or the refund of the purchase price paid for the defective product as determined by Sherwin-Williams. NO OTHER WARRANTY OR GUARANTEE OF ANY KIND IS MADE BY SHERWIN-WILLIAMS, EXPRESSED OR IMPLIED, STATUTORY, BY OPERATION OF LAW OR OTHERWISE, INCLUDING MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE.



Protective & Marine Coatings



MACROPOXY® 846 PW WINTER GRADE EPOXY

PART A	B58H710	BUFF
PART A	B58W710	OFF WHITE
PART A	B58L700	LIGHT BLUE
PART B	B58V700	HARDENER

Revised: July 24, 2014

APPLICATION BULLETIN

4.54

SURFACE PREPARATIONS

Surface must be clean, dry, and in sound condition. Remove all oil, dust, grease, dirt, loose rust, and other foreign material to ensure adequate adhesion.

Carbon Steel, Immersion Service:

Clean and degrease the surface prior to abrasive blasting per SSPC-SP1 Solvent Cleaning. Methods described in SSPC-SP1 include solvents, alkali, detergent/water, emulsions, and steam. The surface shall be abrasive blasted to SSPC-SP10/NACE No. 2 Near-White Blast Cleaning with a 2-3 mil (50-75 micron) profile. The anchor pattern shall be sharp with no evidence of a polished surface. The finished surface shall be free of all visible oil, grease, dust, dirt, mill scale, rust, coating, oxides, corrosion products, and other foreign matter with no more than 5% staining. After blasting, all dust and loose residue should be removed from the surface by acceptable means. Coat steel the same day as it is prepared and prior to the formation of rust.

Iron & Steel, Atmospheric Service:

Minimum surface preparation is Hand Tool Clean per SSPC-SP2. Remove all oil and grease from surface by Solvent Cleaning per SSPC-SP1. For better performance, use Commercial Blast Cleaning per SSPC-SP6/NACE 3, blast clean all surfaces using a sharp, angular abrasive for optimum surface profile (2 mils / 50 microns). Prime any bare steel within 8 hours or before flash rusting occurs.

Ductile Iron, Immersion Service:

Refer to National Association of Pipe Fabricators Surface Preparations Standard NAF 500-03 as follows:

- NAF 500-03-01 "Solvent Cleaning"
- NAF 500-03-02 "Hand Tool Cleaning"
- NAF 500-03-03 "Power Tool Cleaning"
- NAF 500-03-04 "Abrasive Blast Cleaning of Ductile Iron Pipe".

Concrete and Masonry

For surface preparation, refer to SSPC-SP13/NACE 6, or ICRI No. 310.2R, CSP 1-3. Surfaces should be thoroughly clean and dry. Concrete and mortar must be cured at least 28 days @ 75°F (24°C). Remove all loose mortar and foreign material. Surface must be free of laitance, concrete dust, dirt, form release agents, moisture curing membranes, loose cement and hardeners. Fill bug holes, air pockets and other voids with Steel-Seam FT910.

Follow the standard methods listed below when applicable:

- ASTM D4258 Standard Practice for Cleaning Concrete.
- ASTM D4259 Standard Practice for Abrading Concrete.
- ASTM D4260 Standard Practice for Etching Concrete.
- ASTM F1869 Standard Test Method for Measuring Moisture Vapor Emission Rate of Concrete.
- SSPC-SP 13/NACE 6 Surface Preparation of Concrete.
- ICRI No. 310.2R Concrete Surface Preparation.

Concrete, Immersion Service:

For surface preparation, refer to SSPC-SP13/NACE 6, Section 4.3.1 or 1.3.2 or ICRI No. 310.2R, CSP 1-3.

Previously Painted Surfaces:

If in sound condition, clean the surface of all foreign material. Scarify the surface to create the desired surface profile. Apply coatings on a test area, allowing paint to dry one week before testing adhesion. If adhesion is poor, or if this product attacks the previous finish, removal of the previous coating may be necessary.

Surface Preparation Standards

Condition of Surface	ISO 8501-1 BS7079:A1	Swedish Std. SIS055900	SSPC	NACE
White Metal	Sa 3	Sa 3	SP 5	1
Near White Metal	Sa 2.5	Sa 2.5	SP 10	2
Commercial Blast	Sa 2	Sa 2	SP 6	3
Brush-Off Blast	Sa 1	Sa 1	SP 7	4
Hand Tool Cleaning	C St 2	C St 2	SP 2	-
Pitted & Rusted	D St 2	D St 2	SP 2	-
Rusted	C St 3	C St 3	SP 3	-
Power Tool Cleaning	D St 3	D St 3	SP 3	-

APPLICATION CONDITIONS

Temperature:	35°F (1.6°C) minimum, 75°F (24°C) maximum (air, surface, and material) Surface temperature must be at least 5°F (2.8°C) above dew point
Relative humidity:	85% maximum

APPLICATION EQUIPMENT

The following is a guide. Changes in pressures and tip sizes may be needed for proper spray characteristics. Always purge spray equipment before use with listed reducer. Any reduction must be compliant with existing VOC regulations and compatible with the existing environmental and application conditions.

Reducer/Clean UpReducer R7K15

Airless Spray

Unit.....	30:1 Pump
Pressure.....	2800-3000 psi
Hose.....	1/4" ID
Tip.....	017" - .023"
Filter.....	60 mesh
Reduction.....	As needed up to 12% by volume

Conventional Spray

Oil and moisture separators recommended	
Gun.....	DeVilbiss MBC-510
Fluid Tip.....	E
Air Cap.....	704
Atomization Pressure.....	60-65 psi
Fluid Pressure.....	10-20 psi
Reduction.....	As needed up to 12% by volume

Brush

Brush.....	Nylon/Polyester or Natural Bristle
Reduction.....	As needed up to 12% by volume

Roller

Cover.....	3/8" woven with solvent resistant core
Reduction.....	As needed up to 12% by volume

Recommended Spreading Rate per coat:

	Standard	AWWA
Wet mils (microns):	6.0 (150) - 12.0 (300)	4.4 (110) - 8.8 (220)
Dry mils (microns):	4.0 (100) - 8.0* (200)	3.0 (75) - 6.0* (150)
Coverage:	136 (3.3) - 272 (6.6) sq ft/gal (m ² /L)	181 (4.4) - 362 (8.8)

* See recommended systems on Product Information page

If specific application equipment is not listed above, equivalent equipment may be substituted.



Protective & Marine Coatings



MACROPOXY[®] 846 PW WINTER GRADE EPOXY

PART A B58H710
PART A B58W710
PART A B58L700
PART B B58V700

BUFF
OFF WHITE
LIGHT BLUE
HARDENER

Revised: July 24, 2014

APPLICATION BULLETIN

4.54

APPLICATION PROCEDURES

Surface preparation must be completed as indicated.

Mix contents of each component thoroughly using low speed power agitation. Make certain no pigment remains on the bottom of the can. Then combine one part by volume of Part A with one part by volume of Part B. Thoroughly agitate the mixture with power agitation. Allow the material to sweat-in as indicated prior to application. Re-stir before using. If reducer solvent is used, add only after both components have been thoroughly mixed, after sweat-in.

Apply paint at the recommended film thickness and spreading rate as indicated below:

Recommended Spreading Rate per coat:

	Standard		AWWA	
	Min.	Max.	Min.	Max.
Wet mils (microns)	6.0	150	12.0	300
Dry mils (microns)	4.0	100	8.0*	200*
Coverage sq ft/gal (m ² /L)	136	3.3	272	6.6
Theoretical coverage sq ft/gal (m ² /L) @ 1 mil/25 micron dft	1088 (26.6)			

NOTE: Brush or roll application may require multiple coats to achieve maximum film thickness and uniformity of appearance.

*See Recommended Systems on reverse side

Drying Schedule @ 6.0 mils wet (150 microns):

	@ 40°F/4.5°C	@ 75°F/24°C 50% RH
To touch:	1 hour	45 minutes
To handle:	8 hours	4 hours
To recoat:		
minimum:	8 hours	4 hours
maximum:	30 days	30 days
Cure for		
immersion:	14 days	7 days

If maximum recoat time is exceeded, abrade surface before recoating.
Drying time is temperature, humidity, and film thickness dependent.

Pot Life: 3 hours 2 hours
Sweat-in-Time: 30 minutes 15 minutes
For Potable Water Service, allow a minimum cure time of 7 days at 77°F (25°C) prior to placing in service. Sterilize and rinse per AWWA C652.

Application of coating above maximum or below minimum recommended spreading rate may adversely affect coating performance.

CLEAN UP INSTRUCTIONS

Clean spills and spatters immediately with Reducer R7K15. Clean tools immediately after use with Reducer R7K15. Follow manufacturer's safety recommendations when using any solvent.

DISCLAIMER

The information and recommendations set forth in this Product Data Sheet are based upon tests conducted by or on behalf of The Sherwin-Williams Company. Such information and recommendations set forth herein are subject to change and pertain to the product offered at the time of publication. Consult your Sherwin-Williams representative to obtain the most recent Product Data Information and Application Bulletin.

PERFORMANCE TIPS

Stripe coat all crevices, welds, and sharp angles to prevent early failure in these areas.

When using spray application, use a 50% overlap with each pass of the gun to avoid holidays, bare areas, and pinholes. If necessary, cross spray at a right angle

Spreading rates are calculated on volume solids and do not include an application loss factor due to surface profile, roughness or porosity of the surface, skill and technique of the applicator, method of application, various surface irregularities, material lost during mixing, spillage, overthinning, climatic conditions, and excessive film build.

Excessive reduction of material can affect film build, appearance, adhesion, and UL classification to NSF 61 approval.

Do not apply the material beyond recommended pot life.

Do not mix previously catalyzed material with new.

In order to avoid blockage of spray equipment, clean equipment before use or before periods of extended downtime with Reducer R7K15.

Not recommended for use at temperatures greater than 75°F (24°C).

Tinting is not recommended for immersion service.

Insufficient ventilation, incomplete mixing, miscatalyzation, and external heaters may cause premature yellowing.

Excessive film build, poor ventilation, and cool temperatures may cause solvent entrapment and premature coating failure.

For Immersion Service: (if required) Holiday test in accordance with ASTM D5162 for steel, or ASTM D4787 for concrete.

Refer to Product Information sheet for additional performance characteristics and properties.

SAFETY PRECAUTIONS

Refer to the MSDS sheet before use.

Published technical data and instructions are subject to change without notice. Contact your Sherwin-Williams representative for additional technical data and instructions.

WARRANTY

The Sherwin-Williams Company warrants our products to be free of manufacturing defects in accord with applicable Sherwin-Williams quality control procedures. Liability for products proven defective, if any, is limited to replacement of the defective product or the refund of the purchase price paid for the defective product as determined by Sherwin-Williams. NO OTHER WARRANTY OR GUARANTEE OF ANY KIND IS MADE BY SHERWIN-WILLIAMS, EXPRESSED OR IMPLIED, STATUTORY, BY OPERATION OF LAW OR OTHERWISE, INCLUDING MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE.