



Protective & Marine Coatings

QUICK-KICK® EPOXY ACCELERATOR

B60V200

Revised: October 2, 2023

PRODUCT INFORMATION

4.99

Quick-Kick Epoxy Accelerator is designed for use in select Sherwin-Williams epoxy coatings to enhance drying times. Use up to 4 oz of Quick-Kick Epoxy Accelerator to 1 mixed gallon of the respective coating. Add Quick-Kick Epoxy Accelerator immediately after catalyzing.

Please note that the use of Quick-Kick Epoxy Accelerator:

- Will shorten the pot life (working time) of the material
- Not recommended for immersion service
- May cause premature yellowing of the coating
- May cause brittleness of the coating

Packaging: Quarts and Gallons
Shelf Life: 1 year, unopened
Store indoors at 40°F (4.5°C) to 100°F (38°C).

	Standard Product	4 oz. Quik-Kick Accelerator	Standard Product	4 oz./gal. Accelerator
Macropoxy HS	@ 50°F (10°C)	@ 50°F (10°C)	@ 77°F (25°C)	@ 77°F (25°C)
Touch	7 hours	5 hours	5 hours	1 hours
Recoat	24 hours	7 hours	18 hours	3.5 hours
Pot Life	6 hours	1.5 hours	2 hours	1 hours
Macropoxy 646	@ 35°F (1.7°C)	@ 40°F (4.5°C)	@ 77°F (25°C)	@ 77°F (25°C)
Touch	4-5 hours	1-2 hours	2 hours	30 min.
Recoat	48 hours	24 hours	8 hours	3.5 hours
Pot Life	10 hours	4 hours	4 hours	2 hours
Macropoxy 646-100	@ 35°F (1.7°C)	@ 40°F (4.5°C)	@ 77°F (25°C)	@ 77°F (25°C)
Touch	4-5 hours	1-2 hours	2 hours	30 min.
Recoat	48 hours	24 hours	8 hours	3.5 hours
Pot Life	10 hours	4 hours	4 hours	2 hours
Pro Industrial High Performance Epoxy	@ 50°F (10°C)	@ 50°F (10°C)	@ 77°F (25°C)	@ 77°F (25°C)
Touch	10 hours	4.5 hours	8 hours	2.5 hours
Recoat	36 hours	21 hours	8 hours	5 hours
Pot Life	2.5 hours	1.5 hours	2 hours	1 hour
Recoatable Epoxy Primer	@ 35°F (1.6°C)	@ 35°F (1.6°C)	@ 77°F (25°C)	@ 77°F (25°C)
Touch	1 hour	1 hour	15 minutes	15 minutes
Recoat	6 hours	4 hours	2 hours	2 hours
Pot Life	9 hours	7 hours	8 hours	5 hours
Tile Clad HS	@ 55°F (13°C)	@ 55°F (13°C)	@ 77°F (25°C)	@ 77°F (25°C)
Touch	3 hours	1 hour	1 hour	1 hour
Recoat	6 hours	5 hours	2 hours	2 hours
Pot Life	4 hours	2 hours	4 hours	2 hours
Epolon II Multi-Mil	@ 50°F (10°C)	@ 50°F (10°C)	@ 77°F (25°C)	@ 77°F (25°C)
Touch	4 hours	4 hours	3 hours	3 hours
Recoat	24 hours	8 hours	18 hours	8 hours
Pot Life	4 hours	2 hours	4 hours	2 hours
TarGuard Coal Tar Epoxy	@ 50°F (10°C)	@ 50°F (10°C)	@ 77°F (25°C)	@ 77°F (25°C)
Touch	14 hours	3-1/2 hours	8-10 hours	3-1/2 hours
Recoat	48 hours	24 hours	18 hours	16 hours
Pot Life	2 hours	1 hour	2 hours	1 hour

DISCLAIMER

The information and recommendations set forth in this Product Data Sheet are based upon tests conducted by or on behalf of The Sherwin-Williams Company. Such information and recommendations set forth herein are subject to change and pertain to the product offered at the time of publication. Consult your Sherwin-Williams representative to obtain the most recent Product Data Information and Application Bulletin.

WARRANTY

The Sherwin-Williams Company warrants our products to be free of manufacturing defects in accord with applicable Sherwin-Williams quality control procedures. Liability for products proven defective, if any, is limited to replacement of the defective product or the refund of the purchase price paid for the defective product as determined by Sherwin-Williams. NO OTHER WARRANTY OR GUARANTEE OF ANY KIND IS MADE BY SHERWIN-WILLIAMS, EXPRESSED OR IMPLIED, STATUTORY, BY OPERATION OF LAW OR OTHERWISE, INCLUDING MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE.