



# Protective & Marine Coatings

## RESUFLOOR™ AQUA 3461 GLOSS TOPCOAT WATER-BASED EPOXY

PART A  
PART B

GP3461  
GP3461B01

SERIES  
HARDENER

Revised: March 17, 2021

### PRODUCT INFORMATION

#### PRODUCT DESCRIPTION

**RESUFLOOR AQUA 3461 Gloss Topcoat** is a unique, high solids water-based epoxy used as a grout and or topcoat for the Resufloor Aqua floor systems. This product can be applied in films up to 12 mils (300 microns) without impacting cure properties and offers better UV resistance than traditional epoxies.

#### ADVANTAGES

- Breathable
- Good chemical resistance
- Excellent UV stability
- Long working time
- Acceptable for use in USDA inspected facilities

#### TYPICAL USES

**RESUFLOOR AQUA 3461 Gloss Topcoat** is used as a grout and seal coat for the Resufloor Aqua flooring systems. May also be used on other slurry broadcast systems or as a clear grout coat.

#### LIMITATIONS

- Substrate must be structurally sound, dry and free of bond inhibiting contaminants
- During installation and initial cure cycle substrate and ambient air temperature must be at a minimum of 50°F (10°C) (for lower temperature installation contact your Sherwin-Williams representative).
- **Strictly adhere to published coverage rates. Never exceed application of more than 12 WFT mils (300 microns).**
- DO NOT apply direct to concrete
- DO NOT install in immersion environments
- DO NOT install in kitchens or hot grease environments
- Cure times will be extended in conditions of high humidity and poor ventilation due to low evaporation rate
- When high humidity (>75% relative humidity) is anticipated, provide additional air movement and/or dehumidification
- In uncontrolled climate environments, DO NOT INSTALL when rain is imminent or humidity is above 90%
- **This coating though resistant, is not a guarantee against tire staining. Vehicular tires from cars and trucks to tractors and boat trailers are varied and have the potential to leave a stain under certain conditions. Place rubber mats or carpet pieces under the tires to avoid the issue.**

#### SURFACE PREPARATION

Proper inspection and preparation of the substrate to receive resinous material is critical. Read and follow the "Instructions for Concrete Surface Preparation" (Form G-1) for complete details.

#### PRODUCT CHARACTERISTICS

<b>Color:</b>	Clear
<b>Mix Ratio:</b>	1:2 Reduction 10-20% with Potable Water
<b>Viscosity, mixed:</b>	600 cps
<b>Volume Solids:</b>	71% ± 2%, mixed
<b>Weight Solids:</b>	69% ± 2%, mixed
<b>VOC (EPA Method 24):</b>	Unreduced: <50 g/L ; 0.41 lb/gal mixed

#### Recommended Spreading Rate per coat:

	Minimum	Maximum
<b>Wet mils (microns):</b>	<b>5.0</b> (25)	<b>12.0</b> (300)
<b>~Coverage sq ft/gal (m<sup>2</sup>/L):</b>	<b>320</b> (8.1)	<b>133</b> (3.4)

#### Drying Schedule @ 6 mils (150 microns) wet:

	<b>@ 73°F (23°C)</b>
<b>To touch:</b>	6-8 hours
<b>To recoat:</b>	10-12 hours
<b>Light traffic:</b>	18-24 hours minimum
<i>If maximum recoat time is exceeded, abrade surface before recoating. Drying time is temperature, humidity, and film thickness dependent.</i>	
<b>Pot Life:</b>	gallon mass 60 minutes @ 73°F (23°C)

<b>Shelf Life:</b>	Part A: 36 months, unopened Part B: 36 months, unopened
	Store indoors at 50°F (10°C) to 90°F (32°C)
<b>Flash Point:</b>	>210°F (>99°C), ASTM D 93, mixed

#### PERFORMANCE CHARACTERISTICS

Test Name	Test Method	Results
<b>Abrasion Resistance</b>	ASTM D4060, CS17 wheel, 1000 cycles	48 mg loss



# Protective & Marine Coatings

## RESUFLOOR™ AQUA 3461 GLOSS TOPCOAT WATER-BASED EPOXY

PART A  
PART B

GP3461  
GP3461B01

SERIES  
HARDENER

Revised: March 17, 2021

### PRODUCT INFORMATION

#### APPLICATION

##### APPLICATION INSTRUCTIONS:

1. Premix 3461 Part A and Part B using a low speed drill and Jiffy blade. Mix until uniform, exercising caution to not entrain air into the product.
2. Add 1 part 3461A (resin) to 2 parts 3461B (hardener) by volume. Mix with low speed drill and Jiffy blade until uniform (typically 90 seconds), material will thicken as you mix. To insure proper cure and performance, strictly follow the mix ratio. Material may be reduced by 10% potable water as a grout or topcoat. **DO NOT REDUCE PRODUCT UNTIL BOTH COMPONENTS HAVE BEEN MIXED TOGETHER FOR 90 SECONDS.**
3. Apply 3461 using a flat or notched squeegee coat and backroll with a high quality 3/16" nap roller. Apply at a spread rate 266 sq. ft. per gallon to yield 6 WFT mils (150 microns), evenly with no puddles, making sure of uniform coverage. Cross hatch backrolling is recommended for uniformity.
4. Allow to cure 18 hours minimum before opening to traffic. Cure times will vary dependent upon environmental conditions.

#### ORDERING INFORMATION

Packaging:	
Part A:	1 gallon (3.78L) and 5 gallon (18.9L) containers
Part B:	1 gallon (3.78L) and 5 gallon (18.9L) containers
Weight:	9.9 ± 0.2 lb/gal; 1.19 Kg/L

#### CHEMICAL RESISTANCE

For comprehensive chemical resistance information, consult the Chemical Resistant Guide and contact your Sherwin-Williams representative.

#### TINTING

Do not tint.

#### CLEANUP

Clean up mixing and application equipment immediately after use with soap and water.

#### SAFETY

Refer to the SDS sheet before use.

Published technical data and instructions are subject to change without notice. Contact your Sherwin-Williams representative for additional technical data and instructions.

#### MAINTENANCE

Occasional inspection of the installed material and spot repair can prolong system life. For specific information, contact your Sherwin-Williams representative.

#### DISCLAIMER

The information and recommendations set forth in this Product Data Sheet are based upon tests conducted by or on behalf of The Sherwin-Williams Company. Such information and recommendations set forth herein are subject to change and pertain to the product offered at the time of publication. Consult your Sherwin-Williams representative to obtain the most recent Product Data Information and Application Bulletin.

#### WARRANTY

The Sherwin-Williams Company warrants our products to be free of manufacturing defects in accord with applicable Sherwin-Williams quality control procedures. Liability for products proven defective, if any, is limited to replacement of the defective product or the refund of the purchase price paid for the defective product as determined by Sherwin-Williams. NO OTHER WARRANTY OR GUARANTEE OF ANY KIND IS MADE BY SHERWIN-WILLIAMS, EXPRESSED OR IMPLIED, STATUTORY, BY OPERATION OF LAW OR OTHERWISE, INCLUDING MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE.