



**SHERWIN  
WILLIAMS.**



107.10

# PREPRITE® BLOCK FILLER

## INTERIOR/EXTERIOR LATEX B25W25

As of 09/22/08, Complies with:	
OTC	Yes LEED® Clv2.0 Yes
SCAQMD	Yes LEED® NCv2.2Yes
CARB	Yes LEED® CSv2.0Yes
MPI Spec #	4 LEED® H Yes
NAHB	Yes

### CHARACTERISTICS

- Allows topcoat on **concrete block** to be smooth and uniform
- Effective on above-grade, unpainted masonry surfaces

**Use on unpainted:**

- Masonry
- Concrete
- Cement
- Flat Surfaced Concrete Block

**Color:** Off White

**Coverage:** 75-125 sq ft/gal  
@ 16 mils wet; 8 mils dry

**Drying Time, @ 77°F, 50% RH:**  
temperature and humidity dependent

Touch: 2 hours

Recoat with latex based: 18 hours

Recoat with solvent based: 48 hours

**Flash Point:** N/A

**Finish:** 0-5 units @ 85°

**Vehicle Type:** Vinyl Acrylic

**B25W00025**

**VOC (less exempt solvents):**  
45 g/L; 0.37 lb/gal

**Volume Solids:** 48 ± 2%

**Weight Solids:** 68 ± 2%

**Weight per Gallon:** 13.5 lb

**PrepRite Block Filler** meets or exceeds the criteria set forth by the U. S. Green Building Council LEED-CI, Version 2.0 and LEED-NC Version 2.2. All results have been verified by our ISO 9001 Laboratory.

### APPLICATION

**Masonry, Concrete, Cement, Block**

1 ct. PrepRite Block Filler  
2 cts. Appropriate topcoat

**Recommended Architectural Topcoats**

A-100 Exterior Latex  
Loxon Masonry Coating  
SuperPaint Exterior  
Duration Exterior

Classic 99 Interior

Duration Home

ProClassic Interior

ProMar Interior

SuperPaint Interior

**Recommended Industrial Topcoats**

DTM Acrylic Enamel  
Industrial Enamel  
Metalatex Semi-Gloss  
Water Based Catalyzed Epoxy

Apply at temperatures above 50°F.

No reduction necessary.

**Brush** - Use a nylon/polyester brush.

**Roller** - Use a 3/8" to 1-1/2" nap cover.

**Spray - Airless**

Pressure ..... 2300 psi

Tip ..... .028"

Reduction ... as needed up to 1 pt/gal

Remove all in-line and gun filters

Spray application may be backrolled to work material into the surface. All application methods may be squeegeed to provide a very smooth surface.

### SURFACE PREPARATION

**WARNING!** Removal of old paint by sanding, scraping or other means may generate dust or fumes that contain lead. Exposure to lead dust or fumes may cause brain damage or other adverse health effects, especially in children or pregnant women. Controlling exposure to lead or other hazardous substances requires the use of proper protective equipment, such as a properly fitted respirator (NIOSH approved) and proper containment and cleanup. For more information, call the National Lead Information Center at 1-800-424-LEAD (in US) or contact your local health authority.

**Masonry, Concrete, Cement, Block**

Remove all surface contamination, form release agents, moisture curing membranes, etc. by washing with an appropriate cleaner, rinse and allow to dry. Pressure wash the surface if needed. Remove existing peeled or checked paint to a sound surface. Concrete and mortar must be cured, generally 30 days, at 75°F before painting.

Complete removal of sealers, release compounds, and to provide a profile, tilt-up and poured-in-place concrete could require sandblasting or cleaning with commercial detergents. **Do not apply to smooth, slick surfaces, peeling may result.**

Masonry surfaces must be dry before priming. Moisture content must be 15% or lower, and the pH between 6 and 9. If the pH is greater than 9, use Loxon Block Surfacer in place of PrepRite Block Filler.

For repairing **exterior** cracks, bugholes, air pockets, and other voids use ConSeal™ Patches and Sealants.

107.10

PREPRITE®

BLOCK FILLER

INTERIOR/EXTERIOR LATEX

B25W25



**SHERWIN  
WILLIAMS.**

### SURFACE PREPARATION

#### **Mildew**

Remove before painting by washing with a solution of 1 part liquid bleach and 3 parts water. Apply the solution and scrub the mildewed area. Allow the solution to remain on the surface for 10 minutes. Rinse thoroughly with water and allow the surface to dry before painting. Wear protective eyewear, waterproof gloves, and protective clothing. Quickly wash off any of the mixture that comes in contact with your skin. Do not add detergents or ammonia to the bleach/water solution.

### CLEANUP INFORMATION

Clean spills and spatters immediately with soap and warm water. Clean hands and tools immediately after use with soap and warm water. After cleaning, flush spray equipment with mineral spirits to prevent rusting of the equipment. Follow manufacturer's safety recommendations when using mineral spirits.

### CAUTIONS

Do not apply at temperatures below 50°F. Protect from freezing.

#### LABEL CAUTIONS

CAUTION contains CRYSTALLINE SILICA. Use only with adequate ventilation. To avoid overexposure, open windows and doors or use other means to ensure fresh air entry during application and drying. If you experience eye watering, headaches, or dizziness, increase fresh air, or wear respiratory protection (NIOSH approved) or leave the area. Adequate ventilation required when sanding or abrading the dried film. If adequate ventilation cannot be provided wear an approved particulate respirator (NIOSH approved). Follow respirator manufacturer's directions for respirator use. Avoid contact with eyes and skin. Wash hands after using. Keep container closed when not in use. Do not transfer contents to other containers for storage. FIRST AID: In case of eye contact, flush thoroughly with large amounts of water. Get medical attention if irritation persists. If swallowed, call Poison Control Center, hospital emergency room, or physician immediately. DELAYED EFFECTS FROM LONG TERM OVEREXPOSURE. Abrading or sanding of the dry film may release crystalline silica which has been shown to cause lung damage and cancer under long term exposure. WARNING: This product contains chemicals known to the State of California to cause cancer and birth defects or other reproductive harm. DO NOT TAKE INTERNALLY. KEEP OUT OF THE REACH OF CHILDREN.

HOTW 09/22/2008 B25W00025 25 00

The information and recommendations set forth in this Product Data Sheet are based upon tests conducted by or on behalf of The Sherwin-Williams Company. Such information and recommendations set forth herein are subject to change and pertain to the product offered at the time of publication. Consult your Sherwin-Williams representative to obtain the most recent Product Data Sheet.