



**SHERWIN
WILLIAMS.**

INTERIOR/EXTERIOR ALKYD ALL SURFACE ENAMEL A11 SERIES

<u>CHARACTERISTICS</u>	<u>SPECIFICATIONS</u>	<u>SURFACE PREPARATION</u>									
<p>All Surface Enamel is designed for use on interior and exterior wood, metal, dry-wall, and other surfaces. This high quality coating provides excellent resistance to weather and sunlight. The exceptional durability allows it to be used on doors, trim, windows, and other hard wear areas, including exterior wood floors.</p> <p style="text-align: center;">Topcoats</p> <p>Color: Many Colors Coverage: 350 - 400 sq ft/gal @ 4.0 mils wet; 1.6 mils dry Drying Time, @ 77°F, 50% RH: temperature and humidity dependent Touch: 1-2 hours Recoat: 8 hours Flash Point: 101°F, PMCC Finish: 70 units @ 60° Satin Black 10-20 units @ 85° Satin Ultradeep 30-40 units @ 85° Tinting with Blend-A-Color:</p> <table border="0"> <thead> <tr> <th>Base</th> <th>oz/gal</th> <th>Strength</th> </tr> </thead> <tbody> <tr> <td>Tinting White</td> <td>0-3</td> <td>75%</td> </tr> <tr> <td>Ultradeep Base</td> <td>3-9</td> <td>75%</td> </tr> </tbody> </table> <p>Vehicle Type: Alkyd</p> <p style="text-align: center;">A11W201</p> <p>VOC (less exempt solvents): 440 g/L; 3.67 lb/gal</p> <p>Volume Solids: 43 ± 2% Weight Solids: 58 ± 2% Weight per Gallon: 8.8 lb Not OTC Compliant</p>	Base	oz/gal	Strength	Tinting White	0-3	75%	Ultradeep Base	3-9	75%	<p>Aluminum 1 ct. Galvite HS 2 cts. All Surface Enamel</p> <p>Drywall, interior 1 ct. PrepRite Classic Primer 2 cts. All Surface Enamel</p> <p>Galvanized Steel 1 ct. Galvite HS 2 cts. All Surface Enamel</p> <p>Masonry, Concrete, Cement, Block 1 ct. PrepRite Block Filler (optional) or PrepRite Masonry Primer, interior or Loxon Masonry Primer, exterior 2 cts. All Surface Enamel</p> <p>Plaster 1 ct. PrepRite Masonry Primer 2 cts. All Surface Enamel</p> <p>Steel 1 ct. All Surface Enamel Primer 2 cts. All Surface Enamel</p> <p>Wood, interior 1 ct. PrepRite Classic Primer 2 cts. All Surface Enamel</p> <p>Wood, exterior 1 ct. A-100 Exterior Oil Primer 2 cts. All Surface Enamel</p> <p>Wood, exterior floors 2 cts. All Surface Enamel</p>	<p>WARNING! Removal of old paint by sanding, scraping or other means may generate dust or fumes that contain lead. Exposure to lead dust or fumes may cause brain damage or other adverse health effects, especially in children or pregnant women. Controlling exposure to lead or other hazardous substances requires the use of proper protective equipment, such as a properly fitted respirator (NIOSH approved) and proper containment and cleanup. For more information, call the National Lead Information Center at 1-800-424-LEAD (in US) or contact your local health authority.</p> <p>Remove all surface contamination by washing with ProClean Professional® Prep Wash Concentrated Cleaner or other appropriate cleaner, rinse thoroughly and allow to dry. Existing peeled or checked paint should be scraped and sanded to a sound surface. Glossy surfaces should be sanded dull. Stains from water, smoke, ink, pencil, grease, etc. should be sealed with PrepRite® ProBlock® Primer Sealer.</p> <p>Aluminum and Galvanized Steel Wash with ProClean Professional® Prep Wash Concentrated Cleaner to remove any oil, grease, or other surface contamination. Remove all corrosion with sandpaper, steel wool, or other abrading method.</p> <p>Drywall Fill cracks and holes with patching paste/spackle and sand smooth. Joint compounds must be cured and sanded smooth. Remove all sanding dust.</p>
Base	oz/gal	Strength									
Tinting White	0-3	75%									
Ultradeep Base	3-9	75%									
<p style="text-align: center;">Primer</p> <p>Color: White Coverage: 200 - 275 sq ft/gal @ 8.0 mils wet; 4.0 mils dry Drying Time, @ 77°F, 50% RH: temperature and humidity dependent Touch: 30 minutes Topcoat: 1 hour Flash Point: 87°F, PMCC Vehicle Type: Alkyd</p> <p style="text-align: center;">A11W210</p> <p>VOC (less exempt solvents): 498 g/L; 4.16 lb/gal</p> <p>Volume Solids: 42 ± 2% Weight Solids: 63 ± 2% Weight per Gallon: 11.3 lb Not OTC Compliant</p>											

107.04

INTERIOR/EXTERIOR ALKYD ALL SURFACE ENAMEL A11 SERIES



**SHERWIN
WILLIAMS.**

SURFACE PREPARATION

Masonry, Concrete, Cement, Block

All new surfaces must be cured according to the supplier's recommendations—usually about 30 days. Remove all form release and curing agents. Rough surfaces can be filled to provide a smooth surface. If painting cannot wait 30 days, allow the surface to cure 7 days and prime the surface with PrepRite Masonry Primer (interior) or Loxon Masonry Primer (exterior).

Plaster

Bare plaster must be cured and hard. Textured, soft, porous, or powdery plaster should be treated with a solution of 1 pint household vinegar to 1 gallon of water. Repeat until the surface is hard, rinse with clear water and allow to dry.

Steel

Rust and mill scale must be removed using sandpaper, steel wool, or other abrading method. Bare steel must be primed the same day as cleaned.

Wood

Sand any exposed wood to a fresh surface. Patch all holes and imperfections with a wood filler or putty and sand smooth.

Mildew

Remove before painting by washing with ProClean Professional Mildew Eliminator or a solution of 1 part liquid bleach and 3 parts water. Apply the solution and scrub the mildewed area. Allow the solution to remain on the surface for 10 minutes. Rinse thoroughly with water and allow the surface to dry before painting. Wear protective eyewear, waterproof gloves, and protective clothing. Quickly wash off any of the mixture that comes in contact with your skin. Do not add detergents or ammonia to the bleach/water solution.

Caulking

Exterior gaps between windows, doors, trim, and other through-wall openings; and interior gaps between walls, ceilings, crown moldings, and other trim can be filled with the appropriate Pro Select® Caulk after priming the surface.

SURFACE PREPARATION

Caulking

Exterior gaps between windows, doors, trim, and other through-wall openings; and interior gaps between walls, ceilings, crown moldings, and other trim can be filled with the appropriate Pro Select® Caulk after priming the surface.

APPLICATION

Apply at temperatures above 50°F.

No reduction necessary

Brush

Use a natural bristle brush

Roller

Use a 1/4" - 3/8" nap lambswool cover.

Spray—Airless

Pressure 1800 psi

Tip017" - .019"

Reduction
if needed, up to 5% (6 oz) per gallon

CLEANUP INFORMATION

Clean spills, spatters, hands and tools immediately after use with mineral spirits. Follow manufacturer's safety recommendations when using mineral spirits.

CAUTIONS

Not for use on roofs.

Do not use colorants formulated for interior use only on exterior surfaces.

LABEL CAUTIONS

CAUTION contains CRYSTALLINE SILICA. Use only with adequate ventilation. To avoid overexposure, open windows and doors or use other means to ensure fresh air entry during application and drying. If you experience eye watering, headaches, or dizziness, increase fresh air, or wear respiratory protection (NIOSH approved) or leave the area. Adequate ventilation required when sanding or abrading the dried film. If adequate ventilation cannot be provided wear an approved particulate respirator (NIOSH approved). Follow respirator manufacturer's directions for respirator use. Avoid contact with eyes and skin. Wash hands after using. Keep container closed when not in use. Do not transfer contents to other containers for storage. FIRST AID: In case of eye contact, flush thoroughly with large amounts of water. Get medical attention if irritation persists. If swallowed, call Poison Control Center, hospital emergency room, or physician immediately. DELAYED EFFECTS FROM LONG TERM OVEREXPOSURE. Abrading or sanding of the dry film may release crystalline silica which has been shown to cause lung damage and cancer under long term exposure. WARNING: This product contains chemicals known to the State of California to cause cancer. DO NOT TAKE INTERNALLY. KEEP OUT OF THE REACH OF CHILDREN.
HOTW 12/15/2004 A11W00201 33 00

The information and recommendations set forth in this Product Data Sheet are based upon tests conducted by or on behalf of The Sherwin-Williams Company. Such information and recommendations set forth herein are subject to change and pertain to the product offered at the time of publication. Consult your Sherwin-Williams representative to obtain the most recent Product Data Sheet.