



**SHERWIN
WILLIAMS.**

EXTERIOR ACCENTS

LATEX HIGH GLOSS Y32 SERIES

CHARACTERISTICS

Exterior Accents Latex High Gloss provides vivid, bright, and deep colors for most exterior surfaces.

Recommended uses:

Homes
Garages
Trimwork
Windows
Shutters
and other architectural surfaces

Recommended substrates:

Masonry, Concrete, Block, Stucco
Aluminum, Steel, and Galvanized
Wood, Composition Board, Plywood
Vinyl Siding

Color: Many exterior colors

Coverage: 350 - 400 sq ft/gal
@ 4 mils wet; 1.5 mils dry

Drying Time @ 77°F and 50% RH:
temperature and humidity dependent

Touch: 1 hour

Recoat: 24 hours

Flash Point: N/A

Finish: 70+ units @ 60°

Tinting with Blend-A-Color:

Base	oz/gal	Strength
All Bases	4-12	100%

Vehicle Type: Acrylic

Y32T54

VOC (less exempt solvents):

110 g/L; 0.91 lb/gal

Volume Solids: 41 ± 2%

Weight Solids: 44 ± 2%

Weight per Gallon: 8.7 lb

OTC Compliant

Mildew Resistant

This coating contains agents which inhibit the growth of mildew on the surface of this coating film.

SPECIFICATIONS

Two topcoats are recommended for all surfaces.

Aluminum & Aluminum Siding

no primer necessary

Block

Loxon Block Surfacer

Exterior Drywall

Exterior Latex Wood Primer

Galvanized Steel

no primer necessary

Masonry/Cement/Stucco

Loxon Concrete & Masonry Primer

Plywood

Exterior Latex Wood Primer

Steel

All Surface Enamel Latex Primer

Vinyl Siding

no primer necessary

Wood, Composition Board

Exterior Oil-Based Wood Primer
or Exterior Latex Wood Primer

SURFACE PREPARATION

WARNING! Removal of old paint by sanding, scraping or other means may generate dust or fumes that contain lead. Exposure to lead dust or fumes may cause brain damage or other adverse health effects, especially in children or pregnant women. Controlling exposure to lead or other hazardous substances requires the use of proper protective equipment, such as a properly fitted respirator (NIOSH approved) and proper containment and cleanup. For more information, call the National Lead Information Center at 1-800-424-LEAD (in US) or contact your local health authority.

Remove all surface contamination by washing with an appropriate cleaner, rinse thoroughly and allow to dry. Scrape and sand peeled or checked paint to a sound surface. Sand glossy surfaces dull. Seal stains from water, smoke, ink, pencil, grease, etc. with the appropriate primer/sealer.

Aluminum and Galvanized Steel

Wash to remove any oil, grease, or other surface contamination. All corrosion must be removed with sandpaper, steel wool, or other abrading method.

Cement Composition Siding/Panels

Remove all dirt, dust, grease, oil, loose particles, laitance, foreign material, and peeling or defective coatings. Allow the surface to dry thoroughly. If the surface is new, test it for pH, if the pH is higher than 8, prime with Loxon Concrete & Masonry Primer.

102.53

EXTERIOR ACCENTS

LATEX HIGH GLOSS

Y32 SERIES



**SHERWIN
WILLIAMS.**

SURFACE PREPARATION

Masonry, Concrete, Cement, Block

All new surfaces must be cured according to the supplier's recommendations—usually about 30 days. Remove all form release and curing agents. Rough surfaces can be filled to provide a smooth surface. If painting cannot wait 30 days, allow the surface to cure 7 days and prime the surface with Loxon Acrylic Primer. Cracks, voids, and other holes should be repaired with an elastomeric patch or sealant.

Steel

Rust and mill scale must be removed using sandpaper, steel wool, or other abrading method. Bare steel must be primed the same day as cleaned.

Stucco

Remove any loose stucco, efflorescence, or laitance. Allow new stucco to cure at least 30 days before painting. If painting cannot wait 30 days, allow the surface to dry 5-7 days and prime with Loxon Masonry Primer. Repair cracks, voids, and other holes with an elastomeric patch or sealant.

Vinyl

Clean the surface thoroughly by scrubbing with warm, soapy water. Rinse thoroughly.

Wood, Plywood, Composition Board

Sand any exposed wood to a fresh surface. Patch all holes and imperfections with a wood filler or putty and sand smooth. All patched areas must be primed.

Caulking

Gaps between windows, doors, trim, and other through-wall openings can be filled with the appropriate caulk after priming the surface.

SURFACE PREPARATION

Mildew

Remove before painting by washing with a solution of 1 part liquid bleach and 3 parts water. Apply the solution and scrub the mildewed area. Allow the solution to remain on the surface for 10 minutes. Rinse thoroughly with water and allow the surface to dry before painting. Wear protective eyewear, waterproof gloves, and protective clothing. Quickly wash off any of the mixture that comes in contact with your skin. Do not add detergents or ammonia to the bleach/water solution.

APPLICATION

Apply at temperatures above 50°F.

No reduction necessary.

Brush

Use a nylon/polyester brush

Roller

Use a 3/8" - 3/4" nap synthetic cover

Spray—Airless

Pressure 2000 psi

Tip015"-.019"

CLEANUP INFORMATION

Clean spills, spatters, hands and tools immediately after use with soap and warm water. After cleaning, flush spray equipment with mineral spirits to prevent rusting of the equipment.

Follow manufacturer's safety recommendations when using mineral spirits.

CAUTIONS

For exterior use only.

Protect from freezing.

Non-photochemically reactive.

LABEL CAUTIONS

Use only with adequate ventilation. To avoid overexposure, open windows and doors or use other means to ensure fresh air entry during application and drying. If you experience eye watering, headaches, or dizziness, increase fresh air, or wear respiratory protection (NIOSH approved) or leave the area. Avoid contact with eyes and skin. Wash hands after using. Keep container closed when not in use. Do not transfer contents to other containers for storage. **FIRST AID:** In case of eye contact, flush thoroughly with large amounts of water. Get medical attention if irritation persists. If swallowed, call Poison Control Center, hospital emergency room, or physician immediately. **WARNING:** This product contains chemicals known to the State of California to cause cancer and birth defects or other reproductive harm. **DO NOT TAKE INTERNALLY. KEEP OUT OF THE REACH OF CHILDREN.**

HOTW 10/27/2004 Y32T00054 04 00

The information and recommendations set forth in this Product Data Sheet are based upon tests conducted by or on behalf of The Sherwin-Williams Company. Such information and recommendations set forth herein are subject to change and pertain to the product offered at the time of publication. Consult your Sherwin-Williams representative to obtain the most recent Product Data Sheet.