



**SHERWIN  
WILLIAMS.**

# ProMar 200 XP®

## INTERIOR LATEX EG-SHEL

### B20-3200 SERIES

As of 09/22/08, Complies with:		
OTC	Yes	LEED® Clv2.0 Yes
SCAQMD	No	LEED® NCv2.2Yes
CARB	Yes	LEED® CSv2.0Yes
MPI Spec #	No	LEED® H Yes
NAHB	Yes	

### CHARACTERISTICS

**ProMar 200 XP Interior Latex Eg-Shel** is a high quality product designed for the professional for interior use on unprimed wallboard.

**ProMar 200 XP Interior Latex Eg-Shel** delivers the same performance in one coat that two coats of conventional Eg-Shels deliver.

**ProMar 200 XP Interior Latex Eg-Shel**, when airless sprayed and backrolled, delivers a subtle, uniform stipple that covers surface irregularities and minor drywall imperfections.

**Excellent for use on:**

- Warehouses
- Chain Stores
- Shopping Centers
- Manufacturing facilities
- Airports
- Commercial jobs

- **Superior Scrubbability over 1200 scrubs**
- **Excellent Burnish Resistance 0.1 unit change in gloss**

### SYSTEMS

**Primers**

**Drywall (optional)**

Self-sealing over bare drywall  
ProMar200 Int. Latex Primer

**Masonry**

Loxon Block Surfacers  
Loxon Concrete & Masonry Primer

### SPECIFICATIONS

**Color:** most colors

**Coverage:**

**For proper performance, this product MUST be applied from:**

160 sq ft/gal @ 10 mils wet; 4.6 mils dry to:

114 sq ft/gal @ 14 mils wet; 6.4 mils dry

**Drying Time, @ 77°F, 50% RH:** temperature and humidity dependent

**Touch:** 1 hour

**Recoat:** 4 hours

**Finish:** 15-20 units @ 85°  
5+ units @ 60°

**Flash Point:** N/A

**Tinting with Blend-A-Color:**

Base oz/gal Strength

Extra White 0-5 100%

Deep Base 4-12 100%

**Vehicle Type:** 100% Acrylic

**B20W3251**

**VOC (less exempt solvents):** 92 g/L; 0.76 lb/gal

**Volume Solids:** 47 ± 2%

**Weight Solids:** 61 ± 2%

**Weight per Gallon:** 11.3 lb

### APPLICATION

The ProMar 200 XP Interior Latex Eg-Shel is designed to deliver the best performance when applied by airless spray and back rolled 3 - 5 minutes after spraying.

**For proper performance, this product MUST be applied from 10.0 mils wet to 14.0 mils wet.**

Apply at temperatures above 50°F. No reduction needed.

**Spray—Airless**

Pressure ..... 2000 psi  
Tip ..... .519 or larger  
Flash off ..... 3 - 5 minutes  
Backroll once with a ½" polyester cover using minimal pressure to produce a uniform surface with a subtle stippling effect.

**Brush (small areas only)**

Use a nylon/polyester brush.

**Roller**

May be applied by roller, using a ½" or ¾" polyester cover, to achieve a film build of 10 to 14 mils wet. Backroll tightly into the corners to achieve the best finish appearance

**Painting Systems**

Typical Eg-Shel	ProMar 200 XP
1 ct primer	1 coat primer
2 topcoats	1 topcoat
1 ct primer	(none needed)
2 topcoats	2 topcoats
1 ct primer	(none needed)
1 topcoat	1 topcoat

101.25

# PROMAR 200 XP<sup>®</sup>

## INTERIOR LATEX EG-SHEL

### B20-3200 SERIES



**SHERWIN  
WILLIAMS.**

#### SURFACE PREPARATION

**WARNING!** Removal of old paint by sanding, scraping or other means may generate dust or fumes that contain lead. Exposure to lead dust or fumes may cause brain damage or other adverse health effects, especially in children or pregnant women. Controlling exposure to lead or other hazardous substances requires the use of proper protective equipment, such as a properly fitted respirator (NIOSH approved) and proper containment and cleanup. For more information, call the National Lead Information Center at 1-800-424-LEAD (in US) or contact your local health authority.

Remove all surface contamination by washing with an appropriate cleaner, rinse thoroughly and allow to dry. Existing peeled or checked paint should be scraped and sanded to a sound surface. Glossy surfaces should be sanded dull. Stains from water, smoke, ink, pencil, grease, etc. should be sealed with the appropriate primer/sealer.

#### **Drywall**

Fill cracks and holes with patching paste/spackle and sand smooth. Joint compounds must be cured and sanded smooth. Remove all sanding dust.

#### **Masonry, Concrete, Cement, Block**

All new surfaces must be cured according to the supplier's recommendations—usually about 30 days. Remove all form release and curing agents. Rough surfaces can be filled to provide a smooth surface. If painting cannot wait 30 days, allow the surface to cure 7 days and prime the surface with Loxon Concrete & Masonry Primer.

#### SURFACE PREPARATION

#### **Mildew**

Remove before painting by washing with a solution of 1 part liquid bleach and 3 parts water. Apply the solution and scrub the mildewed area. Allow the solution to remain on the surface for 10 minutes. Rinse thoroughly with water and allow the surface to dry before painting. Wear protective eyewear, waterproof gloves, and protective clothing. Quickly wash off any of the mixture that comes in contact with your skin. Do not add detergents or ammonia to the bleach/water solution.

#### **Caulking**

Gaps between walls, ceilings, crown moldings, and other interior trim can be filled with the appropriate caulk after priming the surface.

#### CLEANUP INFORMATION

Clean spills, spatters, hands and tools immediately after use with soap and warm water. After cleaning, flush spray equipment with mineral spirits to prevent rusting of the equipment. Follow manufacturer's safety recommendations when using mineral spirits.

#### CAUTIONS

For interior use only.  
Protect from freezing.  
Non-photochemically reactive.

#### **Label Caution**

CAUTION contains CRYSTALLINE SILICA. Use only with adequate ventilation. To avoid overexposure, open windows and doors or use other means to ensure fresh air entry during application and drying. If you experience eye watering, headaches, or dizziness, increase fresh air, or wear respiratory protection (NIOSH approved) or leave the area. Adequate ventilation required when sanding or abrading the dried film. If adequate ventilation cannot be provided wear an approved particulate respirator (NIOSH approved). Follow respirator manufacturer's directions for respirator use. Avoid contact with eyes and skin. Wash hands after using. Keep container closed when not in use. Do not transfer contents to other containers for storage. FIRST AID: In case of eye contact, flush thoroughly with large amounts of water. Get medical attention if irritation persists. If swallowed, call Poison Control Center, hospital emergency room, or physician immediately. DELAYED EFFECTS FROM LONG TERM OVEREXPOSURE. Abrading or sanding of the dry film may release crystalline silica which has been shown to cause lung damage and cancer under long term exposure. WARNING: This product contains chemicals known to the State of California to cause cancer and birth defects or other reproductive harm. DO NOT TAKE INTERNALLY. KEEP OUT OF THE REACH OF CHILDREN.

HOTW 09/22/2008 B20W03251 06 00

The information and recommendations set forth in this Product Data Sheet are based upon tests conducted by or on behalf of The Sherwin-Williams Company. Such information and recommendations set forth herein are subject to change and pertain to the product offered at the time of publication. Consult your Sherwin-Williams representative to obtain the most recent Product Data Sheet.