



**SHERWIN
WILLIAMS.**

| | | | |
|--------------------------------|-----|--------------|-----|
| As of 11/25/08, Complies with: | | | |
| OTC | Yes | LEED® Clv2.0 | Yes |
| SCAQMD | No | LEED® NCv2.2 | Yes |
| CARB | Yes | LEED® CSv2.0 | No |
| MPI Spec # | 47 | LEED® H | No |
| NAHB | Yes | | |

PROCLASSIC XP®

INTERIOR ALKYD SEMI-GLOSS

B34 SERIES

| <u>CHARACTERISTICS</u> | <u>SPECIFICATIONS</u> | <u>SURFACE PREPARATION</u> |
|---|--|--|
| <ul style="list-style-type: none"> • Superior flow and leveling characteristics result in a smooth and durable finish. • A heavier bodied formulation, that delivers outstanding hide and coverage. • Superior product application & brushability expected by professionals when working with traditional alkyd products <p>Color: White and select pastel colors Coverage: 350 - 400 sq ft/gal @ 4.0 mils wet; 3.7 mils dry Drying Time, @ 77°F, 50% RH: Drying and recoat times are temperature, humidity, and film thickness dependent. Touch: 3-6 hours Recoat: 24 hours Finish: 24 hours 80-90 units @ 60° 30 days 30-40 units @ 60° Flash Point: 149°F, PMCC Tinting with Blend-A-Color: Base oz/gal Strength Extra White 0-5 125% Vehicle Type: Alkyd B34W551 VOC (less exempt solvents): 144 g/L; 1.20 lb/gal Volume Solids: 90 ± 2% Weight Solids: 83 ± 2% Weight per Gallon: 12.2 lb</p> | <p>Block 1 ct. Loxon Block Surfacer 1-2 cts. ProClassic XP Int. Alkyd Semi-Gloss</p> <p>Drywall 1 ct. PrepRite Classic Latex Primer 1-2 cts. ProClassic XP Int. Alkyd Semi-Gloss</p> <p>Plaster 1 ct. PrepRite Classic Latex Primer or PrepRite Wall and Wood Primer 1-2 cts. ProClassic XP Int. Alkyd Semi-Gloss</p> <p>Masonry 1 ct. PrepRite Masonry Primer 1-2 cts. ProClassic XP Int. Alkyd Semi-Gloss</p> <p>Steel 1 ct. ProCryl Primer 1-2 cts. ProClassic XP Int. Alkyd Semi-Gloss</p> <p>Wood 1 ct. PrepRite Classic Latex Primer or PrepRite Wall and Wood Primer 1-2 cts. ProClassic XP Int. Alkyd Semi-Gloss</p> | <p>WARNING! Removal of old paint by sanding, scraping or other means may generate dust or fumes that contain lead. Exposure to lead dust or fumes may cause brain damage or other adverse health effects, especially in children or pregnant women. Controlling exposure to lead or other hazardous substances requires the use of proper protective equipment, such as a properly fitted respirator (NIOSH approved) and proper containment and cleanup. For more information, call the National Lead Information Center at 1-800-424-LEAD (in US) or contact your local health authority.</p> <p>Remove all surface contamination by washing with an appropriate cleaner, rinse thoroughly and allow to dry. Existing peeled or checked paint should be scraped and sanded to a sound surface. Glossy surfaces should be sanded dull. Stains from water, smoke, ink, pencil, grease, etc. should be sealed with the appropriate primer/sealer.</p> <p>Drywall Fill cracks and holes with patching paste/spackle and sand smooth. Joint compounds must be cured and sanded smooth. Remove all sanding dust.</p> <p>Masonry, Concrete, Cement, Block All new surfaces must be cured according to the supplier's recommendations—usually about 30 days. Remove all form release and curing agents. Rough surfaces can be filled to provide a smooth surface. If painting cannot wait 30 days, allow the surface to cure 7 days and prime the surface with PrepRite Masonry Primer.</p> |

103.34

PROCLASSIC XP[®]

INTERIOR ALKYD SEMI-GLOSS

B34 SERIES



**SHERWIN
WILLIAMS.**

SURFACE PREPARATION

Plaster

Bare plaster must be cured and hard. Textured, soft, porous, or powdery plaster should be treated with a solution of 1 pint household vinegar to 1 gallon of water. Repeat until the surface is hard, rinse with clear water and allow to dry.

Steel

Rust and mill scale must be removed using sandpaper, steel wool, or other abrading method. Bare steel must be primed the same day as cleaned.

Wood

Sand any exposed wood to a fresh surface. Patch all holes and imperfections with a wood filler or putty and sand smooth.

Mildew

Remove before painting by washing with a solution of 1 part liquid bleach and 3 parts water. Apply the solution and scrub the mildewed area. Allow the solution to remain on the surface for 10 minutes. Rinse thoroughly with water and allow the surface to dry before painting. Wear protective eyewear, waterproof gloves, and protective clothing. Quickly wash off any of the mixture that comes in contact with your skin. Do not add detergents or ammonia to the bleach/water solution.

Caulking

Gaps between walls, ceilings, crown moldings, and other interior trim can be filled with the appropriate caulk after priming the surface.

APPLICATION

Apply at temperatures above 50°F.

No reduction needed.

Brush

Use a natural bristle brush.

Roller

Use a 1/4" - 3/4" nap lambswool cover.

Spray-Airless

Pressure 2500 - 3000 psi

Tip013"-.019"

CLEANUP INFORMATION

Clean spills, spatters, hands and tools immediately with mineral spirits. Follow manufacturer's safety recommendations when using mineral spirits.

CAUTIONS

For interior use only.

Non-photochemically reactive.

LABEL CAUTIONS

CAUTION contains CRYSTALLINE SILICA, 1-Methyl-2-Pyrrolidinone. CONTAINS MATERIAL THAT MAY CAUSE ADVERSE REPRODUCTIVE EFFECTS AND MAY ADVERSELY AFFECT THE DEVELOPING FETUS BASED ON ANIMAL DATA. Contents are COMBUSTIBLE. Keep away from heat and open flame. Use only with adequate ventilation. To avoid overexposure, open windows and doors or use other means to ensure fresh air entry during application and drying. If you experience eye watering, headaches, or dizziness, increase fresh air, or wear respiratory protection (NIOSH approved) or leave the area. Adequate ventilation required when sanding or abrading the dried film. If adequate ventilation cannot be provided wear an approved particulate respirator (NIOSH approved). Follow respirator manufacturer's directions for respirator use. Avoid contact with eyes and skin. Wash hands after using. Keep container closed when not in use. Do not transfer contents to other containers for storage. FIRST AID: In case of eye contact, flush thoroughly with large amounts of water. Get medical attention if irritation persists. If swallowed, call Poison Control Center, hospital emergency room, or physician immediately. DELAYED EFFECTS FROM LONG TERM OVEREXPOSURE. Abrading or sanding of the dry film may release crystalline silica which has been shown to cause lung damage and cancer under long term exposure. WARNING: This product contains chemicals known to the State of California to cause cancer and birth defects or other reproductive harm. DO NOT TAKE INTERNALLY. KEEP OUT OF THE REACH OF CHILDREN.

HOTW 09/23/2008 B34W00551 11 00

The information and recommendations set forth in this Product Data Sheet are based upon tests conducted by or on behalf of The Sherwin-Williams Company. Such information and recommendations set forth herein are subject to change and pertain to the product offered at the time of publication. Consult your Sherwin-Williams representative to obtain the most recent Product Data Sheet.