



**SHERWIN
WILLIAMS®**

| As of 05/01/09, Complies with: | | | |
|--------------------------------|-----|--------------|-----|
| OTC | Yes | LEED® Clv2.0 | Yes |
| SCAQMD | Yes | LEED® NCv2.2 | Yes |
| CARB | Yes | LEED® CSv2.0 | Yes |
| MPI Spec # | No | LEED® H | Yes |
| NAHB | Yes | | |

High BUILD PRIMER

INTERIOR LATEX

B28W8601

PREVIOUSLY PREPRITE® HIGH BUILD PRIMER/SURFACER

| SMOOTHS AND FILLS DRYWALL IMPERFECTIONS | CHARACTERISTICS | SURFACE PREPARATION |
|--|---|---|
| <ul style="list-style-type: none"> Fills and surfaces rough and uneven new drywall construction Uniforms various porosities between drywall paper and joints Ensures the finish coat will be a smooth and uniform sheen Minimizes minor surface imperfections: paper fuzz, minor sanding grooves, nicks, pinholes. <p>For use on these surfaces:</p> <ul style="list-style-type: none"> Drywall Cured Plaster Previously painted surfaces | <p>Color: White</p> <p>Coverage: can be applied from: 400 sq ft/gal @ 4 mils wet; 0.8 mils dry to: 80 sq ft/gal @ 20 mils wet; 4.4 mils dry</p> <p>Drying Time, @ 77°F, 50% RH: Drying and recoat times are temperature, humidity and film thickness dependent.</p> <p>Touch: 1 hour Recoat: 4 hours</p> <p>Finish: 0-10 units @ 85°</p> <p>Flash Point: N/A</p> <p>Tinting - For best color development, use the recommended "P"-shade primer. If desired, up to 4 oz per gallon of Blend-A-Color Toner can be used to approximate the topcoat color. Check color before use. Six minutes minimum mixing on a mechanical shaker is required for complete mixing of color.</p> <p>Vehicle Type: Vinyl Acrylic B28W08601</p> <p>VOC (less exempt solvents): 74 g/L; 0.62 lb/gal</p> <p>Volume Solids: 23 ± 2%</p> <p>Weight Solids: 40 ± 2%</p> <p>Weight per Gallon: 10.6 lb</p> <p>Must be topcoated within 14 days with architectural latex or oil finishes or wallcovering. Apply wallcovering after 24 hours drying.</p> <p>When spot priming on some surfaces, a non-uniform appearance of the final coat may result, due to differences in holdout between primed and unprimed areas. To avoid this, prime the entire surface rather than spot priming.</p> | <p>WARNING! Removal of old paint by sanding, scraping or other means may generate dust or fumes that contain lead. Exposure to lead dust or fumes may cause brain damage or other adverse health effects, especially in children or pregnant women. Controlling exposure to lead or other hazardous substances requires the use of proper protective equipment, such as a properly fitted respirator (NIOSH approved) and proper containment and cleanup. For more information, call the National Lead Information Center at 1-800-424-LEAD (in US) or contact your local health authority.</p> <p>Use on new, bare drywall construction Joint compound must be thoroughly dry and sanded smooth. Repair any significant surface damage, cracks, holes, etc. Remove all sanding dust and construction dust by sweeping or vacuuming. Seal stains from water, ink, pencil, grease, etc. with an appropriate primer sealer.</p> <p>Caulking Fill gaps between walls, ceilings, crown moldings, and other trim with the appropriate caulk after priming the surface.</p> <p>Special Recommendations When topcoating with enamels, 2 topcoats are required for full sheen development, reducing the potential for areas of uneven sheen when touching up.</p> |

108.35

HIGH BUILD PRIMER

INTERIOR LATEX

B28W8601



**SHERWIN
WILLIAMS®**

SURFACE PREPARATION

Mildew

Remove before painting by washing with a solution of 1 part liquid bleach and 3 parts water. Apply the solution and scrub the mildewed area. Allow the solution to remain on the surface for 10 minutes. Rinse thoroughly with water and allow the surface to dry before painting. Wear protective eyewear, waterproof gloves, and protective clothing. Quickly wash off any of the mixture that comes in contact with your skin. Do not add detergents or ammonia to the bleach/water solution.

Caulking

Gaps between walls, ceilings, crown moldings, and other interior trim can be filled with caulk after priming the surface.

Other Uses

To produce a smooth, economical latex wall primer, up to 1 gallon of water can be added to 5 gallons of Primer/Surfacer.

Box thoroughly to a uniform consistency.

To make a thicker surfacer, High Build can be mixed with drywall compounds. The types of compound that can be mixed with High Build are pre-mixed, all purpose and topping compounds. **DO NOT USE QUICK SET COMPOUNDS, THEY WILL CAUSE THE FILM TO CRACK AND PEEL!** Box thoroughly to a uniform consistency.

The following mixes will increase surface build and improve holdout when texturing walls and ceilings:

Spray applied skim coat:
2 parts compound, 1 part High Build

Hopper sprayed spatter texture:
3 or 4 parts compound, 1 part High Build

APPLICATION

Apply at temperatures above 50°F.
No reduction necessary.

Brush

Use a nylon/polyester brush

Roller

Use a 3/8" - 3/4" nap synthetic cover

Airless Spray

Pressure 2000 psi

Tip017" - .021"

Use a coarse filter, 30-40 mesh

CLEANUP INFORMATION

Clean spills, spatters, hands and tools with soap and warm water. After cleaning, flush spray equipment with mineral spirits to prevent rusting of the equipment. Follow manufacturer's safety recommendations when using mineral spirits.

CAUTIONS

For interior use only.
Protect from freezing.
Non-photochemically reactive.

LABEL CAUTIONS

CRYSTALLINE SILICA. Use only with adequate ventilation. To avoid overexposure, open windows and doors or use other means to ensure fresh air entry during application and drying. If you experience eye watering, headaches, or dizziness, increase fresh air, or wear respiratory protection (NIOSH approved) or leave the area. Adequate ventilation required when sanding or abrading the dried film. If adequate ventilation cannot be provided wear an approved particulate respirator (NIOSH approved). Follow respirator manufacturer's directions for respirator use. Avoid contact with eyes and skin. Wash hands after using. Keep container closed when not in use. Do not transfer contents to other containers for storage. **FIRST AID:** In case of eye contact, flush thoroughly with large amounts of water. Get medical attention if irritation persists. If swallowed, call Poison Control Center, hospital emergency room, or physician immediately. **DELAYED EFFECTS FROM LONG TERM OVEREXPOSURE.** Abrading or sanding of the dry film may release crystalline silica which has been shown to cause lung damage and cancer under long term exposure. **WARNING:** This product contains chemicals known to the State of California to cause cancer and birth defects or other reproductive harm. **DO NOT TAKE INTERNALLY. KEEP OUT OF THE REACH OF CHILDREN.**
HOTW 05/13/2009 B28W08601 01 00

The information and recommendations set forth in this Product Data Sheet are based upon tests conducted by or on behalf of The Sherwin-Williams Company. Such information and recommendations set forth herein are subject to change and pertain to the product offered at the time of publication. Consult your Sherwin-Williams representative to obtain the most recent Product Data Sheet.