



**SHERWIN
WILLIAMS.**

SUPERPAINT®

**EXTERIOR LATEX HIGH GLOSS ENAMEL
A85 SERIES**

| | | | |
|--------------------------------|-----|--------------|-----|
| As of 12/03/08, Complies with: | | | |
| OTC | Yes | LEED® C1v2.0 | N/A |
| SCAQMD | No | LEED® NCv2.2 | N/A |
| CARB | Yes | LEED® CSv2.0 | N/A |
| MPI Spec # | No | LEED® H | N/A |
| NAHB | N/A | | |

CHARACTERISTICS

SuperPaint Exterior Latex High Gloss Enamel

Recommended for:

- Doors
- Trim
- Windows
- Shutters

Use on:

- Wood
- Metal—Aluminum, Galvanized, Primed Steel
- Masonry, Cement, Brick, Block
- Stucco
- Vinyl trim, Shutters

Superior Performance in:

- Block Resistance
- Moisture Resistance
- Gloss Retention
- Flow and Leveling

Color: Most colors
Coverage: 350 - 400 sq ft/gal
 @ 4 mils wet: 1.3 mils dry

Drying Time, @ 77°F, 50% RH:
 temperature and humidity dependent
 Touch: 1 hour
 Tack Free: 4 hours
 Recoat: 18 hours

Flash Point: N/A

Finish: 70+ units @ 60°

Tinting with Blend-A-Color:

| Base | oz/gal | Strength |
|----------------|--------|----------|
| Extra White | 0-5 | 100% |
| Light Yellow | 4-12 | 100% |
| Deep Base | 4-12 | 100% |
| Ultradeep Base | 4-12 | 100% |

Vehicle Type: Acrylic

A85W00051

VOC (less exempt solvents):
 98 g/L; 0.82 lb/gal

Volume Solids: 44 ± 2%

Weight Solids: 53 ± 2%

Weight per Gallon: 9.9 lb

Mildew Resistant

This coating contains agents which inhibit the growth of mildew on the surface of this coating film.

SPECIFICATIONS

Aluminum & Aluminum Siding

- 1 ct. All Surface Enamel Latex Primer
- 2 cts. SuperPaint Exterior Latex High Gloss

Block

- 1 ct. Loxon Block Surfacer
- 2 cts. SuperPaint Exterior Latex High Gloss

Brick

- 1 ct. Loxon Conditioner
- 2 cts. SuperPaint Exterior Latex High Gloss

Exterior Drywall

- 1 ct. A-100 Exterior Latex Primer
- 2 cts. SuperPaint Exterior Latex High Gloss

Galvanized Steel

- 1 ct. All Surface Enamel Latex Primer
- 2 cts. SuperPaint Exterior Latex High Gloss

Masonry/Stucco

- 1 ct. Loxon Masonry Primer
- 2 cts. SuperPaint Exterior Latex High Gloss

Plywood

- 1 ct. A-100 Exterior Latex Primer
- 2 cts. SuperPaint Exterior Latex High Gloss

Steel

- 1 ct. All Surface Enamel Primer
- 2 cts. SuperPaint Exterior Latex High Gloss

Vinyl

- 2 cts. SuperPaint Exterior Latex High Gloss

Wood, Composition Board

- 1 ct. A-100 Exterior Oil Primer
- 2 cts. SuperPaint Exterior Latex High Gloss

SURFACE PREPARATION

WARNING! Removal of old paint by sanding, scraping or other means may generate dust or fumes that contain lead. Exposure to lead dust or fumes may cause brain damage or other adverse health effects, especially in children or pregnant women. Controlling exposure to lead or other hazardous substances requires the use of proper protective equipment, such as a properly fitted respirator (NIOSH approved) and proper containment and cleanup. For more information, call the National Lead Information Center at 1-800-424-LEAD (in US) or contact your local health authority.

Remove all surface contamination by washing with an appropriate cleaner, rinse thoroughly and allow to dry. Scrape and sand peeled or checked paint to a sound surface. Sand glossy surfaces dull. Seal stains from water, smoke, ink, pencil, grease, etc. with the appropriate primer/sealer.

Aluminum and Galvanized Steel

Remove any oil, grease, or other surface contamination. All corrosion must be removed with sandpaper, steel wool, or other abrading method.

Cement Composition Siding/Panels

Remove all dirt, dust, grease, oil, loose particles, laitance, foreign material, and peeling or defective coatings. Allow the surface to dry thoroughly. If the surface is new, test it for pH, if the pH is higher than 8, prime with Loxon Acrylic Primer.

102.22

SUPERPAINT®

EXTERIOR LATEX HIGH GLOSS ENAMEL A85 SERIES



**SHERWIN
WILLIAMS.**

SURFACE PREPARATION

Masonry, Concrete, Cement, Block

All new surfaces must be cured according to the supplier's recommendations—usually about 30 days. Remove all form release and curing agents. Rough surfaces can be filled to provide a smooth surface. If painting cannot wait 30 days, allow the surface to cure 7 days and prime the surface with Loxon Acrylic Primer. Cracks, voids, and other holes should be repaired with ConSeal™ Patch or Sealant.

Steel

Rust and mill scale must be removed using sandpaper, steel wool, or other abrading method. Bare steel must be primed the same day as cleaned.

Stucco

Remove any loose stucco, efflorescence, or laitance. Allow new stucco to cure at least 30 days before painting. If painting cannot wait 30 days, allow the surface to dry 5-7 days and prime with Loxon® Masonry Primer. Repair cracks, voids, and other holes with ConSeal™ Patches and Sealants.

Vinyl

Clean the surface thoroughly by scrubbing with warm, soapy water. Rinse thoroughly. Do not paint vinyl siding with any color darker than the original color. Painting with darker colors may cause the siding to warp.

Wood, Plywood

Sand any exposed wood to a fresh surface. Patch all holes and imperfections with a wood filler or putty and sand smooth. All patched areas must be primed.

Caulking

Gaps between windows, doors, trim, and other through-wall openings can be filled with the appropriate caulk after priming the surface.

SURFACE PREPARATION

Mildew

Remove before painting by washing with a solution of 1 part liquid bleach and 3 parts water. Apply the solution and scrub the mildewed area. Allow the solution to remain on the surface for 10 minutes. Rinse thoroughly with water and allow the surface to dry before painting. Wear protective eyewear, waterproof gloves, and protective clothing. Quickly wash off any of the mixture that comes in contact with your skin. Do not add detergents or ammonia to the bleach/water solution.

APPLICATION

Apply at temperatures above 50°F. No reduction needed.

Brush

Use a nylon/polyester brush.

Roller

Use a 3/8"-1/2" SherFab roller cover.

Spray—Airless

Pressure 2000 psi

Tip013"-.017"

SuperPaint High Gloss Enamel sets up very quickly, providing painted surfaces which resists sticking together (blocking). When used at normal temperature and humidity, windows and doors can be closed after 4 hours drying. Maximum blocking resistance is achieved after 24 hours. With this benefit, some adjustments to your painting approach must be made.

- Do not paint in direct sun. Temperatures over 80°F and humidities under 30% will make the paint set up quicker.
- Do not over-work the product. Load paint on the surface, spread to cover, smooth out with long, even strokes. Finish this area before moving to a new area. Do not attempt to brush back into and further uniform an area once finished.
- Work quickly to maintain a wet edge.
- Paint objects in a vertical position to reduce the collection of airborne dirt and dust on the drying paint.

CLEANUP INFORMATION

Clean spills, spatters, hands and tools immediately after use with soap and warm water. After cleaning, flush spray equipment with mineral spirits to prevent rusting of the equipment.

Follow manufacturer's safety recommendations when using mineral spirits.

CAUTIONS

For exterior use only.

Protect from freezing.

Non-photochemically reactive.

LABEL CAUTION

Use only with adequate ventilation. To avoid overexposure, open windows and doors or use other means to ensure fresh air entry during application and drying. If you experience eye watering, headaches, or dizziness, increase fresh air, or wear respiratory protection (NIOSH approved) or leave the area. Avoid contact with eyes and skin. Wash hands after using. Keep container closed when not in use. Do not transfer contents to other containers for storage. **FIRST AID:** In case of eye contact, flush thoroughly with large amounts of water. Get medical attention if irritation persists. If swallowed, call Poison Control Center, hospital emergency room, or physician immediately. **WARNING:** This product contains chemicals known to the State of California to cause cancer and birth defects or other reproductive harm. **DO NOT TAKE INTERNALLY. KEEP OUT OF THE REACH OF CHILDREN.**
HOTW 12/03/2008 A85W00051 14 00

The information and recommendations set forth in this Product Data Sheet are based upon tests conducted by or on behalf of The Sherwin-Williams Company. Such information and recommendations set forth herein are subject to change and pertain to the product offered at the time of publication. Consult your Sherwin-Williams representative to obtain the most recent Product Data Sheet.