



PRO INDUSTRIAL™

113.01
PRE-CATALYZED
WATERBASED EPOXY
 K45-150 SERIES EG-SHEL
 K46-150 SERIES SEMI-GLOSS

CHARACTERISTICS

Pro Industrial Precatalyzed Waterbased Epoxies are revolutionary, single-component pre-catalyzed waterborne acrylic epoxies that offers the adhesion, durability and resistance to stains and most cleaning solvents usually characteristic of two-component waterborne acrylic epoxy products.

These products are low in VOC, have a very mild odor, and can be applied over a wide variety of primers on properly prepared interior metal, wood, masonry, plaster and drywall.

- Interior institutional/commercial high maintenance areas
- Upgrade surfaces painted with conventional coatings with a high performance protection system with excellent adhesion
- Corrosion and Chemical resistant
- Hospitals and Schools
- Institutional dining and kitchen areas
- Suitable for use in USDA inspected facilities

Color: most colors
Recommended Spread Rate per coat:
 4.0 mils wet; 1.5 mils dry
 350 - 400 sq ft/gal

Note: Brush or roll application may require multiple coats to achieve maximum film thickness and uniformity of appearance.

Drying Time, @ 77°F, 50% RH:
 temperature and humidity dependent
 Touch: 1 hour
 Recoat: 8 hours

If this product dries 72 hours or longer it must be sanded before it is recoated. This product is fully cured in approximately 5 - 7 days.

Finish:
 Eg-Shel 20 - 30 units @ 85°
 Semi-Gloss 55 - 65 units @ 60°
Flash Point: N/A

Tinting with Blend-A-Color:
Use SherCOLOR Formulation System
Vehicle Type: Acrylic Epoxy
K45W00151

VOC (less exempt solvents):
 141 g/L; 1.18 lb/gal
Volume Solids: 37 ± 2%
Weight Solids: 51 ± 2%
Weight per Gallon: 10.7 lb ± 0.2 lb

SPECIFICATIONS

Block

- 1 ct. Loxon Block Surfacer
- 2 cts. Pro Industrial Precatalyzed Epoxy

Drywall

- 1 ct. PrepRite 200 Latex Primer
- 2 cts. Pro Industrial Precatalyzed Epoxy

Plaster

- 1 ct. PrepRite Wall and Wood Primer or PrepRite Masonry Primer
- 2 cts. Pro Industrial Precatalyzed Epoxy

Masonry

- 1 ct. PrepRite Masonry Primer
- 2 cts. Pro Industrial Precatalyzed Epoxy

Steel, Aluminum, Galvanized

- 1 ct. Pro Industrial Pro-Cryl Universal Primer
- 2 cts. Pro Industrial Precatalyzed Epoxy

Wood

- 1 ct. PrepRite Wall and Wood Primer or PrepRite Classic Primer
- 2 cts. Pro Industrial Precatalyzed Epoxy

System Tested:

Substrate: Steel
 Surface Preparation: SSPC-SP6
 Primer: 1 ct. DTM Acrylic Primer
 Finish: 1 ct. Pro Industrial PreCatalyzed Epoxy Eg-Shel

As of 09/22/08, Complies with:			
OTC	Yes	LEED® C1v2.0	Yes
SCAQMD	No	LEED® NCv2.2	Yes
CARB	Yes	LEED® CSv2.0	Yes
MPI Spec #	No	LEED® H	N/A
NAHB	N/A		

Adhesion

ASTM D 3359 5B
 100% Adhesion for light colors; Darker colors require longer cure time for same level of adhesion

Pencil Hardness

ASTM D 3363 2B

Block Resistance

Lab Assessment Excellent

Scrub Resistance

ASTM D 2486 500 - 600 cycles with Stiff Bristle Brush and Pumice Scrub Media

Chemical Resistance

ASTM D 1308
 Rating:
 Excellent Resistance •
 Limited Resistance x
 Distilled Water
 (Hot and at Room Temperature) •
 Ethyl Alcohol •
 Vinegar (3% acetic acid) •
 Alkali (10% Sodium Hydroxide) •
 Acid (10% Sulfuric Acid) •
 Soap (10% Fantastik®) •
 50/50 Xylene/Mineral Spirits •

Stain Resistance

ASTM D 3023
 Rating:
 Excellent Resistance •
 Limited Resistance x
 Mustard •
 Grape Juice •
 Red Crayon x
 Lipstick, Red •
 Permanent Ink x
 Coffee •
 10% Sodium Hydroxide (alkali) •
 Acetic Acid •

113.01 PRO INDUSTRIAL™ PRE-CATALYZED WATERBASED EPOXY

K45-150 SERIES EG-SHEL
K46-150 SERIES SEMI-GLOSS



**SHERWIN
WILLIAMS.**

SURFACE PREPARATION

WARNING! Removal of old paint by sanding, scraping or other means may generate dust or fumes that contain lead. Exposure to lead dust or fumes may cause brain damage or other adverse health effects, especially in children or pregnant women. Controlling exposure to lead or other hazardous substances requires the use of proper protective equipment, such as a properly fitted respirator (NIOSH approved) and proper containment and cleanup. For more information, call the National Lead Information Center at 1-800-424-LEAD (in US) or contact your local health authority.

Remove all surface contamination including mildew by washing with an appropriate cleaner, rinse thoroughly and allow to dry. Scrape and sand peeled or checked paint to a sound surface. Sand glossy surfaces dull. Seal stains from water, smoke, ink, pencil, grease, etc. with PrepRite® ProBlock® Primer Sealer.

Aluminum and Galvanized Steel - Remove any oil, grease, or other surface contamination. Remove all corrosion with sandpaper, steel wool, or other abrading method.

Drywall - Fill cracks and holes with patching paste/spackle and sand smooth. Joint compounds must be cured and sanded smooth. Remove all sanding dust.

Masonry, Concrete, Cement, Block - All new surfaces must be cured according to the supplier's recommendations—usually about 30 days. Remove all form release and curing agents. Rough surfaces can be filled to provide a smooth surface. If painting cannot wait 30 days, allow the surface to cure 7 days and prime the surface with PrepRite® Masonry Primer.

SURFACE PREPARATION

Plaster - Bare plaster must be cured and hard. Textured, soft, porous, or powdery plaster should be treated with a solution of 1 pint household vinegar to 1 gallon of water. Repeat until the surface is hard, rinse with clear water and allow to dry.

Steel

Rust and mill scale must be removed using sandpaper, steel wool, or other abrading method. Bare steel must be primed the same day as cleaned.

Wood

Sand any exposed wood to a fresh surface. Patch all holes and imperfections with a wood filler or putty and sand smooth.

Caulking

Gaps between walls, ceilings, crown moldings, and other interior trim can be filled with the appropriate caulk after priming the surface.

APPLICATION

Apply at temperatures above 50°F.

No reduction needed.

Brush

Use a nylon/polyester brush.

Roller

Use a 1/4" - 1/2" nap synthetic cover.

Spray—Airless

Pressure 1800-2700 psi

Tip015"-.021"

CLEANUP INFORMATION

Clean spills, spatters, hands and tools immediately after use with soap and warm water. After cleaning, flush spray equipment with mineral spirits to prevent rusting of the equipment. Follow manufacturer's safety recommendations when using mineral spirits.

CAUTIONS

For interior use only.

Non-Photochemically Reactive

Protect from freezing.

This product is **NOT** recommended for floors or for submerged surfaces, or in areas subject to continuous high moisture such as shower stalls (two-component solvent-based, conventional epoxy products or possibly "wet surface" specialty epoxy products are recommended for these areas).

LABEL CAUTION

Use only with adequate ventilation. To avoid overexposure, open windows and doors or use other means to ensure fresh air entry during application and drying. If you experience eye watering, headaches, or dizziness, increase fresh air, or wear respiratory protection (NIOSH approved) or leave the area. Adequate ventilation required when sanding or abrading the dried film. If adequate ventilation cannot be provided wear an approved particulate respirator (NIOSH approved). Follow respirator manufacturer's directions for respirator use. Avoid contact with eyes and skin. Wash hands after using. Keep container closed when not in use. Do not transfer contents to other containers for storage. **FIRST AID:** In case of eye contact, flush thoroughly with large amounts of water. Get medical attention if irritation persists. If swallowed, call Poison Control Center, hospital emergency room, or physician immediately. **SPILL AND WASTE:** Remove all sources of ignition. Ventilate and remove with inert absorbent. Incinerate in approved facility. Do not incinerate closed container. Dispose of in accordance with Federal, State, and Local regulation regarding pollution. **DELAYED EFFECTS FROM LONG TERM OVEREXPOSURE.** Abrading or sanding of the dry film may release crystalline silica which has been shown to cause lung damage and cancer under long term exposure. **WARNING:** This product contains chemicals known to the State of California to cause cancer and birth defects or other reproductive harm. **DO NOT TAKE INTERNALLY. KEEP OUT OF THE REACH OF CHILDREN. FOR INDUSTRIAL USE ONLY. SEE MATERIAL SAFETY DATA SHEET.**
HOTW 07/23/2008 K45W00151 01 00

The information and recommendations set forth in this Product Data Sheet are based upon tests conducted by or on behalf of The Sherwin-Williams Company. Such information and recommendations set forth herein are subject to change and pertain to the product offered at the time of publication. Consult your Sherwin-Williams representative to obtain the most recent Product Data Information and Application Bulletin.