



Product Finishes

PermaSwade® 9401 Grip

GRIP.....F63TC11
CATALYST.....V66V55
CUSTOM BLEND.....F63ZS

PRODUCT DESCRIPTION

PermaSwade® 9401 Grip is a two component urethane technology designed to give a grip feel to various plastics.

Advantages

- Apply using conventional or HVLP spray methods.
- Free of lead and chromate hazards
- Adheres directly to ABS, PC/ABS, B1000
- Excellent mar resistance.
- RoHS Compliant
- Maximum 4 ounces of Phoenix® Black can be used to make colors.
- Can be used as a topcoat over metallic or pigmented Kem Aqua® 600, Polane® G Plus, Polane® T and Acrylic Lacquer EP® without any loss of performance

CHARACTERISTICS

Volatile Organic Compounds(VOC)* as packaged, less exempts.

3.50 lb/gal, 419 g/L

Catalyzed and Reduced :

2.96 lb/gal, 354 g/L

Gloss at 60°: 10 - 20 units

Volume Solids: 32.8 ± 1%

Weight Solids: 42.8 ± 1%

Viscosity: at 25°C (77°F)

Package 26-32 sec #3 Zahn

Ready to Spray 16-20 sec #3 Zahn

Recommended Film Thickness:

Wet: 3.9 – 6.4 mils

Dry: 1.5 – 2.5 mils

Spreading Rate: (Catalyzed and Reduced)

564 sq.ft./gal. at 1.0 mil DFT

Flash Point: 40°F Pensky-Martens Closed Cup

Package Life: 6 months unopened
V66V55 12 months, Unopened

*VOC compliance limits vary from state to state; please consult local Air Quality rules and regulations.

CHARACTERISTICS (Cont.)

Mixing Ratio: (by volume)

5 parts F63TC11
1 part V66V55
2 parts Reducer R2KS1

Pot Life : 1 Hour

Drying: (1.0 mils, 77°F, 50% R/H)

To Touch 1 Hour
To Handle 3-4 Hours
To Pack Overnight

Force Dry:

Flash off time 5 minutes
30 minutes at 140-180°F

Do not exceed the heat distortion temperature of the substrate.

An Environmental Data Sheet is available from your local Sherwin-Williams facility or at www.paintdocs.com

SPECIFICATIONS

General: Substrate should be free of grease, oil, dirt, fingerprints, drawing compounds, any contamination, and surface passivation treatments to ensure optimum adhesion and coating performance properties.

Plastics: Due to the diverse nature of plastic substrates, a coating or coating system must be tested for acceptable adhesion to the substrate prior to use in production. Reground and recycled plastics along with various fire retardants, flowing agents, mold release agents, and foaming/blowing agents will affect coating adhesion. A filler or primer/barrier coat may be required. Please consult your Sherwin-Williams Product Finishes Sales Representative for system recommendations.

Metal: Consult Metal Preparation Brochure CC-T1 for additional details.

Testing: The information, data, and recommendations set forth in this Product Data Sheet are based upon test results believed to be reliable. However, due to the wide variety of substrates, substrate properties, surface preparation methods, equipment and tools, application methods, and environments, the customer should test the complete system for adhesion, compatibility and performance prior to full scale application.

APPLICATION

Typical Setups

May be applied by:

Conventional Spray
HVLP

Conventional Spray:

Air Pressure 45-55 psi
Fluid Pressure..... 10-15 psi
Tip..... 0.055-0.070

HVLP:

Air Pressure at the cap 10 psi max
Fluid Pressure..... 6-10 psi
Tip..... 0.055-0.070

Cleanup:

Clean tools/equipment immediately after use with R7KC386 reducer, MEK, or MIBK, or n-butyl acetate.

SPECIFICATIONS

Product Limitations:

- Short pot life. Plural component equipment recommended
- Protect from moisture. Water affects pot life and product properties. Store indoors
- At least 1.5 mils is needed to obtain sufficient "feel"
- Heat shortens pot life. Do not spray hot.
- Do not pump catalyzed material into circulating systems. Friction heat developed by pumps and circulation will shorten pot life
- Do not blend with any polyurethane quality. No other catalysts, colorants or reducers are recommended because foreign materials such as alcohols and glycols destroy performance properties. Do not use lacquer thinners or alcohol containing solvents.
- Phoenix® Black is the only pigment allowed. Do not exceed 4 ounces per gallon.

PERFORMANCE TESTING

Adhesion to substrate:

ABS	Excellent
PC-ABS	Excellent
CRS	Excellent
B1000 P99X	Excellent

Linear Abrasion – CS-17

10 cycles, 1000 gram	No visible scratch
50 cycles, 1000 gram	Minor scratches
100 cycles, 1000 gram	Minor scratches
50 Double MEK Rubs	Pass
50 Double IPA Rubs	Pass

Chemical Resistance

(72 hr uncovered spot test over ABS)

Dish Soap	Excellent
Mustard	Stain
Fantastik®	Excellent
Cola	Excellent
IPA	Good
Extra Virgin Olive Oil	Excellent
Vaseline® Hand Lotion	Excellent
Rouge	Excellent
Lip Polish	Excellent
Hair Gel	Excellent
Cucina® Hand Cream	Excellent
Perspirant	Excellent
Ketchup	Excellent
Mayonaise	Excellent
Formula 409®	Excellent
Windex®	Excellent
Acetone	Good
Lipids	Good
Purell® Hand Sanitizer	Excellent

Chemical Resistance (cont) (72 hr uncovered spot test over ABS)

Coffee	Good
LED/LCD Cleaner	Excellent
Clorox® Wipe	Excellent
Banana Boat®	Fail
Oleic Acid	Good

Chemical Resistance

(1 hour covered spot test over ABS)

Lipstick	Excellent
Coffee	Excellent
Mustard	Stain
Water Ink	Excellent
Wax Pencil	Excellent
Red Wine	Stain
Cola	Excellent
Coppertone®	Fail
Nivea® Hand Lotion	Excellent
Formula 409®	Excellent
Ammonia (10%)	Excellent

Environmental Testing

Thermal Cycling:

High and low test extremes

High 66°C, 75% RH(72hrs)

Low 25°C, 50% RH

No Effect

All trademarks are the property of their respective owners

CAUTIONS

FOR INDUSTRIAL SHOP APPLICATION ONLY

Thoroughly review product label and Safety Data Sheet (SDS) for safety information and cautions prior to using this product.

To obtain the most current version of the Environmental Data Sheet (EDS), Product Data Sheet (PDS), or Safety Data Sheet (SDS) please visit your local Sherwin-Williams facility or www.paintdocs.com.

Please direct any questions or comments to your local Sherwin-Williams facility.

CAUTIONS (Cont.)

Catalyst CONTAINS ISOCYANATES. People who have chronic (long-term) lung or breathing problems or have had a reaction to isocyanates, must not be in the area where this product is being applied. Where overspray is present, a positive pressure air-supplied respirator should be worn. If unavailable, a properly fitted organic vapor/particulate respirator may be effective. Consult catalyst MSDS and product label for complete handling instructions.

Note: All purchases of products from Sherwin-Williams are exclusively subject to Sherwin-Williams' terms and conditions of sale which can be found at www.sherwin.com. Please review these terms and conditions prior to the purchase of the products.

Sherwin-Williams warrants the product to be free of manufacturing defect in accordance with Sherwin-Williams' quality control procedures. Except for the preceding sentence, due to factors that are outside of Sherwin-Williams' control, including substrate selection, and customer handling, preparation, and application, Sherwin-Williams cannot make any other warranties related to the product or the performance of the product. SHERWIN-WILLIAMS DISCLAIMS ALL WARRANTIES OF ANY KIND, EXPRESS OR IMPLIED, INCLUDING BUT NOT LIMITED TO THE IMPLIED WARRANTY OF MERCHANTABILITY, THE IMPLIED WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE.

Liability for products proven to be defectively manufactured will be limited solely to replacement of the defective product or the refund of the purchase price paid for the defective product, as determined by Sherwin-Williams. Under no circumstances shall Sherwin-Williams be liable for indirect, special, incidental or consequential damages, lost profits or punitive damages arising from any cause whatsoever.

WKM 3/2017