



General Industrial Coatings

POLANE® 2K Acrylic Waterborne Enamel Monochromatics & Clears

Black F63BL0504 Red Oxide F63RL500 Catalyst V66VL6
30-40 Gloss Clear F63TL0500 White F63WL504 *Custom Blend Series (KA Colorants)..... F63KK
Full Gloss Clear F63CL500 Yellow Oxide F63YL500 *Custom Blend Series (KA SR Colorants). F63KR

DESCRIPTION

Polane® 2K Acrylic Waterborne Enamel is a Non-HAP, <1.1 VOC, two-component, high performance polyurethane coating.

Advantages:

- Good gloss and color retention
- Product is designed for interior use
- Good performance for exterior use
- Clear and Blend monochromatics are provided
- Can be used on metal, plastic, or wood with the appropriate pretreatment, primer or basecoat.
- Designed to meet AAMA 623 and 613
- Can be blended with up to 8 oz/gal Kem Aqua colorants or Kem Aqua Solar Reflective colorants.
- *Formulated to meet < 1.1 lbs./gal. VOC, less exempts.
- Formulated to be non-HAP.

CHARACTERISTICS

60° Gloss:

Monochromatics 30-40
30-40 Gloss Clear, F63TL500 30-40
Full Gloss Clear, F63CL500 85+

Volume Solids (varies by color):

As Packaged 36 ± 2 %
Catalyzed & Reduced 36 ± 2 %

Weight Solids (varies by color):

As Packaged 40 ± 2 %
Catalyzed & Reduced 36 ± 2 %

Viscosity (at 77° F): 20-30 secs., #2 Zahn

Recommended Film Thickness:

Mils Wet 3.0-5.0
Mils Dry 1.1-1.8

Spreading Rate (no application loss):
591 ft.²/gal. at 1.0 mil DFT

*VOC Compliance limits vary from state to state; please consult local Air Quality rules and regulations.

An Environmental Data Sheet is available from your local Sherwin-Williams facility or at www.PaintDocs.Com.

Cure:

Air Dry or
Force Dry Flash 10 mins., 15 mins. at 140° F

Fiberglass Cure Schedule		
Pencil Hardness		
Cure @ 130° F	Post Cure	Overnight
15 mins.	6B	B
60 mins.	3B	HB

PVC Cure Schedule		
Pencil Hardness		
Cure @ 130° F	Post Cure	Overnight
15 mins.	2B	2H
60 mins.	HB	3H

Good air movement and humidity control are necessary for proper drying of water reducible coatings.

Substrate Disclaimer: Curing of coating at temperatures higher than the heat distortion parameters of the substrate may cause substrate issues.

Drying (77° F, 50% RH):

To Touch 20-30 minutes
Tack Free 30-40 minutes
To Handle 40-50 minutes
To Sand 50-60 minutes
To Recoat Sand between coats
No critical recoat time
To Pack Overnight

Mixing Ratio (by volume):

Part A 10 Parts
Catalyst, V66VL6 1 Part

Mixing Ratio With Plural Component:

Part A 12 Parts
Catalyst, V66VL6 1 Part

If you do not use plural component equipment, you must mix at least five minutes with good agitation before spraying.

Working Potlife Is Product Dependent

Monochromatics 4-5 hours
Clears 7-8 hours

Flash Point (Pensky Martens Closed Cup):

Bases N/A ° F
V66VL6 104 ° F

Air Quality Data (as packaged, may vary by color):

Non-photochemically Reactive
Volatile Organic Compounds (VOC), Less Exempts: ≤ 1.1 lb/gal, 125 g/L
Hazardous Air Pollutants (HAPS): Non-HAP

Recommended Storage: Inside, sealed container, 45-95° F, freeze hazard.

Package Life:

Part A 1 year, unopened
Catalyst, V66VL6 9 months, unopened

SPECIFICATIONS

General: All substrates should be free of mold release, oil, grease, dirt, fingerprints, drawing compounds, surface passivation treatments and any other contaminants to ensure optimum adhesion and coating performance. Consult Metal Preparation brochure CC-T1 for additional details. Any use over metal must be primed and/or a basecoat applied. Product does not contain flash rust inhibitors so use over any metal must be tested thoroughly.

Plastics & Composites: Due to the diverse nature of plastic/composite substrates, a coating or coating system must be tested for acceptable adhesion to the substrate prior to use in production. Reground and recycled plastics along with various fire retardants, flowing agents, mold release agents, and foaming/blowing agents will affect coating adhesion. A filler or primer/barrier coat may be required. Please consult your Sherwin-Williams Product Finishes Sales Representative for system recommendations.

Wood (Interior): Must be clean, dry, and finish sanded. Use of Sherwood® Interior Millwork Primer is suggested for priming. Substrate should be free of grease, oil, dirt, fingerprints, and any contamination to ensure optimum adhesion and coating performance properties. Moisture content of wood should be 6-8%.

Wood (Exterior): Must be clean, dry, and finish sanded. Use of exterior alkyd primer or Sherwood 90 Day Exterior Primer is recommended for priming. Due to the nature of wood and use of various primers, these products should be thoroughly tested for exterior performance.

Testing: The information, data, and recommendations set forth in this Product Data Sheet are based upon test results believed to be reliable. However, due to the wide variety of substrates, substrate properties, surface preparation methods, equipment and tools, application methods, and environments, the customer should test the complete system for adhesion, compatibility and performance prior to full scale application.

APPLICATION

Typical Setups

Plural component equipment for mixing is preferred

Mixing Ratio With Plural Component:

Part A	12 Parts
Catalyst, V66VL6	1 Part

May be applied by: Conventional Spray
Airless Spray
Air Assisted Airless Spray
HVLP Spray

Conventional Spray:

Air Pressure	40-60 psi
Fluid Pressure	10-15 psi
Cap/Tip	797/FF

Airless Spray:

Pressure	> 1,500 psi
Tip	Dependent on line speed

Air Assisted Airless Spray:

Air Assist Pressure	20 psi
Fluid Pressure	150-250 psi
Tip	Dependent on line speed

HVLP Spray:

Gun	Binks Mach 1
Air Pressure at the ca[40-65 psi
Fluid Pressure	6-10 psi
Cap/Tip	95P/97

Equipment/application guidelines are only guidelines and individual application & process parameters will dictate exact requirements.

Cleanup: Clean tools and equipment immediately after use with a mixture of 25% Butyl Cellosolve/75% water. Clean V66VL6 with Butyl Acetate. **Do not use solvents such as MEK or acetone to clean up V66VL6, as they may contain water and may cause plug up of lines or equipment.** Flush equipment with solvent to prevent rusting.

Follow manufacturer's safety recommendations when using any solvent.

ADDITIONAL INFORMATION

1. **This product must be properly catalyzed before using. DO NOT VARY CATALYST RATIO.** The catalyst ratio has been established for optimum hardness, flexibility, gloss, and chemical & solvent resistance.
2. Do not store material that has been catalyzed. Pressure can build in closed containers. Use all catalyzed material.
3. Potlife maybe different for each color or clear.
4. Do not freeze. Store between 45 – 90 °F.
5. Due to the wide variety of substrates, surface preparation methods, application methods, and environments, the customer should test the complete system for adhesion and compatibility prior to full scale application.
6. Product is designed for interior use. Product has good performance when used exterior. Please consult your S-W Representative to discuss use for exterior applications.
7. Drying time is dependent on film thickness and atmospheric conditions. Heavier film thickness causes slow drying.
8. **If Solar Reflective colors are used for a heat sensitive substrate, then only the Clear and Monochromatic White can be used in the formula.**
9. Compatible with Kem Aqua Colorants. Do not add more than 8 ounces of Kem Aqua or Kem Aqua Solar Reflective Colorants per gallon of base.

	Colorant Used	
	Kem Aqua Colorants	Kem Aqua Solar Reflective Colorants
Blend Prefix To Use	F63KK	F63KR

All trademarks are the property of their respective owners.

CAUTIONS

FOR INDUSTRIAL SHOP APPLICATION ONLY

Thoroughly review the product label and Safety Data Sheet (SDS) for safety information and cautions prior to using this product.

To obtain the most current version of the Environmental Data Sheet (EDS), Product Data Sheet (PDS), or Safety Data Sheet (SDS) please visit your local Sherwin-Williams facility or www.PaintDocs.Com.

Please direct any questions or comments to your local Sherwin-Williams facility.

Note:

All purchases of products from Sherwin-Williams are exclusively subject to Sherwin-Williams' [Standard Terms And Conditions Of Sale](#). Please review these terms and conditions prior to the purchase of the products.

Sherwin-Williams warrants the product to be free of manufacturing defect in accordance with Sherwin-Williams' quality control procedures. Except for the preceding sentence, due to factors that are outside of Sherwin-Williams' control, including substrate selection, and customer handling, preparation, and application, Sherwin-Williams cannot make any other warranties related to the product or the performance of the product. **SHERWIN-WILLIAMS DISCLAIMS ALL WARRANTIES OF ANY KIND, EXPRESS OR IMPLIED, INCLUDING BUT NOT LIMITED TO THE IMPLIED WARRANTY OF MERCHANTABILITY, THE IMPLIED WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE.**

Liability for products proven to be defectively manufactured will be limited solely to replacement of the defective product or the refund of the purchase price paid for the defective product, as determined by Sherwin - Williams. Under no circumstances shall Sherwin-Williams be liable for indirect, special, incidental or consequential damages, lost profits or punitive damages arising from any cause whatsoever.

Building Products Lab / Columbus, MO