



MIL-PRF-22750G, Type III High Solids Epoxy DTM

Tan 686A, 23446..... F92H102
Interior Aircraft Gray, 36231.... F93A33
Medium Gray, 36375..... F93A604

Tan 686A, 33446 F93H4
Gray, 26492..... F92A27
White, 27875 F92W228

Interior Aircraft Gray, 26231 F92A28
Green, 24300 F92G28
Seafoam Green 24533 F92G228
Catalyst (Component B) V93V234

DESCRIPTION	CHARACTERISTICS	SPECIFICATIONS								
<p>MIL-PRF-22750G Type III High Solids Epoxy DTM is a 2-component direct-to-metal epoxy topcoat for interior applications. This product contains less than 0.01 lb/gal VOC* as packaged. This epoxy coating is intended for use as a DTM topcoat for the interior of military ground equipment. This product is applied over zinc phosphate steel and treated aluminum.</p> <p>Advantages:</p> <ul style="list-style-type: none">• Good corrosion protection• 0.01 lb/gal VOC as packaged• Excellent flow characteristics• Free of lead hazards• Good combination of potlife and dry time. <p>The following products are approved by the U. S. Army Research Lab, Aberdeen Proving Ground, Aberdeen, MD</p> <table><tr><td><u>Sherwin-Williams#</u></td><td><u>QPD#</u></td></tr><tr><td>F92A28</td><td>Q2241</td></tr><tr><td>F92G228</td><td>Q2131</td></tr><tr><td>F93A604</td><td>Q2240</td></tr></table> <p>Per Section 6.4.1 of MIL-PRF-22750G w/ Amendment 1, extension to other semi-gloss and lusterless colors are made with the qualification of all three of the color numbers 24533, 26231, and 36375.</p> <p>An Environmental Data Sheet is available from your local Sherwin-Williams facility or at www.paintdocs.com</p> <p>*VOC compliance limits vary from state to state; please consult local Air Quality rules and regulations</p>	<u>Sherwin-Williams#</u>	<u>QPD#</u>	F92A28	Q2241	F92G228	Q2131	F93A604	Q2240	<p>Gloss (60°):</p> <p>Semi Gloss 15-30 units Camouflage Colors 0-5 units @ (1.7-2.3 mils dry)</p> <p>Package, pigmented component Weight/Gallon (Lbs): 13.40 ± 0.3</p> <p>Volume Solids: Component A: 51.3 - 53.6 ± 1% varies by color</p> <p>Weight Solids: Component A: 69.2 - 72.4 ± 1% varies by color</p> <p>Application Viscosity: Admixed: 50 secs. max #4 Ford Cup</p> <p>Recommended film thickness: Mils Wet 4.2-5.1 Mils Dry 1.7-2.3</p> <p>Apply one wet coat to 1.7-2.3 mils dry film thickness. Do not dry spray. Dry spray will reduce gloss.</p> <p>Spreading Rate (no application loss) 686 sq ft/gal @ 1.0 mils DFT</p> <p>Drying (2.0 mils dft, 77°F, 50% RH): Set to Touch: 4 hours maximum Dry Hard: 8 hours maximum Complete Cure: 7 days</p> <p>Flash Point: 50-53°F PMCC</p> <p>Mixing Ratio: 4 parts by volume Component A 1 part Component (V93V234) 1 part Reducer</p> <p>Induction Time: 30 minutes</p> <p>Pot Life: 4 hours at room temperature - higher temperature will shorten pot life.</p> <p>Package Life: 18 months, inside storage V93V234 24 months, inside storage</p> <p>Air Quality Data: Photochemically reactive Volatile Organic Compounds (VOC) Theoretical: catalyzed as above and reduced with MAK, less exempt 1.90 lb/gal, 228 g/L</p>	<p>Steel: Surface must be clean and free of grease, dirt, oil, rust, fingerprints, and other contaminants to insure optimum adhesion and performance properties.</p> <p>Aluminum: Clean with acidic cleaner or other appropriate cleaner depending on contamination. Pretreat with chromate conversion coating MIL-DTL-5541, wash primer DOD-P-15328 (E90G4), or anodize per MIL-A-8625—MIL-C-8514 (E90G16).</p> <p>Galvanized and other metals: Clean and remove oxidation contamination on surface, followed by treatment with DOD-P-15328D wash primer (E90G4), MIL-C-8514 (E90G16), or anodize per MIL-A-8625. Due to the variability in these surfaces, testing adhesion on each situation is recommended.</p> <p>Primers may be applied under the topcoat. For ferrous substrates, use MIL-DTL-53022 primers.</p> <p>For non-ferrous substrates, MIL-PRF-23377(E90G203) (Type I, Class C2 , 2.8 VOC); or MIL-DTL-53022.</p> <p>Check the data sheet of each primer for recoat time of topcoat.</p> <p>Testing: The information, data, and recommendations set forth in this Product Data Sheet are based upon test results believed to be reliable. However, due to the wide variety of substrates, substrate properties, surface preparation methods, equipment and tools, application methods, and environments, the customer should test the complete system for adhesion, compatibility and performance prior to full scale application.</p>
<u>Sherwin-Williams#</u>	<u>QPD#</u>									
F92A28	Q2241									
F92G228	Q2131									
F93A604	Q2240									

APPLICATION

Typical Setups

Reduction: Reduce with MAK, R6K30, Oxsol or Dimethyl Carbonate.

Please consult with your Sherwin-Williams sales representative for proper settings for your spray equipment.

Cleanup:

Clean tools/equipment immediately after use with MIL-T-81772 Type II Thinner (R91K210), MEK (R6K10), or other epoxy reducer. A blend of MIBK and Xylene works well also.

Follow manufacturer's safety recommendations when using any solvent.

SPECIFICATIONS

Product Limitations:

- MIL-PRF-22750 Type III coatings (Component A) must be catalyzed with Catalyst (Component B), V93V234, at 4:1 ratio by volume.
- Do not use other catalysts.
- Do not vary catalyst mixing ratio.
- Component A must be well agitated prior to use.
- Agitate entire mixture, Component A, Component B, and Reducer well before spray.
- A 30 minute induction period is necessary.
- Potlife will be shorter with warmer temperatures.
- Force drying will lower the gloss of this product. This coating is recommended for interior application only.

Performance Properties:

Meets all the performance properties of MIL-PRF-22750G.

CAUTIONS

FOR INDUSTRIAL SHOP APPLICATION ONLY

Thoroughly review product label and Safety Data Sheet (SDS) for safety information and cautions prior to using this product.

To obtain the most current version of the Environmental Data Sheet (EDS), Product Data Sheet (PDS), or Safety Data Sheet (SDS) please visit your local Sherwin-Williams facility or www.paintdocs.com.

Please direct any questions or comments to your local Sherwin-Williams facility

Note: All purchases of products from Sherwin-Williams are exclusively subject to Sherwin-Williams' terms and conditions of sale which can be found [by following this link \(click here\)](#). Please review these terms and conditions prior to the purchase of the products.

Sherwin-Williams warrants the product to be free of manufacturing defect in accordance with Sherwin-Williams' quality control procedures. Except for the preceding sentence, due to factors that are outside of Sherwin-Williams' control, including substrate selection, and customer handling, preparation, and application, Sherwin-Williams cannot make any other warranties related to the product or the performance of the product. **SHERWIN-WILLIAMS DISCLAIMS ALL WARRANTIES OF ANY KIND, EXPRESS OR IMPLIED, INCLUDING BUT NOT LIMITED TO THE IMPLIED WARRANTY OF MERCHANTABILITY, THE IMPLIED WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE.**

Liability for products proven to be defectively manufactured will be limited solely to replacement of the defective product or the refund of the purchase price paid for the defective product, as determined by Sherwin-Williams. Under no circumstances shall Sherwin-Williams be liable for indirect, special, incidental or consequential damages, lost profits or punitive damages arising from any cause whatsoever.