



**SHERWIN  
WILLIAMS.**

# Product Finishes

CC-E38

## KEM AQUA® BP Siding Select

White ..... M64WL0580  
 Red Oxide ..... M64RL0583  
 Green ..... M64GL0586

Blending Clear.....M64CL0581  
 Yellow Oxide .....M64YL0584  
 Bright Red .....M64RL0587

Black ..... M64BL0582  
 Blue ..... M64LL0585  
 Bright Yellow ..... M64YL0588  
 Custom Blend..... M64SS Series

<u>DESCRIPTION</u>	<u>CHARACTERISTICS</u>	<u>APPLICATION</u>
<p><b>KEM AQUA® BP Siding Select</b> is a premium waterborne single-component monochromatic coating for wood and composite siding and building products. It is formulated with polyurethane dispersion technology and is available in a wide range of colors using monochromatic bases. Colors can also be made utilizing KEM AQUA® Solar Reflective colorants for temperature sensitive substrates. Kem AQUA® BP Siding Select is ideal for (but not limited to) primed wood, primed LP Smartside®, primed fiber cement, polymer composite and other composite substrates common to building products.</p> <p><b>Advantages:</b></p> <ul style="list-style-type: none"> <li>• Excellent gloss and color retention</li> <li>• Enhanced pigment platform with UV absorbers</li> <li>• Formulated for a wide range of application tolerances</li> <li>• Available in a wide range of colors with consistent performance across many substrates</li> <li>• Excellent mar and scuff resistance</li> <li>• Designed for exterior use. Can also be used for interior applications.</li> </ul> <p>An Environmental Data Sheet is available from your local Sherwin-Williams facility or at <a href="http://www.paintdocs.com">www.paintdocs.com</a>.</p> <p>*VOC compliance limits vary from state to state; please consult local Air Quality rules and regulations.</p>	<p><b>Typical of M64WL580 White</b></p> <p><b>Gloss 60°:</b> 12 - 18 units</p> <p><b>Volume Solids:</b> 39 ± 1% calculated varies by color</p> <p><b>Package Viscosity:</b> 24 – 42 Sec #3 Signature Zahn Cup, varies by color</p> <p><b>Recommended film thickness per coat:</b>  Mils Wet 5.0 mils minimum  Mils Dry 1.9 mils minimum</p> <p><b>Spreading Rate</b> (no application loss)  327 sq ft/gal @ 1.9 mils DFT</p> <p><b>Drying</b> (77°F, 50% RH):  To Touch: 10 – 15 minutes  To Handle: 40 – 50 minutes  To Recoat: No critical recoat (sand between coats)  To Topcoat: As soon as able to handle  To Pack: 16 hours  Force Dry: 3-5 minutes flash then cure with high velocity air for 25-30 minutes at 140°F  Results are dependent on line and factory conditions</p> <p>Do not exceed the heat distortion temperature of the substrate.</p> <p><b>Flash Point:</b> &gt;199°F Pinsky-Martens Closed Cup</p> <p><b>Package Life:</b> M64LL0585, 6 months, unopened  All others, 12 months, unopened</p> <p><b><u>REGULATORY</u></b></p> <p><b>Air Quality Data:</b></p> <ul style="list-style-type: none"> <li>• Non-Photochemically reactive</li> <li>• VOC* theoretical as packaged, maximum, less water and exempt solvents: 1.07 lbs/gal, 129 g/L</li> <li>• VOC maximum emitted 0.43 lbs/gal, 51 g/L</li> <li>• VHAPS as packaged 0.00 lbs/gal solids, 0.00 g/L solids</li> </ul>	<p><b>Typical Setups</b></p> <p><b>May be applied by:</b>  Spray, flood coater, direct roll coater and curtain coating</p> <p><b>Airless Spray:</b>  Pressure ..... 1000 - 1800 psi  Tip ..... Dependent on line speed</p> <p><b>Air Assisted Airless:</b>  Air Assist Pressure ..... 20- 30 psi  Fluid Pressure ..... 200-600 psi</p> <p><b>Flood coater, direct roll coater, curtain coater:</b>  Consult SW representative to discuss specific line settings</p> <p><b>Cleanup:</b>  Clean tools and equipment immediately after use with MEK (R6K10).</p> <p>Follow manufacturer's safety recommendations when using solvents.</p> <p>If no solvents are available, a 5-10% ammonia in water blend is suggested</p>

## SPECIFICATIONS

**General:** Substrate should be free of grease, oil, dirt, fingerprints, drawing compounds, any contamination. Low energy substrates could benefit from surface passivity treatments to ensure optimum adhesion and coating performance properties. Consult industry suppliers for detailed recommendations.

**Plastic/composites:** A solvent wipe (IPA or Acetone) is recommended. Due to the diverse nature of plastic/composite substrates, a coating or coating system must be tested for acceptable adhesion to the substrate prior to use in production. Re-ground and recycled plastics along with various fire retardants, flowing agents, mold release agents, and foaming/blowing agents will affect coating adhesion. A filler or primer/barrier coat may be required. Please consult your Sherwin-Williams Sales Representative for system recommendations.

**Wood (interior):** Must be clean, dry, and finish sanded. Use of interior millwork primer is recommended for priming. Substrate should be free of any contamination to ensure optimum adhesion and coating performance properties. Moisture content of wood should be equilibrated to plant conditions to minimize warping from application and cure procedure.

**Wood (Exterior) –** Must be primed clean, dry, and finish sanded with 240 – 320 grit paper. Use suitable exterior quality millwork primer. Due to the nature of wood and use of various primers these products should be thoroughly tested for exterior performance.

**Fiber Cement :** Check pH prior to application. The recommended pH range is 6-13. An additional coat of suitable primer in addition to factory applied primer is recommended followed by one or two coats of basecoat.

**Testing:** The information, data, and recommendations set forth in this Product Data Sheet are based upon test results believed to be reliable. However, due to the wide variety of substrates, substrate properties, surface preparation methods, equipment and tools, application methods, and environments, the customer should test the complete system for adhesion, compatibility and performance prior to full scale application.

All trademarks are the property of their respective owners

## ADDITIONAL INFORMATION

- **All colors for heat sensitive substrates (Vinyl, PVC, etc) MUST be submitted to the Building Products Lab for TSR and HBU testing and approval before the product is used in customer production environments. Contact Building Products Lab or Building Products Marketing for further details.**
- **Bright Yellow (M64YL0588) and Bright Red (M64RL0587) are intended for interior applications. Use of these colorants for exterior applications should be evaluated on a case by case basis**
- Please consult your Sherwin-Williams Representative to discuss use for exterior applications.
- Do not use M64CL581 (Blending Clear) as a stand alone clear finish. It is intended to be used for custom blending.
- Solar Reflective colors are made blending M64WL0580 White and M64CL0581 Clear with up to 8 oz/gal Kem Aqua® Solar Reflective colorants for temperature sensitive substrates. Detailed information on SR products is available.
- Settling may occur during storage. Shake or mix well before using
- Kem AQUA® BP Siding Select requires complete evaluation including application and performance for each end user on each substrate to qualify for use
- Intended for OEM applicators only
- Protect from freezing. Store inside between 45°- 90°F.
- Do not apply below 60°F. Recommended application temperature is 60° - 90° F
- Good air movement and humidity control are necessary for proper drying of water reducible coatings. Cold and moist conditions prolong cure dramatically if conditions are near dew point. Seven days is necessary for full cure. Slip sheeting is recommended especially for fiber cement and heavy or abrasive substrates. Packaging should allow finished products to breath to allow excess moisture to escape.

## CAUTIONS

### FOR INDUSTRIAL SHOP APPLICATION ONLY

Thoroughly review product label and Safety Data Sheet (SDS) for safety information and cautions prior to using this product.

To obtain the most current version of the Environmental Data Sheet (EDS), Product Data Sheet (PDS), or Safety Data Sheet (SDS) please visit your local Sherwin-Williams facility or [www.paintdocs.com](http://www.paintdocs.com).

Please direct any questions or comments to your local Sherwin-Williams facility.

**Note:** All purchases of products from Sherwin-Williams are exclusively subject to Sherwin-Williams' terms and conditions of sale which can be found [by following this link \(click here\)](#) Please review these terms and conditions prior to the purchase of the products.

Sherwin-Williams warrants the product to be free of manufacturing defect in accordance with Sherwin-Williams' quality control procedures. Except for the preceding sentence, due to factors that are outside of Sherwin-Williams' control, including substrate selection, and customer handling, preparation, and application, Sherwin-Williams cannot make any other warranties related to the product or the performance of the product. **SHERWIN-WILLIAMS DISCLAIMS ALL WARRANTIES OF ANY KIND, EXPRESS OR IMPLIED, INCLUDING BUT NOT LIMITED TO THE IMPLIED WARRANTY OF MERCHANTABILITY, THE IMPLIED WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE.**

Liability for products proven to be defectively manufactured will be limited solely to replacement of the defective product or the refund of the purchase price paid for the defective product, as determined by Sherwin- Williams. Under no circumstances shall Sherwin-Williams be liable for indirect, special, incidental or consequential damages, lost profits or punitive damages arising from any cause whatsoever