

CC-F61

SHER-WOOD[®] KEMVAR[®] Glaze

Van Dyke Brown	. S66N31
Natural	S66T30
Custom Blend	. S66SG Series

DESCRIPTION **CHARACTERISTICS** SHER-WOOD® KEMVAR® Glaze is an **Volume Solids:** $27 - 30 \pm 1\%$ alkyd type glaze formulated for use with Varies by color a wide variety of Sher-Wood finishes to provide color and accents to interior Weight Solids: $34 - 40 \pm 1\%$ wood products. Varies by color Advantages: Viscosity: 53 - 63 KU Stormer · Ready-to-use · Clean color attains rich wood tones Recommended film thickness: NA No color fade or bleeding Apply full wet coat and wipe clean · Excellent clarity-highlights wood grain Good workability - 10 minute open **Drying:** (77 DF, 50% RH): working time To Handle: 15 minutes 30 minutes · Excellent rewetting of glaze even after To Recoat: 24 hours drying Force Dry: 5-15 minutes at 120 DF · Excellent adhesion on unsanded or 10 minutes at 140 DF catalyzed Good air movement is necessary for materials such as adequate drying. conversion varnish and catalvzed lacquers Flash Point: • Apply by spray, brush, dip or cloth 40°F PMCC · May be used with all Sher-Wood Package Life: 24 months unopened solvent borne Sealer and Topcoat systems Air Quality Data: Non-photochemically reactive Volatile Organic Compounds (VOC) Not Stocked - Special Order Only: theoretical as packaged, maximum, White...... S66W32 less exempt solvents: 4.83 lb/gal, 579 g/L · Volatile Hazardous Air Pollutants (VHAPS) as packaged, maximum: < 0.8 lb/lb solids An Environmental Data Sheet is available from your local Sherwin-Williams facility, or at www.paintdocs.com.

SPECIFICATIONS

General: Surface should be free of grease, oil, dirt, fingerprints, and any contamination to ensure optimum adhesion and coating performance properties. Sealer, basecoat or topcoat should be thoroughly dried, sanded and dust free prior to glazing.

Testing: The information, data, and recommendations set forth in this Product Data Sheet are based upon test results believed to be reliable. However, due to the wide variety of substrates, substrate properties, surface preparation methods, equipment and tools. application methods, and environments, the customer should test the complete system for adhesion, compatability and performance prior to full scale application.

APPLICATION

Product must be used under agitation.

- Wipe off excess glaze. Heavy glaze films may cause adhesion problems.
- Reduce as required to adjust strength or modify drying characteristics. Use mineral spirits to reduce, use R1K140 to retard.
- Dry 30 minutes air dry. Force dry 5-15 minutes at 120F.
- If wiping becomes difficult due to dryness of stain, rewet with a cloth dipped in glaze and then re-wipe.

Sher-Wood Natural Filler D70T1 can be added to the S66 glaze to increase the filling properties of the glaze. Penetrating Oil V82V50 can be added to the S66 glaze to provide the glaze with higher vehicle content. This will provide an oilier glaze at application that could improve open time and wiping characteristics.

May be applied by:

Conventional Spray Airless Spray Air Assisted Airless **HVLP** Dip

Cleanup:

Clean tools/equipment immediately after use with mineral spirits.

Flush equipment with solvent to prevent rusting.

Follow manufacturer's safety recommendations when using any solvent.

All trademarks are the property of their respective owners.

ADDITIONAL INFORMATION

CAUTIONS

FOR INDUSTRIAL SHOP APPLICATION

ONLY

Thoroughly review product label and

Safety Data Sheet (SDS) for safety

information and cautions prior to

To obtain the most current version of the

Product Data Sheet (PDS), or Safety

Please direct any questions or comments

to your local Sherwin-Williams facility.

Sherwin-Williams

Sheet (EDS),

facility

visit your

or

using this product.

www.paintdocs.com.

local

Environmental Data

Data Sheet (SDS) please

- For interior use only. •
- Do not use under ULTRA-CURE® UV products.
- Agitation is recommended to maintain uniform color.
- Final color is influenced by wood type and substrate variations. Solvent based glaze may appear very strong in color on soft wood. If color is too deep, reduce glaze with solvent or allow less drying time before wiping.
- Not recommended for exterior use.
- Customer should pretest glaze on substrate and under coating system.
- Do not exceed 10% SHER-WOOD®
- SB Colorants (D59B70 series) in S66N31 and S66W32. Do not exceed 25% SHER-WOOD® SB tinting may affect adhesion.
- Sealed or finished surfaces must be glazed and top coated within 16 hours, otherwise the surface must be sanded prior to glazing.

Performance Tests:

Cross Hatch Adhesion: 3B to 5B of glaze left on the surface.

Colorants in S66T30. Excessive Note: Each purchase and/or use of products from Sherwin-Williams are exclusively subject to Sherwin-Williams' terms and conditions of sale which can be found here: www.sherwin-williams.com/terms-andconditions#standard-tc

Please review these terms and conditions prior to each purchase and/or use of the products.

Sherwin-Williams warrants the product to be manufactured in accordance with Sherwin-Williams' quality control procedures. Except for the preceding sentence, SHERWIN-WILLIAMS SPECIFICALLY DISCLAIMS ALL depending on coating system and amount WARRANTIES OF ANY KIND, EXPRESS OR IMPLIED, INCLUDING BUT NOT LIMITED TO THE IMPLIED WARRANTY OF IMPLIED MERCHANTABILITY, THE WARRANTY OF FITNESS FOR PARTICULAR PURPOSE.

> Sherwin-Williams' liability for products will be limited solely to replacement of the defective product or the refund of the purchase price paid for the defective product, as determined by Sherwin-Williams. Under no circumstances shall Sherwin-Williams be liable for indirect, special, incidental, or consequential damages, lost profits or punitive damages arising from any cause whatsoever.