



Protective & Marine Coatings

DURA-PLATE® 2300 (FORMERLY COROBOND 300) WATERBASED EPOXY CEMENTITIOUS RESURFACER

KIT	B58A320	DURA-PLATE 2300 KIT
PART A	2300A	HARDENER
PART B	2300B	CONCRETE GRAY
PART C	2300C	MORTAR

Revised: May 2, 2025

PRODUCT INFORMATION

TRM.68

PRODUCT DESCRIPTION

DURA-PLATE 2300 is a three component, epoxy modified cementitious resurfacer containing Portland Cement, hydrophobic thixotropes, fiber reinforcement, graded silica sand and other abrasion resistant aggregates. It is used for resurfacing, patching and filling voids (bugholes) in concrete and masonry structures. Dura-Plate 2300 provides a hard durable surface with excellent adhesion that minimizes outgassing problems typically associated with coating concrete.

PRODUCT DESCRIPTION

Finish:	Flat
Color:	Concrete Gray
Density:	110 lb/cubic ft.
Volume Solids:	100%, mixed
VOC:	19 g/L; 0.15 lb/gal, mixed
Mix Ratio:	3.1 gallon, pre-measured kit

Recommended Spreading Rate:

Coverage for 3.1 gallon kit: Approximately 77 ft² (7.2 m²) at 1/16" thickness; 38.5 ft² (3.6m²) at 1/8" thickness; 19.25 ft² (1.8 m²) at 1/4" thickness; 10 ft² (1.7 m²) at 1/2" thickness

Drying Schedule:

	@ 40°F/4.5°C	@ 77°F/25°C	@ 85°F/29°C
--	--------------	-------------	-------------

To touch:	6-8 hours	3-4 hours	2-3 hours
-----------	-----------	-----------	-----------

Topcoat/Overcoat:			
-------------------	--	--	--

minimum:	12 hours	8 hours	8 hours
----------	----------	---------	---------

maximum:	Unlimited	Unlimited	Unlimited
----------	-----------	-----------	-----------

Drying time is temperature, humidity, and film thickness dependent.

Pot Life:	90 minutes	70 minutes	45 minutes
-----------	------------	------------	------------

Sweat-in-Time:	None required		
----------------	---------------	--	--

Shelf Life:	24 months, unopened Store indoors at 40°F (4.5°C) to 100°F (38°C).
-------------	--

Flash Point:	>200°F (93°C), mixed
--------------	----------------------

Reducer:	Not recommended
----------	-----------------

Clean Up:	Soap and warm water
-----------	---------------------

RECOMMENDED USES

Concrete Structures

- Water
- Wastewater
- Secondary containment
- Power
- Food and Beverage
- Sewer Collection Systems

PERFORMANCE CHARACTERISTICS

Substrate*: Concrete

Surface Preparation*: SSPC-SP13/NACE 6, ICRI Concrete Surface Profile (CSP) 5

System Tested*:

1 ct. Dura-Plate 2300 @ 3/16" dft

*28-day cure unless otherwise noted below

Test Name	Test Method	Results
Adhesion to Concrete	ASTM D7234	403 psi* / >438 psi**
Coefficient of Thermal Expansion	ASTM C531	6.9 x 10 ⁻⁶ in/in/F**
Flexural Strength	ASTM C293	795 psi* / > 1,270 psi**
Linear Shrinkage	ASTM C596 ASTM C531	-0.014%** -0.366%**
Modulus of Elasticity	ASTM C469	>1,680,000 psi* >1,860,000 psi **
Shear Bond	ASTM C882	2,094* / 2,804 psi**
Shrinkage	ASTM C157	<0.18%**
Splitting Tensile Strength	ASTM C496	480 psi* / 600 psi**
Tensile Strength	ASTM C307	>600 psi*

* 24 hour cure

** 28-day cure



Protective & Marine Coatings

DURA-PLATE® 2300 (FORMERLY COROBOND 300) WATERBASED EPOXY CEMENTITIOUS RESURFACER

KIT	B58A320	DURA-PLATE 2300 KIT
PART A	2300A	HARDENER
PART B	2300B	CONCRETE GRAY
PART C	2300C	MORTAR

Revised: May 2, 2025

PRODUCT INFORMATION

TRM.68

RECOMMENDED SYSTEMS

Dry Film Thickness / ct.
Mils (Microns)

Concrete:

1 ct. Dura-Plate 2300 to 1/2" maximum thickness

Acceptable topcoats:

Dura-Plate 5900 (Formerly Cor-Cote SC Plus)

Dura-Plate 6000

Dura-Plate 6100

Poly-Cote 115 primed with Corobond 100 (Non Potable Water)

Poly-Cote 115 with SherPlate 600 (Potable Water Applications)

SherFlex primed with Corobond 100 (Non Potable Water)

SherFlex primed with Dura-Plate 235

Sher-Glass FF

SherPlate PW

Note: Do not use in conjunction with vinyl ester and polyester coatings or lining systems. Other coatings may be acceptable. Please consult with your Sherwin-Williams representative.

SURFACE PREPARATION

Surface must be clean, in sound condition, and surface saturated dry. Remove all oil, dust, grease, dirt, loose rust, and other foreign material to ensure adequate adhesion.

Refer to product Application Bulletin for detailed surface preparation information.

Minimum recommended surface preparation:

Concrete & Masonry:	SSPC-SP13/NACE 6, or ICRI No. 310.2R, CSP 3-5
---------------------	--

TINTING

Do not tint.

APPLICATION CONDITIONS

Temperature:	40°F (4.5°C) minimum, 95°F (35°C) maximum (air, surface, and material) At least 5°F (2.8°C) above dew point
--------------	---

Refer to product Application Bulletin for detailed application information.

ORDERING INFORMATION

Packaging:	3.1 gallon kit
Component A:	4 oz
Component B:	128 oz
Component C:	35.5 lbs

Weight:	16 lb/gal, mixed
---------	------------------

SAFETY PRECAUTIONS

Refer to the SDS sheet before use.

Published technical data and instructions are subject to change without notice. Contact your Sherwin-Williams representative for additional technical data and instructions.

WARRANTY

The Sherwin-Williams Company warrants our products to be free of manufacturing defects in accord with applicable Sherwin-Williams quality control procedures. Liability for products proven defective, if any, is limited to replacement of the defective product or the refund of the purchase price paid for the defective product as determined by Sherwin-Williams. NO OTHER WARRANTY OR GUARANTEE OF ANY KIND IS MADE BY SHERWIN-WILLIAMS, EXPRESSED OR IMPLIED, STATUTORY, BY OPERATION OF LAW OR OTHERWISE, INCLUDING MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE.

DISCLAIMER

The information and recommendations set forth in this Product Data Sheet are based upon tests conducted by or on behalf of The Sherwin-Williams Company. Such information and recommendations set forth herein are subject to change and pertain to the product offered at the time of publication. Consult your Sherwin-Williams representative to obtain the most recent Product Data Information and Application Bulletin.

The systems listed above are representative of the product's use, other systems may be appropriate.



Protective & Marine Coatings

DURA-PLATE® 2300 (FORMERLY COROBOND 300) WATERBASED EPOXY CEMENTITIOUS RESURFACER

KIT	B58A320	DURA-PLATE 2300 KIT
PART A	2300A	HARDENER
PART B	2300B	CONCRETE GRAY
PART C	2300C	MORTAR

Revised: May 2, 2025

APPLICATION BULLETIN

TRM.68

SURFACE PREPARATIONS

Surface must be clean, in sound condition, and surface saturated dry. Remove all oil, dust, grease, dirt, loose rust, and other foreign material to ensure adequate adhesion.

Concrete and Masonry

For surface preparation, refer to SSPC-SP13/NACE 6, or ICRI No. 310.2R, CSP 3-5. Thoroughly clean and surface saturated dry as described in performance tips. Concrete and mortar must be cured at least 28 days @ 75°F (24°C). Remove all loose mortar and foreign material. Surface must be free of laitance, concrete dust, dirt, form release agents, loose cement and hardeners.

Follow the standard methods listed below when applicable:

ASTM D4258 Standard Practice for Cleaning Concrete.
ASTM D4259 Standard Practice for Abrading Concrete.
ASTM D4260 Standard Practice for Etching Concrete.
ASTM F1869 Standard Test Method for Measuring Moisture Vapor Emission Rate of Concrete.
ASTM D4263 Standard Test Method for Indicating Moisture in Concrete by Plastic Sheet Method
SSPC-SP 13/Nace 6 Surface Preparation of Concrete.
ICRI No. 310.2R Concrete Surface Preparation.

APPLICATION CONDITIONS

Temperature: 40°F (4.5°C) minimum, 95°F (35°C) maximum
(air, surface, and material)
At least 5°F (2.8°C) above dew point

APPLICATION EQUIPMENT

Reducer/Clean Up Soap and warm water

Apply Material by Using:

Hand trowel application using a pool trowel or square edge trowel.

Hydraulic spray equipment (i.e. Graco M680 mortar pump or 9.1 WIWA 410 pump) followed by troweling to close the material. No special ACI 308 curing requirements - ambient cure only. Standard concrete finishing trowels, broad knives and rubber floats are recommended. For troweling inside and outside corners, the use of a radius or margin trowel is recommended. Do not overwork material. Trowel marks may be reduced by using a dry sponge to smooth them out.

Reduction 2-6 ounces of potable water based on environmental conditions (Contact Tech Service for additional recommendations)

Brush Not recommended

If specific application equipment is not listed above, equivalent equipment may be substituted.



Protective & Marine Coatings

DURA-PLATE® 2300 (FORMERLY COROBOND 300) WATERBASED EPOXY CEMENTITIOUS RESURFACER

KIT	B58A320	DURA-PLATE 2300 KIT
PART A	2300A	HARDENER
PART B	2300B	CONCRETE GRAY
PART C	2300C	MORTAR

Revised: May 2, 2025

APPLICATION BULLETIN

TRM.68

APPLICATION PROCEDURES

Surface preparation must be completed as indicated.

Mixing Instructions: Shake or agitate both "A" and "B" Component, then pour "A" Component into a container large enough to hold all components. While mixing, slowly add "B" Component. Mix until liquids are uniformly blended. Material shall only be mixed on slow speed utilizing a mechanical mixer blade. Slowly sift "C" Component into the liquid while continuing to mix. Do not dump all of "C" Component into the liquids at one time. Mix for a minimum of two minutes or until a smooth consistency with no dry cement-sand aggregate is obtained.

For repair of large spalls and other surface imperfections deeper than the recommended maximum thickness, multi-purpose clean, dry silica sand (conforming to ASTM C33) or clean, dry pea gravel can be post added.

Important: Do not add additional "C" Component.

Apply paint at the recommended film thickness and spreading rate as indicated below:

Recommended Spreading Rate:

Coverage for 3.1 gallon kit: Approximately 77 ft² (7.2 m²) at 1/16" thickness; 38.5 ft² (3.6 m²) at 1/8" thickness; 19.25 ft² (1.8 m²) at 1/4" thickness; 10 ft² (1.7 m²) at 1/2" thickness

Drying Schedule:

@ 40°F/4.5°C @ 77°F/25°C @ 85°F/29°C

To touch: 6-8 hours 3-4 hours 2-3 hours

Topcoat/Overcoat:

minimum: 12 hours 8 hours 8 hours

maximum: Unlimited Unlimited Unlimited

Drying time is temperature, humidity, and film thickness dependent.

Pot Life: 90 minutes 70 minutes 45 minutes

Sweat-in-Time: None required

Application of coating above maximum or below minimum recommended spreading rate may adversely affect coating performance.

CLEAN UP INSTRUCTIONS

Clean spills and spatters immediately with soap and warm water. Clean tools immediately after use with soap and warm water. Follow manufacturer's safety recommendations when using any solvent.

DISCLAIMER

The information and recommendations set forth in this Product Data Sheet are based upon tests conducted by or on behalf of The Sherwin-Williams Company. Such information and recommendations set forth herein are subject to change and pertain to the product offered at the time of publication. Consult your Sherwin-Williams representative to obtain the most recent Product Data Information and Application Bulletin.

PERFORMANCE TIPS

If Dura-Plate 2300 begins to thicken in a pail during use, do not add more water. Simply reagitrate with a drill to bring back the original smooth consistency.

It is possible to add additional water to Dura-Plate 2300 in measured quantities without affecting performance to accommodate spray application. Up to 6 oz. of clean potable water can be added for low pressure spray application.

Overworking or oversaturating the surface will cause a white liquid to appear on the surface and may have an adverse effect on the adhesion of subsequent coatings. If this is evident, allow Dura-Plate 2300 to cure and remove surface deposits using concrete rub brick/stone or other applicable method.

Do not apply the material beyond recommended pot life.

Do not mix previously catalyzed material with new.

Do not use in conjunction with Vinyl Ester and Polyester coatings or lining systems.

Cured Dura-Plate 2300 is acceptable for use on interior of potable water storage tanks and reservoirs when overcoated with an ANSI / NSF Std. 61 certified Sherwin-Williams coating.

Dura-Plate 2300 shall be applied to concrete surfaces that are in a Saturated Surface Dry (SSD) condition.

Refer to Product Information sheet for additional performance characteristics and properties.

SAFETY PRECAUTIONS

Refer to the SDS sheet before use.

Published technical data and instructions are subject to change without notice. Contact your Sherwin-Williams representative for additional technical data and instructions.

WARRANTY

The Sherwin-Williams Company warrants our products to be free of manufacturing defects in accord with applicable Sherwin-Williams quality control procedures. Liability for products proven defective, if any, is limited to replacement of the defective product or the refund of the purchase price paid for the defective product as determined by Sherwin-Williams. NO OTHER WARRANTY OR GUARANTEE OF ANY KIND IS MADE BY SHERWIN-WILLIAMS, EXPRESSED OR IMPLIED, STATUTORY, BY OPERATION OF LAW OR OTHERWISE, INCLUDING MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE.