



# Protective & Marine Coatings

# QUICK-THANE® URETHANE ACCELERATOR

B65V10

ACCELERATOR

Revised: October 26, 2023

## PRODUCT INFORMATION

5.97

**QUICK-THANE URETHANE ACCELERATOR** is designed for use in select Sherwin-Williams' two component urethanes to accelerate drying times. Use up to the amounts indicated below of Quick-Thane Accelerator to 1 mixed gallon of polyurethane. Add Quick-Thane Accelerator immediately after catalyzing.

Acrolon 218 HS Acrylic Polyurethane				Standard Product	1/8 oz Quick-Thane Accelerator	1/4 oz Quick-Thane Accelerator
	Standard Product	1/8 oz Quick-Thane Accelerator	1/4 oz Quick-Thane Accelerator	@ 77°F (25°C)	@ 77°F (25°C)	@ 77°F (25°C)
Touch	@ 35°F (1.7°C)	@ 40°F (4.5°C)	@ 40°F (4.5°C)	1 hour	20 minutes	10 minutes
Handle	4 hours	4 hours	3.5 hours	6 hours	3.5 hours	2 hours
Recoat	18 hours	16 hours	14 hours	8 hours	3.5 hours	2 hours
Pot Life	4.0 hours	3.5 hours	3 hours	2 hours	1 hour	50 minutes

Acrolon Ultra				Standard Product	1/8 oz Quick-Thane Accelerator	1/4 oz Quick-Thane Accelerator
	Standard Product	1/8 oz Quick-Thane Accelerator	1/4 oz Quick-Thane Accelerator	@ 77°F (25°C)	@ 77°F (25°C)	@ 77°F (25°C)
Touch	@ 40°F (4.5°C)	@ 40°F (4.5°C)	@ 40°F (4.5°C)	2 hours	90 minutes	1 hour
Handle	4 hours	3 hours	2.5 hours	6 hours	4 hours	2 hours
Recoat	12 hours	10 hours	7 hours	6 hours	4 hours	2 hours
Pot Life	12 hours	10 hours	7 hours	6 hours	3 hour	90 minutes

Hi-Solids Polyurethane				1/4 oz Quick-Thane Accelerator	Standard Product	1/4 oz Quick-Thane Accelerator
	Standard Product	1/4 oz Quick-Thane Accelerator	Standard Product	@ 40°F (4.5°C)	@ 77°F (25°C)	@ 77°F (25°C)
Touch	@ 20°F (-7°C)	@ 20°F (-7°C)	@ 40°F (4.5°C)	2 hours	2 hours	30 minutes
Handle	16 hours	3 hours	4 hours	12 hours	8 hours	6 hours
Recoat	14 days	3 days	16 hours	16 hours	18 hours	12 hours
Pot Life	32 hours	24 hours	24 hours	1.5 hours	4 hours	1 hour

Hi-Solids Polyurethane 250				1/4 oz Quick-Thane Accelerator	Standard Product	1/4 oz Quick-Thane Accelerator
	Standard Product	1/4 oz Quick-Thane Accelerator	Standard Product	@ 40°F (4.5°C)	@ 77°F (25°C)	@ 77°F (25°C)
Touch	@ 20°F (-7°C)	@ 20°F (-7°C)	@ 40°F (4.5°C)	2 hours	2 hours	30 minutes
Handle	16 hours	3 hours	4 hours	12 hours	8 hours	6 hours
Recoat	14 days	5 days	16 hours	16 hours	18 hours	12 hours
Pot Life	32 hours	24 hours	24 hours	1.5 hours	4 hours	1 hour

Polylon HP				Standard Product	1/4 oz Quick-Thane Accelerator	1/2 oz Quick-Thane Accelerator
	Standard Product	1/4 oz Quick-Thane Accelerator	1/2 oz Quick-Thane Accelerator	@ 77°F (25°C)	@ 77°F (25°C)	@ 77°F (25°C)
Touch	@ 40°F (4.5°C)	@ 40°F (4.5°C)	@ 40°F (4.5°C)	2 hours	1.5 hours	40 minutes
Handle	18 hours	8 hours	4 hours	5 hours	3 hours	2 hours
Recoat	48 hours	24 hours	12 hours	12 hours	6 hours	2 hours
Pot Life	40 hours	20 hours	12 hours	4 hours	1.5 hours	45 minutes

### Quick-Thane Urethane Accelerator is not recommended in:

Diamond-Clad Clear Coat Urethane  
SherThane 2K Urethane

Sher-Loxane 800

**Packaging:** Quart (0.94L) and Gallon (3.78L)

**Shelf Life:** One year, unopened, Store indoors at 40°F (4.5°C) to 100°F (38°C).

### DISCLAIMER

The information and recommendations set forth in this Product Data Sheet are based upon tests conducted by or on behalf of The Sherwin-Williams Company. Such information and recommendations set forth herein are subject to change and pertain to the product offered at the time of publication. Consult your Sherwin-Williams representative to obtain the most recent Product Data Information and Application Bulletin.

### WARRANTY

The Sherwin-Williams Company warrants our products to be free of manufacturing defects in accord with applicable Sherwin-Williams quality control procedures. Liability for products proven defective, if any, is limited to replacement of the defective product or the refund of the purchase price paid for the defective product as determined by Sherwin-Williams. NO OTHER WARRANTY OR GUARANTEE OF ANY KIND IS MADE BY SHERWIN-WILLIAMS, EXPRESSED OR IMPLIED, STATUTORY, BY OPERATION OF LAW OR OTHERWISE, INCLUDING MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE.