



# Protective & Marine Coatings

# COROTHANE® I KA ACCELERATOR

B65V11

ACCELERATOR

Revised: February 15, 2024

## PRODUCT INFORMATION

5.98

Corothane I KA Accelerator is designed for use in select Sherwin-Williams' Corothane I Moisture Cure Urethanes to enhance drying times. Use up to 4 oz of KA Accelerator to 1 gallon (3.78L) of Corothane I MCU. Add Corothane I KA Accelerator when initially agitating the coating.

	Standard Product @ 40°F (4.5°C) & 50% RH	4 oz KA Accelerator @ 40°F (4.5°C) & 50% RH	Standard Product @ 77°F (25°C) & 50% RH	4 oz KA Accelerator @ 77°F (25°C) & 50% RH
Corothane I Coal Tar - B65B11				
To Touch	4 hours	2 hours	1 hour	30-40 minutes
To Recoat	18 hours	6 hours	4 hours	2 hours
Corothane I GalvaPac - B65G10/B69D210 (2 part) or B65G11 (1 part)				
To Touch	45 minutes	30 minutes	20 minutes	10 minutes
To Recoat	8 hours	2 hours	4 - 6 hours	90 minutes
(do not use for NSF applications)				
Corothane I HS- B65W50				
To Touch	4 hours	4 hours	2 hours	2 hours
To Recoat	24 hours	12 hours	12 hours	6 hours
Corothane I IronOx B - B65A11				
To Touch	2 hours	1 hour	40 minutes	30 minutes
To Recoat	8 hours	2 hours	6 hours	1 hour
Corothane I MIO-Aluminum - B65S14				
To Touch	4 hours	2 hours	2 hours	Not recommended
To Recoat	16 hours	8 hours	7 hours	Not recommended
Corothane I MIO-Zinc Primer - B65A14/B69D210 (2 part)				
To Touch	45 minutes	30 minutes	20 minutes	10 minutes
To Recoat	8 hours	1-1/2 hours	4 - 6 hours	1 hour
Corothane I PrePrime - B65C10				
To Touch	4 hours	2 hours	1 hour	45 minutes
To Recoat	24 hours	12 hours	4 hours	3 hours

**Packaging:** Quart (0.94L) can with 25 oz (0.74L) fill  
**Shelf Life:** 12 months unopened, 12 - 24 hours after opening. Store indoors at 40°F (4.5°C) to 100°F (38°C).

### DISCLAIMER

The information and recommendations set forth in this Product Data Sheet are based upon tests conducted by or on behalf of The Sherwin-Williams Company. Such information and recommendations set forth herein are subject to change and pertain to the product offered at the time of publication. Consult your Sherwin-Williams representative to obtain the most recent Product Data Information and Application Bulletin.

### WARRANTY

The Sherwin-Williams Company warrants our products to be free of manufacturing defects in accord with applicable Sherwin-Williams quality control procedures. Liability for products proven defective, if any, is limited to replacement of the defective product or the refund of the purchase price paid for the defective product as determined by Sherwin-Williams. NO OTHER WARRANTY OR GUARANTEE OF ANY KIND IS MADE BY SHERWIN-WILLIAMS, EXPRESSED OR IMPLIED, STATUTORY, BY OPERATION OF LAW OR OTHERWISE, INCLUDING MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE.