



Protective & Marine Coatings

RESUFLOTM 3552W FLEXIBLE WALL EPOXY

PART A
PART B

GP3552W59
GP3552B01

SERIES
HARDENER

Revised: February 2, 2025

PRODUCT INFORMATION

PRODUCT DESCRIPTION

RESUFLO 3552W Flexible Wall Epoxy is a high solids, flexible epoxy material which combines the toughness, adhesion and durability of epoxies with a degree of flexibility common to polyurethanes. Flexibility is achieved without the use of plasticizers or other additives which can separate or migrate out of the epoxy complex as the material ages. Resuflo 3552W is used as a base coat for Resuwall FX System.

ADVANTAGES

- Impact resistant
- Bridges hairline cracks, aids in suppression of reflective cracking due to substrate movement associated with thermal movement
- Flexible, yet tough
- State of the art chemistry assures long-term flexibility
- Remains flexible at low temperatures
- Acceptable for use in USDA inspected facilities

TYPICAL USES

RESUFLO 3552W Flexible Wall Epoxy is recommended for use as a flexible matrix for wall system installations in pharmaceuticals, kitchens, animal research, health care, laboratories, and food processing facilities.

LIMITATIONS

- Substrate must be structurally sound, dry and free of bond inhibiting contaminants
- During installation and initial cure cycle substrate and ambient air temperature must be at a minimum of 60°F (16°C). Substrate temperature must be at least 5°F (3°C) above the dew point (for lower temperature installation contact your Sherwin-Williams representative).
- When required, adequate ventilation shall be provided and proper clothing and respirators worn
- Extinguish all sources of ignition during the entire installation cycle
- **Strictly adhere to published coverage rates**
- **Strictly adhere to mixing ratio**

SURFACE PREPARATION

Proper inspection and preparation of the substrate to receive resinous material is critical. Read and follow the "Instructions for Concrete Surface Preparation" (Form G-1) for complete details.

PRODUCT CHARACTERISTICS

Color:	Off White
Mix Ratio:	1:1
Volume Solids:	93% ± 2%, mixed
Weight Solids:	95% ± 2%, mixed
VOC (EPA Method 24):	<50 g/L mixed; 0.42 lb/gal
Viscosity, mixed:	9,000 cps

Recommended Spreading Rate per coat:

	Minimum	Maximum
Wet mils (microns):	8 (200)	10 (250)
~Coverage sq ft/gal (m ² /L):	160 (4.1)	200 (5.1)

Drying Schedule @ 6 mils (150 microns) wet:

	@ 73°F (23°C)
To touch:	16-24 hours
To recoat:	24 hours
<i>If maximum recoat time is exceeded, abrade surface before recoating.</i>	
<i>Drying time is temperature, humidity, and film thickness dependent.</i>	
Pot Life:	gallon mass 20-25 minutes @ 73°F (23°C)

Shelf Life:	Part A: 36 months, unopened Part B: 36 months, unopened Store indoors at 50°F (10°C) to 90°F (32°C)
Flash Point:	>222°F (>104°C), ASTM D 93, mixed

PERFORMANCE CHARACTERISTICS

Test Name	Test Method	Results
Adhesion	ACI503R	300 psi concrete failure
Elongation	ASTM D 412	145%
Flammability		Self-extinguishing over concrete
Hardness, Shore D	ASTM D 2240	23
Tensile Strength	ASTM D 412	1,200 psi
Thermal Cycling 24 hrs., -21°C - 25°C	ASTM C 884	No cracking



Protective & Marine Coatings

RESUFLOTM 3552W FLEXIBLE WALL EPOXY

PART A
PART B

GP3552W59
GP3552B01

SERIES
HARDENER

Revised: February 2, 2025

PRODUCT INFORMATION

APPLICATION

APPLICATION INSTRUCTIONS:

1. Premix 3552W (resin) using a low speed drill and Jiffy blade. Mix for one minute and until uniform, exercising caution not to introduce air into the material.
2. Add 1 part 3552W (resin) to 1 part 3552B (hardener) by volume. Mix with low speed drill and Jiffy blade for three minutes and until uniform. To insure proper system cure and performance, strictly follow mix ratio recommendations. Resuflo 3552W is a viscous material and requires complete mixing to cross link properly, match the mix blade to the volume of material to insure a full mix and always mix for a minimum of 3 minutes.
3. Resuflo 3552W may be applied via 3/8" roller taped and solvent washed, or brush. Apply at a spread rate of 160-200 sq. ft. per gallon to yield 8-10 mils WFT evenly with no runs. Coverage will vary depending upon porosity of the substrate and surface texture. Roller application will leave a stipple finish, a final backroll with a short nap (1/4" or 3/16") roller or foam roller will reduce but not eliminate the stipple.
4. Allow to cure overnight.

NOTE: Epoxy materials may tend to blush at the surface especially in humid environments. After surface is primed and before installation of each subsequent coat, surface must be examined for blush (a whitish greasy film and/or low gloss). The blush must be completely removed prior to recoating using warm detergent water or through solvent wipe.

Epoxy materials will appear to be cured and dry to touch prior to full chemical cross linking. Allow epoxy to cure 2-3 days prior to exposure to water or other chemicals for best performance.

ORDERING INFORMATION

Packaging:	
Part A:	1 gallon (3.8L) and 5 gallon (18.9L) containers
Part B:	1 gallon (3.8L) and 5 gallon (18.9L) containers
Weight:	9.4 ± 0.2 lb/gal; 1.13 Kg/L

TINTING

Do not tint.

CLEANUP

Clean up mixing and application equipment immediately after use. Use toluene or xylene. Observe all fire and health precautions when handling or storing solvents.

SAFETY

Refer to the SDS sheet before use.

Published technical data and instructions are subject to change without notice. Contact your Sherwin-Williams representative for additional technical data and instructions.

MAINTENANCE

Occasional inspection of the installed material and spot repair can prolong system life. For specific information, contact your Sherwin-Williams representative.

DISCLAIMER

The information and recommendations set forth in this Product Data Sheet are based upon tests conducted by or on behalf of The Sherwin-Williams Company. Such information and recommendations set forth herein are subject to change and pertain to the product offered at the time of publication. Consult your Sherwin-Williams representative to obtain the most recent Product Data Information and Application Bulletin.

WARRANTY

The Sherwin-Williams Company warrants our products to be free of manufacturing defects in accord with applicable Sherwin-Williams quality control procedures. Liability for products proven defective, if any, is limited to replacement of the defective product or the refund of the purchase price paid for the defective product as determined by Sherwin-Williams. NO OTHER WARRANTY OR GUARANTEE OF ANY KIND IS MADE BY SHERWIN-WILLIAMS, EXPRESSED OR IMPLIED, STATUTORY, BY OPERATION OF LAW OR OTHERWISE, INCLUDING MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE.