



# Protective & Marine Coatings

## RESUFLOOR™ 3556 TERRAZZO MEMBRANE

PART A  
PART B

GP3556  
GP3556B01

SERIES  
HARDENER

Revised: December 17, 2021

### PRODUCT INFORMATION

#### PRODUCT DESCRIPTION

**RESUFLOOR 3556 Terrazzo Membrane** is a high solids, flexible epoxy material which combines the toughness, adhesion and durability of epoxies with a degree of flexibility common to polyurethanes. Flexibility is achieved without the use of plasticizers or other additives which can separate or migrate out of the epoxy complex as the material ages or is degraded due to environmental conditions. Resufloor 3556 may be used with fiberglass mesh in surfaces for larger cracks and joints. It is ideal for crack bridging under epoxy terrazzo due to material compatibility.

#### ADVANTAGES

- Optional reinforcement
- Waterproofing
- Bridges hairline cracks, aids in suppression of reflective cracking of terrazzo applied flooring due to substrate movement associated with thermal movement.
- Flexible, yet tough
- State of the art chemistry assures long-term flexibility
- Acceptable for use in USDA inspected facilities

#### TYPICAL USES

**RESUFLOOR 3556 Terrazzo Membrane** is recommended for use as a flexible membrane under Resufloor Terrazzo TG flooring systems where substrate cracking is anticipated and/or evident.

#### LIMITATIONS

- Slab on grade requires vapor/moisture barrier
- Substrate must be structurally sound, dry and free of bond inhibiting contaminants
- During installation and initial cure cycle substrate and ambient air temperature must be at a minimum of 60°F (16°C). Substrate temperature must be at least 5°F (3°C) above the dew point (for lower temperature installation contact your Sherwin-Williams representative).
- When required, adequate ventilation shall be provided and proper clothing and respirators worn
- **Strictly adhere to published coverage rates**
- **Strictly adhere to mixing ratios**

#### SURFACE PREPARATION

Proper inspection and preparation of the substrate to receive resinous material is critical. Read and follow the "Instructions for Concrete Surface Preparation" (Form G-1) for complete details.

#### PRODUCT CHARACTERISTICS

<b>Color:</b>	Gray
<b>Mix Ratio:</b>	1:1
<b>Volume Solids:</b>	93% ± 2%, mixed
<b>Weight Solids:</b>	95% ± 2%, mixed
<b>VOC (EPA Method 24):</b>	<100 g/L mixed; 0.83 lb/gal
<b>Viscosity, mixed:</b>	2,000 cps

#### Recommended Spreading Rate per coat:

<b>Wet mils (microns):</b>	<b>40</b>	(1,000)
<b>~Coverage sq ft/gal (m<sup>2</sup>/L):</b>	<b>40</b>	(1.0)

#### Drying Schedule @ 6 mils (150 microns) wet:

	@ 73°F (23°C)	
<b>To touch:</b>	16-24 hours	
<b>To recoat:</b>	24 hours	
<i>If maximum recoat time is exceeded, abrade surface before recoating. Drying time is temperature, humidity, and film thickness dependent.</i>		
<b>Pot Life:</b>	gallon mass	35 minutes @ 73°F (23°C)

<b>Shelf Life:</b>	Part A: 36 months, unopened Part B: 36 months, unopened
	Store indoors at 50°F (10°C) to 90°F (32°C)
<b>Flash Point:</b>	222°F (106°C), ASTM D 93, mixed

#### PERFORMANCE CHARACTERISTICS

Test Name	Test Method	Results
<b>Adhesion</b>	ACI 503R	300 psi concrete failure
<b>Elongation@ Break</b>	ASTM D 412	130-145%
<b>Flammability</b>		Self-extinguishing over concrete
<b>Hardness, Shore D</b>	ASTM D 2240	23
<b>Tensile Strength</b>	ASTM D 412	1,000-1,300 psi
<b>Thermal Cycling 24 hrs., -21°C - 25°C</b>	ASTM C 884	No cracking



# Protective & Marine Coatings

## RESUFLO<sup>TM</sup> 3556 TERRAZZO MEMBRANE

PART A  
PART B

GP3556  
GP3556B01

SERIES  
HARDENER

Revised: December 17, 2021

### PRODUCT INFORMATION

#### APPLICATION

##### APPLICATION INSTRUCTIONS:

1. Premix 3556A (resin) using a low speed drill and Jiffy blade. Mix for one minute and until uniform, exercising caution not to introduce air into the material.
2. Add 1 part 3556A (resin) to 1 part 3556B (hardener) by volume. Mix with low speed drill and Jiffy blade for three minutes and until uniform. To insure proper system cure and performance, strictly follow mix ratio recommendations.
3. Immediately pour the mixed material onto the substrate and pull out using a v-notched red rubber squeegee at a spread rate of 40 square feet per gallon to yield 40 mils WFT. Readings must be taken continuously during application with a wet mil gauge to verify material is being applied at the proper thickness. Allow material to cure overnight at 73°F (23°C) surface temperature. Material cures slower at lower temperatures.

**NOTE:** Epoxy materials may tend to blush at the surface especially in humid environments. After surface is primed and before installation of each subsequent coat, surface must be examined for blush (a whitish greasy film and/or low gloss). The blush must be completely removed prior to recoating using warm detergent water or through solvent wipe.

**Note:** Epoxy materials will appear to be cured and “dry to touch” prior to full chemical cross linking. Allow epoxy to cure 2-3 days prior to exposure to water or other chemicals for best performance.

#### ORDERING INFORMATION

Packaging:	
Part A:	1 gallon (3.8L) and 5 gallon (18.9L) containers
Part B:	1 gallon (3.8L) and 5 gallon (18.9L) containers
Weight:	8.68 ± 0.2 lb/gal; 1.04 Kg/L

#### TINTING

Do not tint.

#### CLEANUP

Clean up mixing and application equipment immediately after use. Use toluene or xylene. Observe all fire and health precautions when handling or storing solvents.

#### SAFETY

Refer to the SDS sheet before use.

Published technical data and instructions are subject to change without notice. Contact your Sherwin-Williams representative for additional technical data and instructions.

#### MAINTENANCE

Occasional inspection of the installed material and spot repair can prolong system life. For specific information, contact your Sherwin-Williams representative.

#### DISCLAIMER

The information and recommendations set forth in this Product Data Sheet are based upon tests conducted by or on behalf of The Sherwin-Williams Company. Such information and recommendations set forth herein are subject to change and pertain to the product offered at the time of publication. Consult your Sherwin-Williams representative to obtain the most recent Product Data Information and Application Bulletin.

#### WARRANTY

The Sherwin-Williams Company warrants our products to be free of manufacturing defects in accord with applicable Sherwin-Williams quality control procedures. Liability for products proven defective, if any, is limited to replacement of the defective product or the refund of the purchase price paid for the defective product as determined by Sherwin-Williams. NO OTHER WARRANTY OR GUARANTEE OF ANY KIND IS MADE BY SHERWIN-WILLIAMS, EXPRESSED OR IMPLIED, STATUTORY, BY OPERATION OF LAW OR OTHERWISE, INCLUDING MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE.