



FIBERED ASPHALT EMULSION DAMPPROOFING-TROWEL GRADE 40-332 BLACK

PRODUCT DESCRIPTION

Uniflex® Fibered Asphalt Emulsion Dampproofing-Trowel Grade is a single component, trowel-grade, cold-applied, water-based asphalt emulsion that is ideal for reducing dampness on above grade or below grade exterior walls and foundations. It is reinforced with fibers for sag resistance under extreme weather conditions on vertical applications. Meets ASTM D1227, Type II, Class I

GENERAL USES

For use on above and below grade on damp or uncured surfaces. Excellent for bonding polystyrene insulation board to a variety of substrates.

PACKAGING INFORMATION

| SKU | SIZE |
|--------------|----------------------|
| KST040332-20 | 5-gallon pail, black |

APPLICATION CONDITIONS

FOR EXTERIOR USE ONLY. Surface must be free of oil, grease, laitance and loose material. Dry surfaces must be dampened with water and kept damp until application.

Do not apply below 50 °F (10 °C) or when rain is forecast.

APPLICATION PROCEDURES

Mixing Instructions: Mix coating thoroughly. DO NOT THIN

Application Rate: Apply at 4 gallons per 100 sq ft over the entire surface with a trowel. For added protection, apply a second coat at the same rate as soon as the first coat is thoroughly dry (24-48 hours). Fill in all crevices and grooves during application., making sure material is free from breaks and pinholes. Coating will become waterproof only after drying thoroughly.

For Below Grade Surfaces: Apply at 1/16" in thickness when coating dense concrete surfaces not subject to hydrostatic pressure. Carry coating over exposure top and outside of edge of footing.

For Below Grade Foundations: Allow at least 24-48 hours for air circulation, before exposure to water or backfilling. Backfill within 7 days.

KEEP FROM FREEZING.

PRODUCT CHARACTERISTICS

| | |
|--|-------------|
| Color | Black |
| Vehicle Base | Asphalt |
| Weight Per Gallon | 8.73 lbs |
| Solids Per Weight | 50 ± 2% |
| Solids Per Volume | 45 ± 2% |
| Dry Time | |
| Full cure in warm, dry weather | 8-12 hours |
| Full cure in cold, damp weather | 2-7 days |
| Between coats | 24-48 hours |
| <i>Drying Time is temperature, humidity and film thickness dependent</i> | |
| VOC | < 50 g/L |

CLEANING

Clean wet coating with soap and water. Clean dry coating with mineral spirits.

DISCLAIMER

The information and recommendations set forth in this Product Data Sheet are based upon tests conducted by or on behalf of KST Coatings- A Business Unit of the Sherwin-Williams Company. Such information and recommendations set forth herein are subject to change and pertain to the product offered at the time of the publication. Consult your Uniflex Technical Representative to obtain the most recent Product Data Information.

WARRANTY

This product is manufactured in accordance to ISO 9001-2008 standards. Seller and manufacturer's only obligation shall be to replace such quantity of product proved to be defective. Neither seller nor manufacturer shall be liable for any injury, loss or damage, direct or consequential arising from the use or the inability to use the product for his/her intended use, and user assumes all risk and liability. Color fade is not covered under warranty.

If further information is needed, contact Uniflex Technical Service at
1-888-321-3539



101 Prospect Ave. NW
Cleveland, Ohio 44115
1-888-321-3539 • uniflexroof.com

Rev. 05/2017