



FIRETEX® FX6002 REPAIR KIT

ULTRA FAST DRYING INTUMESCENT

Revised 12/2024 Issue 5

PRODUCT DESCRIPTION

Ultra fast-drying and durable intumescent coating.

RECOMMENDED USE

For repair of small areas of mechanical damage to FIRETEX FX6002 intumescent coating.

PRODUCT TECHNICAL DATA

Volume Solids:	92% ± 3% (ISO 3233)
VOC:	24 g/l calculated from solids by volume determination.
Colours:	Light grey
Flash Point:	10°C
Cleaner/Thinner:	No. 9 or E+B (Cleaning only) FX6002 Repair Kit Must not be thinned.
Pack Size:	A multi component material supplied in separate containers to be mixed prior to use: 2 litre (2.9kg) units when mixed Weight will vary with colours and density.
Density:	1.460 kg/l (may vary with colours).
Mixing Ratio:	0.029 kg (0.024 litre) of catalyst to be added to 1.976 litre (2,885 kg) of FX6002 RK. 1% Catalyst (by weight) to be added and mixed in by hand prior to use. (Correct amount will be supplied by manufacturer)
Shelf Life:	9 months from date of manufacture, stored in originally sealed containers in a cool and dry environment. "Use By" date where specified. Both transportation and long term storage of the product must be in a covered environment, out of direct sunlight and in the temperature range 5° to 30°C.

Recommended Application Methods:

Knife, Trowel or Brush

Typical Thickness:

Recommended Spreading Rate Per Coat

	Typical
Dry	400 µm
Wet	435 µm
Theoretical Consumption*	0.635 kg/m ² 0.435 l/m ²
Theoretical Coverage*	1.58 m ² /kg 2.30 m ² /l

*A minimum dry film thickness of 400 microns MUST be achieved. At film thicknesses below this figure retarded curing will be evident..

Pot Life:

20°C
25 minutes

Pot Life is dependant on temperature and volume

AVERAGE DRYING TIMES

	+ 10°C	+ 15°C	+ 23°C
Dry to touch	2 hours	1 hours	45 minutes
Dry to handle	3 hours	2 hours	1 hour
To Recoat	2½ hours	1½ hours	1 hours

These figures are given as a guide only.
Factors such as air movement and humidity must also be considered.

SURFACE PREPARATION

Scrape back all loose or damaged FIRETEX intumescent coatings to a firm edge. Where necessary spot prime with an approved primer, refer to Sherwin-Williams for further details

Apply FIRETEX FX6002 REPAIR KIT to level any surface defects, on larger areas two or more applications may be necessary..

Ensure surfaces to be coated are clean, dry and free from all surface contamination.

APPLICATION CONDITIONS

FIRETEX FX6002 REPAIR KIT should preferably be applied at temperatures in excess of 5°C.

In conditions of high relative humidity, ie 80-85% good ventilation conditions are essential. Substrate temperature shall be at least 3°C above the dew point and always above 0°C.

Application at ambient air temperatures below 5°C is not recommended.

RECOMMENDED SYSTEMS

Primer

Several primers have been fire tested and approved for use under FIRETEX FX6002 REPAIR KIT.

Please consult Sherwin-Williams for detailed information.

Topcoats

Several topcoats have been fire tested and approved for use over FIRETEX FX6002 REPAIR KIT.

Please consult Sherwin-Williams for detailed information

ADDITIONAL NOTES

Numerical values quoted for physical data may vary slightly from batch to batch.



Protective & Marine Coatings
PRODUCT DATA SHEET

FIRETEX® FX6002 REPAIR KIT

ULTRA FAST DRYING INTUMESCENT

Revised 12/2024 Issue 5

HEALTH & SAFETY

Consult Product Health and Safety Data Sheet for information on safe storage, handling and application of this product.

WARRANTY

Whilst all statements made about our products (whether in this data sheet or otherwise) are correct and accurate to the best of our knowledge, we have no control over the quality or the condition of the substrate, the application conditions or the many other factors affecting your use and application of our product.

The appropriateness of the product under the actual conditions of application or intended use must be determined exclusively by you. The content of this document, and of any oral or written statements already made or to be made in relation to the subject matter of this document, including any suggestions as to appropriate products and any proposed application methods, technical details and other product information represent only test results or experience obtained under controlled or defined circumstances, and is therefore provided for general information purposes only.

Unless we agree specifically in writing to do so, we will not be liable to you for any loss or damage whether in contract, tort (including negligence), breach of statutory duty, misrepresentation, misstatement or otherwise, arising under or in connection with this document or such statements.

We disclaim any express or implied representations, warranties or guarantees (including any implied warranty of merchantability or fitness for a particular purpose), though nothing in this disclaimer excludes or limits our liability for death or personal injury arising from our negligence, or our fraud or fraudulent misrepresentation, or any other liability that cannot be excluded or limited by law.

All products supplied and technical advice given are subject to our Standard Terms and Conditions of Sale which you should request a copy of and review carefully.

This document may be modified and updated from time to time, and is uncontrolled once printed. It is the users responsibility to ensure they are using the most up to date version – this can be found at: www.sherwin-williams.com/protectiveEMEA.

If this datasheet has been translated, then it has been done using the English version as the source. In case of any queries, please refer to the master English version which can be found at: www.sherwin-williams.com/protectiveEMEA.



Protective & Marine Coatings
PRODUCT DATA SHEET

FIRETEX® FX6002 REPAIR KIT

ULTRA FAST DRYING INTUMESCENT

Revised 12/2024 Issue 5