



Resupen WB

Revised 04/2018—Issue 1 : REF : PEWB 2016 11

DESCRIPTION

Resupen WB is a coloured UV stable polyurethane finish for application onto concrete, plaster and wood or as a seal coat on Sherwin-Williams wall and flooring systems. Grades available:

- Resupen WB (Coloured) - Satin finish
- Resupen WB Matt (Coloured) - Matt finish

(See separate datasheet for Resupen WB Clear products)

ADVANTAGES

- Good chemical resistance
- UV stable
- Good abrasion and impact resistance
- Hygienic and easy to clean
- No VOC's
- Resistant to hot water

RECOMMENDED USES

- As a seal coat for other Sherwin-Williams floor coatings and screeds
- Laboratories
- Food factory units
- Prisons and police cells
- Pharmaceutical areas
- Medical and healthcare
- Can be used on floors and walls

PRODUCT INFORMATION

System Thickness (Recommended)	100-150 microns WFT 40-60 microns DFT *The suggested thickness range is calculated based on average volume solid as a general recommendation for the specified condition and for each application it may vary.
Solids Content by Weight	53% It may vary slightly for different colours
Solids Content by Volume	40% It may vary slightly for different colours
Pack Sizes	5 litres
Pack Make Up	1 x Base 1 x Hardener
Shelf Life	12 months (Base & Hardener)
Storage	Keep out of direct sunlight. Store in a dry place, between 15°C- 30°C.

APPLICATION INFORMATION at 20°C

Coverage Rate (Theoretical)	5 litres will cover 50m ² @ 100 microns wet film thickness. * Coverage rate is calculated based on a sealed and smooth surface and may vary based on the substrate roughness and other conditions.
Pot Life	Up to 60 minutes * water based coatings may stay liquid for longer than specified pot life but it is recommended to use all mixed paint within the pot life time frame. Application after pot life may affect the cure properties such as gloss and adhesion.
Recoating Intervals	6-8 hours
Light Traffic	12-16 hours
Full Traffic	48 hours
Full Chemical Cure	7 days



BRITISH COATINGS FEDERATION



Specification

Product : Resupen WB

Finish : Satin or Matt

Recommended thickness range : 100-150 µm WFT per coat

Colour : Available in a range of colours, please consult Sherwin-Williams

Products required for this system

Primer : Resuseal WB Clear or R.S. Dampshield on damp substrates where required

System : 1 or 2 Coats of Resupen WB (Multiple coats will be required to achieve full coverage on low opacity colours such as bright yellows and reds)

Preparation

New Concrete Floors: New concrete must be clean, sound, dry and fully cured and surface laitance removed by vacuum enclosed shot blasting or mechanical grinding, a minimum strength of 25N/mm² is required.

Timber Floors : Must be clean, sound, dry . Old clear varnish/topcoat must be removed/sanded prior to application, as it may affect the inter-coat adhesion with **Resupen WB**.

Existing Concrete Floors: Remove all dirt, oil, grease, old paints or any other surface contaminants by vacuum enclosed shot blasting, scarifying or mechanical grinding. Fats, oils or greases must be removed by mechanical means and detergent washing. Local repairs should be carried out using **Resupatch** or **Resuscreed 45**.

Existing Floors (previously coated)

All previous coatings and loose floor paints must be removed by mechanical preparation as described in the above section and primed as specified. If the old resin flooring cannot be removed, then please consult with our technical team for advice on intercoat adhesion and suitability, as it may not be compatible with existing floor coating.

Where **Resupen WB** is applied to masonry/concrete surfaces, care must be taken to ensure that surface preparation is thorough but does not disfigure the surface.

Where surfaces are found to be porous a primer coat may be required to achieve a uniform sealed surface.

Priming

Resupen WB may be applied direct to concrete or as a seal coat or top coat to a resin floor system specified in our datasheets where a primer is not required. When applied direct to porous substrates the surface may require priming. Dry surfaces may be primed with **Resuseal WB Clear** or **Resuprime NT**.

Where the Relative Humidity of the substrate exceeds 75% **R.S. Dampshield** should be specified and selected on the basis of hygrometer readings in accordance with BS 8203. The number of coats to be applied is chosen in accordance with the following table.

ERH%	Required Coating Thickness
75-85	1 coat of R.S.DAMPSHIELD at 200 microns per coat
85-92	2coats of R.S.DAMPSHIELD at 200 microns per coat
92-97	3coats of R.S.DAMPSHIELD at 200 microns per coat

Application

The ambient temperatures of the area should not be allowed to fall below 10°C throughout application and curing. Surface temperature must be above 5°C.

Mixing: Pre-mix the base component to a uniform consistency then add the entire contents of the hardener to the base and mix by using a slow speed hand held powered mixer and mixing paddle for approximately two to three minutes to achieve consistent mixture. Note: Do not use a separate mixing bucket as it may affect the mixing ratio.

Apply the whole mixed paint by using spreading rake, roller and brush to achieve the maximum coverage within the specified pot life time frame.

Do not add solvent to this product.

Slip resistance can be improved by lightly broadcasting anti slip aggregates on the first coat (after primer) whilst still wet and back rolling, at a rate of 50/100 g/m². When cured apply the second **Resupen WB** coat to secure the aggregates. Alternatively one pack of **R.S. Beadgrip** can be added to each pack of **Resupen WB** to achieve a fine non-slip texture.

Category Guide

FeRFA Category : 1 and 2

Technical Information

The following figures are obtained from laboratory tests and our experience with this product .

Slip Resistance Dry > 60

Method BS7976 pt1-3 2002

Wet (Please consult Sherwin-Williams)

The slip resistance of a floor surface can vary as a result of the installation process, conditions at the time of application and subsequent traffic. Inappropriate cleaning or maintenance can adversely affect the performance. For further advice on potential wet areas please consult Sherwin-Williams

Abrasion Resistance

N/A

Method BS8204 /ASTM D4060

Temperature Resistance

Tolerant of sustained temperatures of up to 60°C

Chemical Resistance

Good chemical Resistance
Consult Sherwin-Williams on specific materials

VOC

<10 g/l calculated per full mixed unit

Life Expectancy

Up to 2 years depending on applied thickness and subject to traffic according to FeRFA classification. Sherwin-Williams terms and conditions will apply.

Maintenance and Cleaning

Sherwin-Williams recommend that **Resupen WB** should be cleaned with a regular industrial cleaning regime after specified full chemical cure time frame with a floor scrubber utilising **R.S. Industrial Floor Cleaner** or similar with dirty water being removed. Isolated localised cleaning can be carried out using **R.S. Tyre Mark Remover**, **R.S. Fats, Oils & Grease Remover** and **R.S. Oil Remover**. All surfaces should be thoroughly rinsed with clean water after the use of chemical cleaners.

Do not splash, clean, wash or treat the resin flooring with water or any other chemicals until full cure achieved, as it may affect the surface quality and performance.

Please refer to the Sherwin-Williams Guide to Cleaning of Resin Floors

Health and Safety

Resupen WB is formulated from materials designed to achieve the highest level of performance as safely as possible. However, specific components require proper handling and suitable equipment, this information is given in the relevant safety data sheets. In all cases, spillages or skin contamination should be cleaned as soon as practically possible, by dry wiping of the affected area, and thorough washing with soap and water.

The information given in this data sheet is derived from tests and experience with the products and is believed to be reliable. The information is offered without guarantee to enable purchasers to determine for themselves the suitability of the product for their particular application. Any specification or advice given by Sherwin-Williams or its agents is based on the information supplied by the purchaser. Sherwin-Williams cannot be held accountable for errors or omissions as a result of that information being incorrect or incomplete. No undertakings can be given against infringement of patents. Some materials are derived from natural sources. As such some variation may occur. Site conditions may also contribute to variation in finish and colour.

Sherwin-Williams Protective & Marine
Tower Works, Kestor Street, Bolton, BL2 2AL, United Kingdom
Tel : + 44 (0) 1204 521771 F: + 44 (0) 1204 382115
W : Sherwin-williams.com/protectiveEMEAI
Registered in England : Reg. No. 893081
Reg. Office Tower Works, Kestor Street, Bolton BL2 2AL England