



**PROTECTIVE
&
MARINE
COATINGS**

Resuprime MVT LT
PRODUCT TECHNICAL DATA
(Formerly known as Resuprime PP)

PRODUCT DESCRIPTION

Resuprime MVT LT is a fast curing, moisture tolerant two-component epoxy primer/membrane, which can be applied on cold and damp concrete floors. This enables earlier access onto new concrete substrates for the application of screeds, coatings and other floor coverings including carpets, tiles, vinyl and wood. Resuprime MVT LT is also used for existing concrete slabs where there is no damp proof membrane or where a degree of moisture tolerance is required for a resin floor system being installed.

ADVANTAGES

- Ease of application
- Damp and moisture tolerant
- Fast cure even at low temperatures down to 5°C
- Low odour
- Excellent adhesion
- Solvent free

RECOMMENDED USE

- “Green” concrete
- Concrete substrates with no DPM
- Fast return to service at normal temperatures
- Polymer screeds
- Cementitious underlayments
- Low temperature applications

PRODUCT DATA

Volume Solids:	~100%
VOC:	<15 g/l calculated per full mixed unit
Colours:	Clear
Finish:	Smooth gloss
Flash Point:	N/A
Cleanser/Thinner:	N/A
Pack Size:	5 kg and 15 kg
Pack Weights:	2.99 kg base/2.01 kg hardener (5 kg) 8.97 kg base/6.03 kg hardener (15 kg)
Mixing Ratio:	3 parts base to 2 part hardener by weight only
Mixed Density:	Approximately 1.08 g/cm ³
Shelf Life:	36 months (Base) 12 months (Hardener)
Storage:	Keep out of direct sunlight. Store in a dry place, between 15°C – 30°C
Recommended Application Methods:	Brush, roller or squeegee

Application:	5°C @	10°C @	20°C @
	50% RH	50% RH	50% RH
Recoat Intervals	8-12 hrs*	6-9 hrs*	2-5 hrs*
Light Traffic	12-16 hrs	10-12 hrs	6-10 hrs
Full Traffic	24-36 hrs	20-24 hrs	16-20 hrs
Full Chemical Cure	10-12 days	7-10 days	7 days

* or once surface has lost tackiness

Pot Life: 15 – 20 minutes from mixing, based on 5 kg pack size

The pot life may be shorter for larger pack sizes if the paint is not used within the pot life limit.

Note: All mixed paint must be used within the pot life time limit, if the paint is left in the container after mixing and not used, it may release hazardous fumes due to exothermic reaction.

Coverage Rate: 5 kg will cover 25 m² @ 200 µm WFT (Theoretical)

Coverage rate is calculated based on a sealed and smooth surface and may vary based on the substrate roughness and other conditions.

System Thickness: 200 – 250 µm (Recommended)

The suggested thickness range is calculated based on average volume solid as a general recommendation for the specified condition and for each application may vary.



Resuprime MVT LT

SURFACE PREPARATION

New Concrete Floors: New concrete must be clean, sound, dry, fully cured and surface laitance removed by vacuum enclosed shot blasting or mechanical grinding, a minimum strength of 25 N/mm² is required.

Existing Concrete Floors: Remove all dirt, oil, grease, old paint or any other surface contaminants by vacuum enclosed shot blasting, scarifying or mechanical grinding. Fats, oils or greases must be removed by mechanical means and detergent washing and making sure all residue of detergent is washed and removed by rinsing with clean water. Local repairs should be carried out using **Resuscreed PA**.

Existing Floors (previously coated): All previous coatings and loose floor paints must be removed by mechanical preparation as described in the above section and primed as specified. If the old resin flooring cannot be removed then please consult with our technical team for advice on intercoat adhesion and suitability, as it may not be compatible with the existing floor coating. Where **Resuscreed PA** is applied to masonry/concrete surfaces, care must be taken to ensure that surface preparation is thorough but does not disfigure the surface.

APPLICATION	APPLICATION CONDITIONS								
<p>Mixing: Mix the entire contents of the base with the hardener. If a separate mixing bucket is being used mix thoroughly ensuring all contents of both components are removed from the buckets supplied. Mix using a slow speed electric mixer for approximately two to three minutes until the two components are fully combined.</p> <p>The mixed unit should be applied immediately by roller, brush or squeegee with a consistent procedure. Floor areas should be cross-rolled to ensure even application and to minimise roller marks.</p>	<p>The ambient temperatures of the areas should not be allowed to fall below 15°C throughout the application and the curing period, as this could have an adverse effect on the appearance and colour of the system. Surface temperature must be above 10°C. Where possible it is recommended that the application area is heated to a minimum temperature of 15°C ideally to allow the ambient and substrate temperature to stabilise prior to the installation.</p>								
RECOMMENDED SYSTEMS	TECHNICAL INFORMATION								
<p>See Sherwin-Williams System Sheets for recommended floor systems.</p> <p>Where the Relative Humidity of a substrate exceeds 85% ERH Resuprime MVT LT should be specified and selected on the basis of hygrometer readings in accordance with BS 8203:2017. The number of coats to be applied is chosen in accordance with the following table:</p> <table border="1" data-bbox="116 1301 767 1413"> <thead> <tr> <th>ERH%</th> <th>Required Coating Thickness</th> </tr> </thead> <tbody> <tr> <td>75-85</td> <td>1 coat of Resuprime MVT LT at 200 µm per coat</td> </tr> <tr> <td>85-92</td> <td>2 coats of Resuprime MVT LT at 200 µm per coat</td> </tr> <tr> <td>92-97</td> <td>3 coats of Resuprime MVT LT at 200 µm per coat</td> </tr> </tbody> </table> <p><i>For further information please refer to recommended individual product data sheets.</i></p>	ERH%	Required Coating Thickness	75-85	1 coat of Resuprime MVT LT at 200 µm per coat	85-92	2 coats of Resuprime MVT LT at 200 µm per coat	92-97	3 coats of Resuprime MVT LT at 200 µm per coat	<p>Technical Information:</p> <p>The following figures are obtained from laboratory tests and our experience with this product.</p> <p>Category Guide: FerFA Category 2</p> <p>Bond Strength: >3 N/mm² (Substrate failure)</p> <p>Temperature Resistance: Tolerant of temperatures up to 60°C</p>
ERH%	Required Coating Thickness								
75-85	1 coat of Resuprime MVT LT at 200 µm per coat								
85-92	2 coats of Resuprime MVT LT at 200 µm per coat								
92-97	3 coats of Resuprime MVT LT at 200 µm per coat								
WARRANTY	DISCLAIMER								
<p><i>Any person or company using the product without first making further enquiries as to the suitability of the product for the intended purpose does so at their own risk, and Sherwin-Williams can accept no liability for the performance of the product, or for any loss or damage arising out of such use.</i></p> <p><i>The information detailed in this datasheet is liable to modification from time to time in the light of experience and normal product development, and before using, customers are advised to check with Sherwin-Williams, quoting the reference number, to ensure that they possess the latest issue.</i></p>	<p><i>The information and recommendations set forth in this Product Data Sheet are based upon tests conducted by or on behalf of The Sherwin-Williams Company. Such information and recommendations set forth herein are subject to change and pertain to the product offered at the time of publication. Consult your Sherwin-Williams representative to obtain the most recent Product Data Information and Application Bulletin.</i></p>								
HEALTH AND SAFETY									
<p>Consult Product Health and Safety Datasheet for information on safe storage, handling and application of this product.</p>									

www.sherwin-williams.com/protectiveEMEA

This datasheet is specifically subject to the disclaimer which can be found at: <http://protectiveemea.sherwin-williams.com/Home/Disclaimer>