



Resuthane RS69

Revised 08/2019—Issue 4 : REF : RS69 2016

DESCRIPTION

Resuthane™ RS69 is a water-based polyurethane resin screed designed to provide excellent heavy duty usage with resistance to thermal shock, abrasion and chemical attack in many aggressive environments. RS69 is designed to be applied by use of rake and trowel methods of application. Resuthane™ surfaces are stable to steam cleaning and resistant to boiling water and process liquids up to 120°C when applied at 9mm nominal thickness. A matt, textured surface is provided that is both seamless and possesses good anti-slip properties.

ADVANTAGES

- High chemical resistance
- Resistance to hot water & steam
- Self sealing
- Excellent slip resistant finish
- Matt finish
- Extremely hard wearing

RECOMMENDED USES

- Food manufacture & processing
- Brewing & beverage
- Dairies
- Commercial Kitchens
- Pharmaceutical & chemical plant processing
- Abattoirs and meat processing facilities
- Heavy duty plant and traffic areas

PRODUCT INFORMATION

System Thickness (Recommended)	6mm to 9mm
Solids Content	100% solids by weight
Pack Sizes	26 kg
Pack Make Up	1 x Base 1 x Hardener 1 x Aggregate
Shelf Life	36 months (Base) 12 months (Hardener) 6 months (Aggregate)
Storage	Keep out of direct sunlight. Store in a dry place, between 15°C and 30°C. Aggregates must be stored in a dry area to prevent contamination from moisture, as this will have a detrimental effect on the product.

APPLICATION INFORMATION at 20°C

Coverage Rate (Theoretical)	26 kg will cover 2.00 sq m @ 6mm or 1.35 sq m @ 9mm <small>* Coverage rate is calculated based on a sealed and smooth surface and may vary based on the substrate roughness and other conditions.</small>
Pot Life	15 minutes
Recoating Intervals	N/A
Light Traffic	12 - 16 hours
Full Traffic	48 hours
Full Chemical Cure	5 - 7 days



Specification

Product : Resuthane RS69

Finish : Textured, Matt

Recommended thickness range : 6mm to 9mm

Colour : Limited colour range, consult Sherwin-Williams

Products required for this system

Primer : Resuprime ST, Resuprime MVT

System : Resuthane RS69 at required Thickness

Surface Seal : Not required

Preparation

New Concrete Floors: New concrete must be clean, sound, dry, fully cured and surface laitance removed by vacuum enclosed shot blasting or mechanical grinding, a minimum strength of 25N/mm² is required.

Existing Concrete Floors: Remove all dirt, oil, grease, old paint or any other surface contaminants by vacuum enclosed shot blasting, scarifying or mechanical grinding. Fats, oils or greases must be removed by mechanical means and detergent washing and make sure all residue of detergent is washed and removed by rinsing with clean water.

Existing Floors (previously coated)

All previous coatings and loose floor paints must be removed by mechanical preparation as described in the above section and primed as specified. If the old resin flooring cannot be removed, then please consult with our technical team for advice on intercoat adhesion and suitability, as it may not be compatible with existing floor coating.

To ensure the maximum bond is achieved, grooves must be cut into the perimeter of the subfloor, typically 20mm deep by 10mm wide. These should be inset approximately 150mm from, and running parallel with the walls and adjacent to any doorways, plinths etc. including any finished edge, i.e. both sides of a day work joint. The groove must have a neat square edge and the **Resuthane RS69** laid to the full depth forming a perimeter anchorage.

Priming

Open and porous substrates will require priming with **Resuprime ST** on dry substrates only with less than 75% ERH reading. Where the Relative Humidity of a substrate exceeds 75% ERH **Resuprime MVT** should be specified and selected on the basis of hygrometer readings in accordance with BS 8203.

The number of coats to be applied is chosen in accordance with the following table.

ERH% Required Coating Thickness

75-85 1 coat of Resuprime MVT at 200 microns per coat

85-92 2 coats of Resuprime MVT at 200 microns per coat

92-97 3 coats of Resuprime MVT at 200 microns per coat

For further information please refer to individual product data sheets.

Application

Resuthane™ RS69 may be applied to substrates with a surface temperature in the range of 5-20°C and a relative humidity < 90% RH, with a minimum air temperature of 8°C and no condensation. Do not pre-warm this product as working times will be substantially reduced if materials are warm.

When the primed surface is tack free **Resuthane™ RS69** should be applied at the required rate as soon after mixing as possible. (Delay can result in variation in surface finish, colour and add to application problems).

NB: Cure times are extended at low temperatures.

Mix the coloured base component to an even consistency, ensuring the re-dispersion of any settled pigment, Thoroughly scrape the contents of the base and hardener components into the same container and mix thoroughly for one minute. Pour the combined base and hardener into a rotary drum mixer and add the aggregate component steadily, until a homogeneous mix of the three components is achieved. Apply to pre-primed areas and level between battens as necessary with a steel float, alternatively a sledge can be used set at the required thickness and again finished with a steel float. Where ease of cleaning is very important alongside slip resistance the final finish can be smoothed by back rolling with a short nap roller. A single pass with the weight of the roller is usually sufficient.

Resuthane units should be applied consistently with mixes from the same batch used consecutively where adjacent areas are being laid.

Category Guide

FerFA Category : 8

Technical Information

The following figures are obtained from laboratory tests and our experience with this product.

Slip Resistance Dry > 50 (low slip potential)

Method BS7976 pt1-3 2002

Wet (Please consult Sherwin-Williams)

The slip resistance of a floor surface can vary as a result of the installation process, conditions at the time of application and subsequent traffic. Inappropriate cleaning or maintenance can adversely affect the performance. For further advice on potential wet areas please consult Sherwin-Williams

Abrasion Resistance AR 0.5

Method BS EN 13892-4

(Less than 50µ wear)

Temperature Resistance From -25°C to 100°C at 6mm thickness
From -40°C to 120°C at 9mm thickness

Chemical Resistance Excellent chemical Resistance
Consult Sherwin-Williams on specific materials

VOC 9 g/l calculated per full mixed unit



Sherwin Williams Protective & Marine
Tower Works, Kestor Street, Bolton, BL2 2AL, United Kingdom
Tel: +44 (0) 1204 521771 F: +44 (0) 1204 382115

13

BSEN 13813 SR B 3.2- AR 0.5 - IR>4

Resin coating/screed for use inside buildings as per data sheet

Wear resistance: AR 0.5

Bond strength: B 3.2

Impact resistance: IR > 4

Maintenance and Cleaning

Sherwin-Williams recommend that **Resuthane RS69** should be cleaned with a regular industrial cleaning regime with a floor scrubber utilising **R.S. Industrial Floor Cleaner** or similar with dirty water being removed. Isolated localised cleaning can be carried out using **R.S. Tyre Mark Remover, Degreaser W500 & R.S. Oil Remover**. All surfaces should be thoroughly rinsed with clean water after the use of chemical cleaners.

Please refer to the Sherwin-Williams Guide to Cleaning of Resin Floors

Health and Safety

Resuthane RS69 is formulated from materials designed to achieve the highest level of performance as safely as possible. However, specific components require proper handling and suitable equipment, this information is given in the relevant safety data sheets. In all cases, spillages or skin contamination should be cleaned as soon as practically possible, by dry wiping of the affected area, and thorough washing with soap and water.

The information given in this data sheet is derived from tests and experience with the products and is believed to be reliable. The information is offered without guarantee to enable purchasers to determine for themselves the suitability of the product for their particular application. Any specification or advice given by Sherwin-Williams or its agents is based on the information supplied by the purchaser. Sherwin-Williams cannot be held accountable for errors or omissions as a result of that information being incorrect or incomplete. No undertakings can be given against infringement of patents. Some materials are derived from natural sources. As such some variation may occur. Site conditions may also contribute to variation in finish and colour.

Sherwin-Williams Protective & Marine
Tower Works, Kestor Street, Bolton, BL2 2AL, United Kingdom
Tel : + 44 (0) 1204 521771 F: + 44 (0) 1204 382115
W : Sherwin-williams.com/protectiveEMEAL
Registered in England : Reg. No. 893081
Reg. Office Tower Works, Kestor Street, Bolton BL2 2AL England