

SEAVOYAGE 1200 ANITIFOULING COATING

Revised 07/2020 Issue 1

PRODUCT INFORMATION

PRODUCT DESCRIPTION

Seavoyage 1200 is a tin-free antifouling coating with polishing action in service and long protection against marine organisms. The specific vehicle composition provides long lasting antifouling performance and polishing action.

Recommended Use

Antifouling paint for coastal steel underwater hull. This product is for professional use only.

ENDORSEMENTS

IMO Anti-fouling Systems Convention compliant (AFS/CONF/26). HSE Approval 10479 Irish Biocidal Approval PCS 99271/2/3/4

RECOMMENDED APPLICATION METHODS

Airless Spray Brush* Roller*

*In case of brush or roller application, more layers will be required to achieve the specified film thickness. Below 10°C, additional thinning may be required to obtain the proper application viscosity.

Excessive thinning results in reduced sag resistance and paint film property.

Recommended Thinner:

No.2

PRODUCT CHARACTERISTICS

Flash Point: 37°C

% Solids by Volume: 61± 2%

Colour Availability: Brown, Light brown, Black, Blue

VOC (Theoretical): 346 g/l

TYPICAL THICKNESS

| Dry film thickness μm | | | film ess µm | Theoretical coverage | |
|--------------------------|-----|-----|----------------|----------------------|-----|
| | | | | m²/ltr* | |
| Min | Max | Min | Max | Min | Max |
| 75 | 150 | 123 | 246 | 8.1 | 4.1 |
| * This figure | | | | - f ile | |

* This figure makes no allowance for surface profile, uneven application, overspray or losses in containers and equipment. Film thickness will vary depending on actual use and specification.

Average Drying Times

| Drying time (at dft 100μ) | -5°C 8hrs | 0°C 5hrs | 5°C 3hrs | 10°C 2hrs | 20°C 1hr | 30°C 30min | |
|---------------------------------------|---------------------------------------|-------------|-------------|---------------------|--------------------|----------------------|--|
| Surface Dry | onis | onis | Shis | Zhrs | Int | Somm | |
| Hard Dry | 22hrs | 16hrs | 12hrs | 8hrs | 5hrs | 4hrs | |
| Overcoating interval (at dft 100μ) | -5°C | 0°C | 5°C | 10°C | 20°C | 30°C | |
| Minimum | 22hrs | 16hrs | 12hrs | 8hrs | 5hrs | 4hrs | |
| Maximum | Indefinitely overcoatable with itself | | | | | | |
| Dry to Launch | 48hrs | 36hrs | 24hrs | 18hrs | 12hrs | 10hrs | |

These figures are given as a guide only. Factors such as air movement and humidity must also be considered.

Recommended Primers

Macropoxy C425V2 Seavoyage 1500 Seavoyage Tiecoat 1030

RECOMMENDED TIECOATS

Seavoyage 1500 Seavoyage Tiecoat 1030

PACKAGE

Single Pack Product

Pack Size: 20 litre units

2.9 kg/litre (may vary with shade).

Weight: Shelf Life:

12 months from date of manufacture or 'Use By' date where specified

www.sherwin-williams.com/protectiveEMEA

This Data Sheet is specifically subject to the disclaimer which can be found at http://protectiveemea.sherwin-williams.com/Home/Disclaimer"



SEAVOYAGE 1200 ANITIFOULING COATING

Revised 07/2020 Issue 1

PRODUCT INFORMATION

SURFACE PREPARATION

All surface contamination such as dirt, grease, oil, etc. must be removed. To be used over suitable existing antifoulings and primers.

Please consult Sherwin-Williams' representative for compatibility.

Close high pressure fresh water washing to 250 bar (3500 psi) to remove contamination and any leached layers from existing antifouling.

APPLICATION EQUIPMENT

Airless Spray

Nozzle Size: 621 - 735 Operating Pressure: Typical PSI 1700-2200

The airless spray details given above are intended as a guide only. Details such as fluid hose length and diameter, paint temperature and job shape and size all have an effect on the spray tip and operating pressure chosen. However, the operating pressure should be the lowest possible consistent with satisfactory atomisation. As conditions will vary from job to job, it is the applicators' responsibility to ensure that the equipment in use has been set up to give the best results. If in doubt Sherwin Williams should be consulted.

Brush and Roller can be used

Maximum 85% relative humidity. Substrate temperature shall be at least 3°C above the dew point.

Application at temperature down to -5°C is possible, but curing time takes longer and full cure will be reached when temperature increases.

ADDITIONAL NOTES

On immersion, Seavoyage 1200 may exhibit a slight colour change.

For the expectations of performance from this antifouling product in static conditions: It is necessary to consider parameters such as trading pattern and the environmental conditions i.e., traditional level of fouling activity, pollution levels and water temperatures at static locations."

- a. Observe the precautionary notices displayed on the container.
- b. Provide adequate ventilation.
- c. Avoid skin contact and inhalation of spray mist.
- d. If the product comes into contact with the skin, wash thoroughly with luke warm water and soap or suitable cleaner. If the eyes are contaminated, irrigate with water and seek medical advice immediately.
- e. Since the product contains flammable materials, keep away from sparks and open flames. No smoking should be permitted in the area.

HEALTH AND SAFETY

Consult Product Health and Safety Data Sheet for information on safe storage, handling and application of this product.

WARRANTY

Whilst all statements made about our products (whether in this data sheet or otherwise) are correct and accurate to the best of our knowledge, we have no control over the quality or the condition of the substrate, the application conditions or the many other factors affecting your use and application of our product.

The appropriateness of the product under the actual conditions of application or intended use must be determined exclusively by you. The content of this document, and of any oral or written statements already made or to be made in relation to the subject matter of this document, including any suggestions as to appropriate products and any proposed application methods, technical details and other product information represent only test results or experience obtained under controlled or defined circumstances, and is therefore provided for general information purposes only.

Unless we agree specifically in writing to do so, we will not be liable to you for any loss or damage whether in contract, tort (including negligence), breach of statutory duty, misrepresentation, misstatement or otherwise, arising under or in connection with this document or such statements.

We disclaim any express or implied representations, warranties or guarantees (including any implied warranty of merchantability or fitness for a particular purpose), though nothing in this disclaimer excludes or limits our liability for death or personal injury arising from our negligence, or our fraud or fraudulent misrepresentation, or any other liability that cannot be excluded or limited by law.

All products supplied and technical advice given are subject to our Standard Terms and Conditions of Sale which you should request a copy of and review carefully.

This document may be modified and updated from time to time, and is uncontrolled once printed. It is the users responsibility to ensure they are using the most up to date version – this can be found at: www.protectiveemea.sherwin-williams.com.

If this datasheet has been translated, then it has been done using the English version as the source. In case of any queries, please refer to the master English version which can be found at: www.protectiveemea.sherwin-williams.com.

www.sherwin-williams.com/protectiveEMEA

This Data Sheet is specifically subject to the disclaimer which can be found at http://protectiveemea.sherwin-williams.com/Home/Disclaimer"