

Protective & Marine Coatings

SEAVOYAGE 5800 ANITIFOULING COATING

Revised 07/2020 Issue 1

PRODUCT INFORMATION

PRODUCT DESCRIPTION

Seavoyage 5800 is a hydrolysing self-polishing tin free antifouling coating paint designed to protect hulls for up to 90 months and to provide protection during extended static periods.

RECOMMENDED USE

For antifouling protection up to 90 months between dry-dockings for underwater hulls of ocean going vessels. This product is for professional use only.

ENDORSEMENTS

IMO Anti-fouling Systems Convention compliant (AFS/CONF/26).

HSE Approval number 10477

Irish Biocidal Approval PCS 99269/70

RECOMMENDED APPLICATION METHODS

Airless Spray Brush* Roller*

*In case of brush or roller application, more layers will be required to achieve the specified film thickness.

Recommended Thinner:

No 2

PRODUCT CHARACTERISTICS

Flash Point: 23°C

% Solids by Volume: 65± 2%

Colour Availability: Brown, Light Brown

VOC (Theoretical): 348 g/l

TYPICAL THICKNESS

Dry film thickness µm		Wet film thickness µm		Theoretical coverage	
				m²/ltr*	
Min	Max	Min	Max	Min	Max
75	160	115	246	8.7	4.1

* This figure makes no allowance for surface profile, uneven application, overspray or losses in containers and equipment. Film thickness will vary depending on actual use and specification.

AVERAGE DRYING TIMES

Drying time (at dft 100µ)	-5°C	0°C	5°C	10°C	20°C	30°C	
Surface Dry	8hrs	5hrs	3hrs	2hrs	1hr	30min	
Hard Dry	22hrs	16hrs	12hrs	8hrs	5hrs	4hrs	
Overcoating interval (at dft 100µ)	-5°C	0°C	5°C	10°C	20°C	30°C	
Minimum	22hrs	16hrs	12hrs	8hrs	5hrs	4hrs	
Maximum	Indefinitely overcoatable with itself						
Dry to Launch	48hrs	36hrs	24hrs	18hrs	12hrs	10hrs	

These figures are given as a guide only. Factors such as air movement and humidity must also be considered.

RECOMMENDED PRIMERS

Macropoxy C425V2 Seavoyage 1500

RECOMMENDED TIECOATS

Seavoyage 1030 Tiecoat Seavoyage 1500

PACKAGE

Single Pack Product

Pack Size: 20 litre units

Weight: 1.9 kg/litre (may vary with shade).

Shelf Life: 12 months from date of manufacture or 'Use

By' date where specified



Protective & Marine Coatings

SEAVOYAGE 5800 ANITIFOULING COATING

Revised 07/2020 Issue 1

PRODUCT INFORMATION

SURFACE PREPARATION

All surface contamination such as dirt, grease, oil, etc. must be removed. To be used over suitable existing antifoulings and primers.

Please consult Sherwin-Williams' representative for compatibility.

Close high pressure fresh water washing to 250 bar (3500 psi) to remove contamination and any leached layers from existing antifouling.

APPLICATION EQUIPMENT

Airless Spray

Nozzle Size: 621 - 735

Operating Pressure: Typical PSI 1700 - 2200

The airless spray details given above are intended as a guide only. Details such as fluid hose length and diameter, paint temperature and job shape and size all have an effect on the spray tip and operating pressure chosen. However, the operating pressure should be the lowest possible consistent with satisfactory atomisation. As conditions will vary from job to job, it is the applicators' responsibility to ensure that the equipment in use has been set up to give the best results. If in doubt Sherwin Williams should be consulted.

Brush and Roller may be used.

Maximum 85% relative humidity. Substrate temperature shall be at least 3°C above the dew point.

Application at temperature down to -5°C is possible, but curing time takes longer and full cure will be reached when temperature increases.

ADDITIONAL NOTES

On immersion, Seavoyage 5800 may exhibit a slight colour change. For the expectations of performance from this antifouling product in static conditions: It is necessary to consider parameters such as trading pattern and the environmental conditions i.e., traditional level of fouling activity, pollution levels and water temperatures at static locations.

- a. Observe the precautionary notices displayed on the container.
- b. Provide adequate ventilation.
- c. Avoid skin contact and inhalation of spray mist.
- d. If the product comes into contact with the skin, wash thoroughly with luke warm water and soap or suitable cleaner. If the eyes are contaminated, irrigate with water and seek medical advice immediately.
- e. Since the product contains flammable materials, keep away from sparks and open flames. No smoking should be permitted in the area.

HEALTH AND SAFETY

Consult Product Health and Safety Data Sheet for information on safe storage, handling and application of this product.

WARRANTY

Whilst all statements made about our products (whether in this data sheet or otherwise) are correct and accurate to the best of our knowledge, we have no control over the quality or the condition of the substrate, the application conditions or the many other factors affecting your use and application of our product.

The appropriateness of the product under the actual conditions of application or intended use must be determined exclusively by you. The content of this document, and of any oral or written statements already made or to be made in relation to the subject matter of this document, including any suggestions as to appropriate products and any proposed application methods, technical details and other product information represent only test results or experience obtained under controlled or defined circumstances, and is therefore provided for general information purposes only.

Unless we agree specifically in writing to do so, we will not be liable to you for any loss or damage whether in contract, tort (including negligence), breach of statutory duty, misrepresentation, misstatement or otherwise, arising under or in connection with this document or such statements.

We disclaim any express or implied representations, warranties or guarantees (including any implied warranty of merchantability or fitness for a particular purpose), though nothing in this disclaimer excludes or limits our liability for death or personal injury arising from our negligence, or our fraud or fraudulent misrepresentation, or any other liability that cannot be excluded or limited by law.

All products supplied and technical advice given are subject to our Standard Terms and Conditions of Sale which you should request a copy of and review carefully.

This document may be modified and updated from time to time, and is uncontrolled once printed. It is the users responsibility to ensure they are using the most up to date version – this can be found at: www.protectiveemea.sherwin-williams.com.

If this datasheet has been translated, then it has been done using the English version as the source. In case of any queries, please refer to the master English version which can be found at: www.protectiveemea.sherwin-williams.com.