



Resuseal WB

Revised 08/2019—Issue 4 : REF : SEWB 2017 11

DESCRIPTION

Resuseal WB is a two pack water based epoxy floor/wall coating with excellent adhesion to concrete, wood and other surfaces providing attractive, hard wearing dust-free finishes. Resuseal WB can act as a curing membrane to increase hardness of concrete by allowing full hydration of cement and can be applied to new concrete, 7 days after being poured (refer to application section).

Grades available : Resuseal WB Gloss
Resuseal WB Standard

ADVANTAGES

- Low odour
- Silica Free
- Superb adhesion
- Hard wearing
- Hygienic

RECOMMENDED USES

- As a seal coat for concrete
- Excellent choice for low to medium traffic indoor applications
- Food industries and Warehouses
- Suitable for all types of masonries, asphalt and wood substrates
- Best choice for indoor walkways, stairs, storages, warehouses and similar applications
- Automotive workshops

PRODUCT INFORMATION

System Thickness (Recommended)	100-150 microns WFT 40-60 microns DFT *The suggested thickness range is calculated based on average volume solid as a general recommendation for the specified condition and for each application may vary.
Solids Content by Weight	50% It may vary for clear and different colours
Solids Content by Volume	40% It may vary for clear and different colours
Pack Sizes	5kg & 10kg (colour)
Pack Make Up	1 x Base 1 x Hardener
Shelf Life	24 months (Base & Hardener)
Storage	Keep out of direct sunlight. Store in a dry place, between 15°C- 30°C. Product is not freeze-thaw stable.

APPLICATION INFORMATION at 20°C

Coverage Rate (Theoretical)	5kg will cover 40m ² @ 100 microns wet thickness. * Coverage rate is calculated based on a sealed and smooth surface and may vary based on the substrate roughness and other conditions.
Pot Life	Up to 60 minutes from mixing. * water based epoxy may stay liquid for longer than specified pot life but it is recommended to use all mixed paint within the pot life time frame. Application after pot life may affect the cure properties such as gloss and adhesion.
Recoating Intervals	12 - 24 hours
Light Traffic	24 - 48 hours
Full Traffic	48 - 72 hours
Full Chemical Cure	7 - 10 days



Specification

Product : Resuseal WB

Finish : Satin & Gloss

Recommended thickness range : 100-150 µm WFT per coat

Colour : Limited colour range, please consult Sherwin-Williams

Products required for this system

Primer : Resuseal WB Clear on dry substrates with less than 70% ERH or Resuprime MVT on damp surfaces.

System : 1 x Resuseal WB Clear or Colour x 2 coats (Multiple coats will be required to achieve full coverage on low opacity colours such as bright yellows and reds)

Surface Seal : Not required

Preparation

Surfaces to be coated must be clean, sound, dry and free of any contaminants that could impair good adhesion. Substrate temperature should be between 10-30°C with relative air humidity of 70% maximum. Cold, high humidity and lack of air movement can cause a patchy finish, gloss reduction and delay in curing and damage to final properties. To prevent this ensure good drying conditions and air ventilation prevail throughout the application and cure of the product.

New Concrete Floors: New concrete must be clean and sound with surface laitance removed preferably by vacuum enclosed shot blasting or mechanical grinding, a minimum strength of 25N/ mm² is required. Open, porous substrates may benefit by applying one extra coat of the specified primer.

Existing Concrete Floors: Remove all dirt, oil, grease, old paints or any other surface contaminants by vacuum enclosed shot blasting, scarifying or mechanical grinding. Fats, oils or greases must be removed by mechanical means and detergent washing and rinse with clean water to make sure all residue of detergents and/or chemicals are completely removed. Local repairs should be carried out prior to main application by using the specified primer then **Resuscreed PA** and followed by specified system.

Priming

Open and porous substrates will require priming. **Resuseal WB Clear** is recommended and depending on the porosity and texture of the surface to be primed may require two coats. **Resuseal WB Clear** will not seal block work as it is a thin film primer.

Application

Mixing: Pre-mix the base component to a uniform consistency then add the entire contents of the hardener to the base and mix by using a slow speed hand held powered mixer and mixing paddle for approximately two to three minutes to achieve consistent mixture. Note: Do not use a separate mixing bucket as it may affect the mixing ratio.

Apply the whole mixed paint by using spreading rake, roller and brush to achieve the maximum coverage within the specified pot life time frame.

Do not add water to this product.

Slip resistance can be improved by lightly broadcasting anti slip aggregates on the first coat (after primer) whilst still wet and back rolling, at a rate of 50/100 g/m². When cured apply the second **Resuseal WB** coat to secure the aggregates.

Do not apply **Resuseal WB** on top of polyurethane coatings, as it may not adhere properly.

Resuseal WB can act as a curing membrane to increase hardness of concrete by allowing full hydration of cement. **Resuseal WB** can be applied to a new (green) concrete, 7 days after being poured. In such cases expect surface gloss reduction and delay in cure process due to substrate dampness.

Category Guide

FeRFA Category : 1 and 2

Technical Information

The following figures are obtained from laboratory tests and our experience with this product .

Slip Resistance Dry > 60

Method BS7976-1:2002+A1:2013
BS7976-2:2002+A1:2013
BS7976-3:2002+A1:2013 Wet (Please consult Sherwin-Williams)

The slip resistance of a floor surface can vary as a result of the installation process, conditions at the time of application and subsequent traffic. Inappropriate cleaning or maintenance can adversely affect the performance. For further advice on potential wet areas please consult Sherwin-Williams

Abrasion Resistance 44mg loss per 1000 cycles (average)

Method ASTM D4060-14

Temperature Resistance Tolerant of temperatures of up to 60°C

Chemical Resistance Good chemical Resistance
Consult Sherwin-Williams on specific materials

VOC 10 g/l calculation based on a full mixed unit

Maintenance and Cleaning

Sherwin-Williams recommend that **Resuseal WB** should be cleaned with a regular industrial cleaning regime after specified full chemical cure time frame with a floor scrubber utilising **R.S. Industrial Floor Cleaner** or similar with dirty water being removed. Isolated localised cleaning can be carried out using **R.S. Tyre Mark Remover**, **Degreaser W500** and **R.S. Oil Remover**. All surfaces should be thoroughly rinsed with clean water after the use of chemical cleaners. Do not splash, clean, wash or treat the resin flooring with water or any other chemicals until full cure achieved, as it may affect the surface quality and performance.

Please refer to the Sherwin-Williams Guide to Cleaning of Resin Floors

Health and Safety

Resuseal WB is formulated from materials designed to achieve the highest level of performance as safely as possible. However, specific components require proper handling and suitable equipment, this information is given in the relevant safety data sheets. In all cases, spillages or skin contamination should be cleaned as soon as practically possible, by dry wiping of the affected area, and thorough washing with soap and water.

The information given in this data sheet is derived from tests and experience with the products and is believed to be reliable. The information is offered without guarantee to enable purchasers to determine for themselves the suitability of the product for their particular application. Any specification or advice given by Sherwin-Williams or its agents is based on the information supplied by the purchaser. Sherwin-Williams cannot be held accountable for errors or omissions as a result of that information being incorrect or incomplete. No undertakings can be given against infringement of patents. Some materials are derived from natural sources. As such some variation may occur. Site conditions may also contribute to variation in finish and colour.

Sherwin-Williams Protective & Marine
Tower Works, Kestor Street, Bolton, BL2 2AL, United Kingdom
Tel : + 44 (0) 1204 521771 F: + 44 (0) 1204 382115
W : Sherwin-williams.com/protectiveEMEA
Registered in England : Reg. No. 893081
Reg. Office Tower Works, Kestor Street, Bolton BL2 2AL England