



# Resustat SL23

Revised 05/2018—Issue 1 : REF : SLAS 2016

## DESCRIPTION

Resustat SL23 is a static-dissipative resin based flooring system which is laid at 3 mm nominal thickness. The formulation comprises of a unique blend of conductive fillers blended with polyurethane resin components & pigments to provide an attractive smooth Matt finish. The Resustat SL23 flooring system has an electrical conductivity leakage resistance of  $<10^9$  ohms when tested to BS EN 61340.

## ADVANTAGES

- High chemical resistance
- Resistance to hot water
- Ease of application
- Static dissipative seamless matt finish
- Hard wearing durable floor for industrial use
- Hygienic
- Excellent abrasion and impact resistance

## RECOMMENDED USES

- Pharmaceutical production
- Electronic industrial areas
- Television studios
- Operating theatres
- Chemical plants
- Domestic studios
- Industrial workshops

## PRODUCT INFORMATION

<b>System Thickness (Recommended)</b>	2mm to 3mm
<b>Solids Content</b>	100% solids by weight
<b>Pack Sizes</b>	16 kg
<b>Pack Make Up</b>	1 x Base 1 x Hardener 1 x Aggregate 1 x Conductive Aggregate Pot
<b>Shelf Life</b>	12 months (Base, Hardener & Conductive Aggregate) 6 months (Aggregate)
<b>Storage</b>	Keep out of direct sunlight. Store in a dry place between 15°C—30°C. Aggregate should be stored in a dry area to prevent contamination from moisture, as this would have a detrimental effect on the product.

## APPLICATION INFORMATION at 20°C

<b>Coverage Rate (Theoretical)</b>	16 kg will cover 4m <sup>2</sup> at 2mm thickness or 2.6m <sup>2</sup> at 3mm thickness.
<b>Pot Life</b>	15 minutes
<b>Recoating Intervals</b>	N/A
<b>Light Traffic</b>	12 - 16 hours
<b>Full Traffic</b>	48 hours
<b>Full Chemical Cure</b>	5 - 7 days



BRITISH COATINGS FEDERATION



## Specification

**Product :** Resustat SL23

**Finish :** Smooth, Matt

**Recommended thickness range :** 2mm to 3mm

**Colour :** Limited colour range, consult Sherwin-Williams

### Products required for this system

**Primer :** Resuprime NT or R.S. Dampshield on damp surfaces, where required. Followed by Resustat Primer.

**System :** Resustat SL23

## Preparation

**New Concrete Floors:** New concrete must be clean, sound, dry, fully cured and surface laitance removed by vacuum enclosed shot blasting or mechanical grinding, a minimum strength of 25N/mm<sup>2</sup> is required.

**Existing Concrete Floors:** Remove all dirt, oil, grease, old paint or any other surface contaminants by vacuum enclosed shot blasting, scariying or mechanical grinding. Fats, oils or greases must be removed by mechanical means and detergent washing and make sure all residue of detergent is washed and removed by rinsing with clean water.

### Existing Floors ( previously coated )

All previous coatings and loose floor paints must be removed by mechanical preparation as described in the above section and primed as specified. If the old resin flooring cannot be removed, then please consult with our technical team for advice on intercoat adhesion and suitability, as it may not be compatible with existing floor coating.

To ensure the maximum bond is achieved, grooves must be cut into the perimeter of the subfloor, typically 5mm deep by 10mm wide. These should be inset approximately 150mm from, and running parallel with the walls and adjacent to any doorways, plinths etc. including any finished edge, i.e. both sides of a day work joint. The groove must have a neat square edge and the **Resustat SL23** laid to the full depth forming a perimeter anchorage.

## Priming

Open and porous substrates will require priming with **Resuprime NT** on dry substrates only with less than 75% ERH reading. Where the Relative Humidity of a substrate exceeds 75% ERH **R.S. Dampshield** should be specified and selected on the basis of hygrometer readings in accordance with BS 8203.

The number of coats to be applied is chosen in accordance with the following table.

ERH%	Required Coating Thickness
75-85	1 coat of R.S.DAMPSHIELD at 200 microns per coat
85-92	2 coats of R.S.DAMPSHIELD at 200 microns per coat
92-97	3 coats of R.S.DAMPSHIELD at 200 microns per coat

Following the application of the **Resuprime NT** or **R.S. Dampshield**, copper tape strips are laid to form a grid system where the grids are no larger than 2m x 2m. The copper tape should be left exposed in areas to allow them to be earthed properly. Onto this a coat of **Resustat Primer** is applied to provide a fully conductive layer under the **Resustat SL23**. It is important to take a conductive reading of the cured **Resustat Primer** before applying the **Resustat SL23**.

## Application

**Resustat SL23** may be applied to substrates with a surface temperature in the range of 5-20°C and a relative humidity < 90% RH, with a minimum air temperature of 8°C and no condensation. Do not pre-warm this product as working times will be substantially reduced if materials are warm.

When the primed surface is tack free **Resustat SL23** should be applied at the required rate as soon after mixing as possible. (Delay can result in variation in surface finish, colour and add to application problems). Mix the coloured base component to an even consistency, ensuring the re-dispersion of any settled pigment, Thoroughly scrape the contents of the base and hardener components into the same container and mix thoroughly for one minute. Pour the combined base and hardener into a rotary drum mixer and add the aggregate component steadily followed by the conductive aggregate, until a homogeneous mix of the three components is achieved.

When thoroughly mixed the compound should be poured evenly over the appropriate area to be covered (monitoring rate of coverage to ensure correct depth of screed). Low floor temperatures and reduced thickness may reduce the flow properties of these products. Work out the mix rapidly and evenly over the area with a notched trowel, pin rake or similar to the appropriate thickness. Roll immediately with a spiked roller to achieve an even smooth surface and remove entrapped air.

NB: Spiked rolling should be undertaken immediately after trowelling. Do not re-roll later. **Resustat SL23** units should be applied consistently with mixes from the same batch used consecutively where adjacent areas are being laid.


## Category Guide

FeRFA Category : 5

## Technical Information

The following figures are obtained from laboratory tests and our experience with this product .

Slip Resistance	Dry >50
Method BS7976 pt1-3 2002	Wet (Please consult Sherwin-Williams)
The slip resistance of a floor surface can vary as a result of the installation process, conditions at the time of application and subsequent traffic. Inappropriate cleaning or maintenance can adversely affect the performance. For further advice on potential wet areas please consult Sherwin-Williams	
Abrasion Resistance	AR 1.0
Method BS EN 13892-4	(Less than 100µ wear)
Temperature Resistance	Tolerant of temperatures of up to 80°C @ 3mm
Chemical Resistance	Excellent chemical Resistance Consult Sherwin-Williams on specific materials
Compressive Strength	41 N/mm <sup>2</sup>
Flexural Strength	8.6 N/mm <sup>2</sup>
Tensile Strength	3.4 N/mm <sup>2</sup>
Electrical Resistance	<10 <sup>9</sup> Ohms
Method: BS EN 61340-4	(Results will vary slightly with finish and thickness)
VOOC	14 g/l calculated per full mixed unit
Life Expectancy	Up to 7 years Subject to industrial traffic. Sherwin-Williams terms and conditions will apply

	
<b>Sherwin Williams Protective &amp; Marine</b> <b>Tower Works, Kestor Street, Bolton, BL2 2AL, United Kingdom</b> <b>Tel: +44 (0) 1204 521771 F: +44 (0) 1204 382115</b>	
13	
<b>BSEN 13813 SR B 3.1- AR 1 - IR&gt;4</b> Resin coating/screed for use inside buildings as per data sheet	
Wear resistance:	AR 1
Bond strength:	B 3.1
Impact resistance:	IR > 4

## Maintenance and Cleaning

Sherwin-Williams recommend that **Resustat SL23** should be cleaned with a regular industrial cleaning regime with a floor scrubber utilising **R.S. Industrial Floor Cleaner** or similar with dirty water being removed. Isolated localised cleaning can be carried out using **R.S. Tyre Mark Remover**, **R.S. Fats, Oils & Grease Remover** & **R.S. Oil Remover**. All surfaces should be thoroughly rinsed with clean water after the use of chemical cleaners.

Please refer to the **Sherwin-Williams Guide to Cleaning of Resin Floors**

## Health and Safety

**Resustat SL23** is formulated from materials designed to achieve the highest level of performance as safely as possible. However, specific components require proper handling and suitable equipment, this information is given in the relevant safety data sheets. In all cases, spillages or skin contamination should be cleaned as soon as practically possible, by dry wiping of the affected area, and thorough washing with soap and water.

The information given in this data sheet is derived from tests and experience with the products and is believed to be reliable. The information is offered without guarantee to enable purchasers to determine for themselves the suitability of the product for their particular application. Any specification or advice given by Sherwin-Williams or its agents is based on the information supplied by the purchaser. Sherwin-Williams cannot be held accountable for errors or omissions as a result of that information being incorrect or incomplete. No undertakings can be given against infringement of patents. Some materials are derived from natural sources. As such some variation may occur. Site conditions may also contribute to variation in finish and colour.

Sherwin-Williams Protective & Marine  
Tower Works, Kestor Street, Bolton, BL2 2AL, United Kingdom  
Tel : + 44 (0) 1204 521771 F: + 44 (0) 1204 382115  
W : Sherwin-williams.com/protectiveEMEA  
Registered in England : Reg. No. 893081  
Reg. Office Tower Works, Kestor Street, Bolton BL2 2AL England