

White Lightning®
Oil-based Glazing Compound
WL08015, WL08016, WL08017, WL08018

Type: Oil-based glazing compound
Color: White
Shelf Life: One year minimum
Flash point: Greater than 200 F
Flammability: Not Established
Cure Time: Thin skin forms in 48 to 96 hours*
Tack Free Time: 72 hours to 1 week (3/16" to 3/8" inch bead)*
Application Temperature: 40 F to 90 F
VOC Level: 0.304 lbs / gal.
Mildew Resistance: Excellent (with 2 coats oil based paint)
Odor: Slight, pleasant
Shrinkage: Low / None
Vehicle: Blend of Soya and Marine oils
Weight per gallon: 16.0 +/- 0.5 lbs

*dependant on bead size, temperature and relative humidity.

Performance:

Joint movement capability: Not recommended for applications where joint movement might occur.

Glazing bead sizes (recommended): 3/16" to 3/8"

Freeze / thaw stability: Passes 5 cycles

Clean-up: Mineral Spirits

Flexibility: Permanently flexible / does not harden.

Painting: Oil-based primer and paints recommended**

Water resistance: Excellent

** Water based paints can be used after firm skin has formed.

Oil-based primer recommended.

This glazing product is not intended for use on organically sealed insulated glass, plastic windows, or any pane over 48" in any direction.

Packaging:

Size	Order#	UPC
Half Pint	WL08015	0-23275-08015-7
Pint	WL08016	0-23275-08016-4
Quart	WL08017	0-23275-08017-1
Gallon	WL08018	0-23275-08018-8

For More Information please call or write:
White Lightning Products
101 Prospect Ave NW
Cleveland, OH 44115
1-800-241-5295

