

# 41-LINE



## Porch and Floor Enamel - Acrylic Latex

### INTENDED USES:

A tough flexible coating for new or previously painted wood or concrete floors, porches and stairs. May also be used as a top coat or to freshen up decks or floor surfaces previously coated with Hypalon or Spantex Deck Coating.

### PRODUCT DESCRIPTION:

A modified acrylic latex, pigmented to dry as a tough, water resistant, flexible finish.

---

### TECHNICAL INFORMATION:

#### Finish:

Eggshell

#### Tint Range:

22 standard P & F colours.

#### Theoretical Coverage:

33-43 m<sup>2</sup>/3.7L (350-470 ft<sup>2</sup>/3.7L)

#### Typical Specific Gravity:

1.4

#### Application Thinner:

10-15% Water required for sealing porous substrates.

#### Standard Colours:

White (41-010), Cloud Grey (41-087), Twilight Grey (41-090)

#### Recommended # of coats:

1-2 at recommended coverage

#### Typical Volume Solids:

44%

#### Flash point:

Not Applicable

#### Clean-up Thinner:

Water

---

### SURFACE PREPARATION:

Surfaces must be clean, dry and free from dust, grease, mildew and wax. Remove any loose and peeling paint and repair with patching compound. Ensure all joints and seams are filled with a paintable caulking to prevent moisture ingress. Prepare as required. New Wood: Thin first coat 10-15% and apply second coat as supplied. Concrete Floor: Concrete, including repairs, must be cured (minimum 28 days) before application. Wash weathered concrete using a suitable detergent and pressure washer (pressure tip on a garden hose is acceptance as a minimum). Acid etch new and smooth concrete or if the pH is not within the 6.8 to 8.0 range and rinse thoroughly until the pH is within the given range. Allow a minimum of three days to dry after washing, rain or dew. Thin first coat 10-15%. Previously Painted Surface: Glossy surfaces should be sanded to a dull finish to provide good adhesion. Metal and Other Surfaces: Consult your GP Paint Pro.

### APPLICATION:

Brush or Roller.

Airless Tips: N/A

Dry times at 21°C / 70°F and 40%-60% R.H.:

|              |                                       |
|--------------|---------------------------------------|
| To Touch:    | 15-60 minutes                         |
| To Handle:   | 1-2 hours                             |
| To Overcoat: | 4 hours (takes 28 days to fully cure) |

### PRODUCT HAZARDS SAFETY INFORMATION:

See Material Safety Data Sheet for complete Health and Safety information.

### ADDITIONAL DATA:

Concrete Floor: Ensure that the surface is free from moisture by allowing it to dry completely and ensuring that there is no moisture as a result of hydrostatic pressure. To determine if moisture is present as a result of hydrostatic pressure of ground moisture, tape 2 ft<sup>2</sup> pieces of polythene film on various locations and leave overnight. If there is any moisture visible on the plastic sheets, then there is ground moisture and the substrate is unsuitable for coating. If mildew is present, the surface should be washed

with a chlorine bleach solution (20% household bleach and 1% liquid detergent in warm water) and thoroughly rinsed prior to painting. For optimum adhesion and application performance, ensure that the temperature and relative humidity are between 15-25°C and 40-60% respectively, at the time of application and for four hours afterward. Avoid washing or spilling of water for at least 7 days after application. Allow 24 hours before walking on and 7 days before replacing heavy furniture. Not recommended on surfaces exposed to vehicular traffic.  
Complies with the requirements of MPI #60.

**Legal Details**

The information contained herein is true and accurate to the best of our knowledge. However, no guarantee or warranty of any kind, express or implied, is given with respect to the accuracy or completeness of the said information and data or to the products described herein and we assume no risk or liability for the performance or coverage of or for injury resulting from the handling, use or application of the said information, data or products.