# 60-224 Baseline Latex Block Filler



# **INTENDED USES:**

A surface filler specifically designed to fill voids and reduce texture on concrete, concrete block and other types of masonry. For interior and exterior use.

#### **PRODUCT DESCRIPTION**

A heavy-bodied, water-reducible, latex coating, containing pigments and fillers with VOC levels less than 50 g/l.

TECHNICAL INFORMATION:	
<b>Finish:</b> Flat	Standard Colours: White
Tint Range:	Recommended # of coats:
Light colours	1-2 at recommended coverage
<b>Theoretical Coverage:</b> 12-19 m <sup>2</sup> /3.7L (130-200 ft <sup>2</sup> /3.7L)	<b>Typical Volume Solids:</b> 51%
<b>Typical Specific Gravity:</b> 1.6	Flash point: Not Applicable
Application Thinner:	Clean-up Thinner:
DO NOT THIN	Water

# SURFACE PREPARATION:

Surfaces must be clean, dry and free from dust, grease, mildew and wax. Remove any loose and peeling paint and repair with patching compound. Surface repairs should be spot primed.

### **APPLICATION:**

Brush or Roller. May be applied with suitable heavy duty airless spray equipment.

Airless Tips: .021"- .035"

Dry times at 21°C / 70°F and 40%-60% R.H.:

To Touch:	1-2 hours
To Handle:	4 hours
To Overcoat:	8 hours mimimum

### **PRODUCT HAZARDS AND SAFETY INFORMATION:**

### **ADDITIONAL DATA:**

For optimum adhesion and application performance, ensure that the temperature and relative humidity are between 15-25°C and 40-60% respectively, at the time of application and for four hours afterward. If mildew is present, the surface should be washed with a chlorine bleach solution (20% household bleach and 1% liquid detergent in warm water) and thoroughly rinsed prior to painting. One coat of Latex Sealer should be applied before applying solvent borne finish coats.

Complies with the requirements of MPI #4.

#### Legal Details

The information contained herein is true and accurate to the best of our knowledge. However, no guarantee or warranty of any kind, express or implied, is given with respect to the accuracy or completeness of the said information and data or to the products described herein and we assume no risk or liability for the performance or coverage of or for injury resulting from the handling, use or application of the said information, data or products.