

70-LINE



Elasto-wall

INTENDED USES:

A high build, weather-resistant elastomeric coating for exterior concrete, stucco and masonry. Elasto-wall exhibits excellent durability and longterm flexibility bridging hairline cracks, while providing excellent UV resistance and protection from wind driven rain.

PRODUCT DESCRIPTION:

A high quality, 100% acrylic latex elastomeric coating, pigmented to give a flat finish.

TECHNICAL INFORMATION:

Finish:

Flat (slight angular sheen)

Tint Range:

Light, medium and dark colours

Theoretical Coverage:

5.5-6.0 m²/3.7L (60-65 ft²/3.7L)

Typical Specific Gravity:

1.4

Application Thinner:

Not normally required.

Standard Colours:

White (70-040)

Recommended # of coats:

2 at recommended coverage

Typical Volume Solids:

48%

Flash point:

Not Applicable

Clean-up Thinner:

Water

SURFACE PREPARATION:

Surfaces must be clean, dry and free from dust, grease, mildew, surface hardeners, curing agents and wax. Remove any loose and peeling paint and repair with patching compound. Will bridge hairline cracks up to 0.4mm. All others will require repair.

Although self-priming on most concrete, stucco or masonry surfaces, better adhesion, durability and application properties will be obtained if first primed with 70-004 Epotilt Primer. Substrate pH should be 6 to 10. If the substrate surface has a pH greater than 10, then priming with Epotilt Primer is required.

APPLICATION:

Brush, Roller, Air Spray or Airless Spray.

Airless Tips: .019" - .023" @ 2300-2700 PSI

Dry times at 21°C / 70°F and 40%-60% R.H.:

To Touch:	2 hours
To Handle:	24 hours
To Overcoat:	24 hours (takes 7 days to cure)

PRODUCT HAZARDS SAFETY INFORMATION:

See Material Safety Data Sheet for complete Health and Safety information.

ADDITIONAL DATA:

For optimum adhesion and application performance, ensure that the temperature and relative humidity are between 15-25°C and 40-60% respectively, at the time of application and for four hours afterward. If mildew is present, the surface should be washed with a chlorine bleach solution (20% household bleach and 1% liquid detergent in warm water) and thoroughly rinsed prior to painting. Heavily chalked surfaces should be power washed to remove chalky deposit prior to priming. Do not apply to surfaces below grade.

Legal Details

The information contained herein is true and accurate to the best of our knowledge. However, no guarantee or warranty of any kind, express or implied, is given with respect to the accuracy or completeness of the said information and data or to the products described herein and we assume no risk or liability for the performance or coverage of or for injury resulting from the handling, use or application of the said information, data or products.