

71-LINE



Breeze Exterior Semi-Gloss Latex

INTENDED USES:

A quick drying, extremely weather-resistant finish for most exterior vertical surfaces. Has better long term flexibility than alkyds and lower dirt pick-up than flat finishes. May be applied over aged alkyd, latex stain or paint, which can be used for low temperature application.

PRODUCT DESCRIPTION:

A high quality, 100% acrylic latex pigmented to give a semi-gloss finish.

TECHNICAL INFORMATION:

Finish:

Semi-Gloss

Tint Range:

Full range of colours

Theoretical Coverage:

24-33 m²/3.7L (260-350 ft²/3.7L)

Typical Specific Gravity:

1.2

Application Thinner:

Not normally required. Up to 10% water may be used, if required, for spraying.

Standard Colours:

White

Recommended # of coats:

1-2 at recommended coverage

Typical Volume Solids:

33%

Flash point:

Not Applicable

Clean-up Thinner:

Water

SURFACE PREPARATION:

Surfaces must be clean, dry and free from dust, grease, mildew and wax. Remove any loose and peeling paint and repair with patching compound. Ensure all joints and seams are filled with a paintable caulking to prevent moisture ingress. Prime as required below. Surface repairs should be spot primed.

New Wood: Prime with Exterior Alkyd Primer or Latex Wood Primer.

Previously Painted Surfaces: Glossy surfaces should be sanded to a dull finish to provide good adhesion.

Concrete and Masonry: Allow to age 28 days. No primer required. Latex Block Filler can be used to reduce texture on rough surfaces.

Metal and Other Surfaces: Consult your GP Paint Pro.

APPLICATION:

Brush, Roller, Air Spray or Airless Spray.

Airless Tips: .015" - .021"

Dry times at 21°C / 70°F and 40%-60% R.H.:

To Touch:	15-60 minutes
To Handle:	1-2 hours
To Overcoat:	4 hours (takes 28 days to fully cure)

PRODUCT HAZARDS SAFETY INFORMATION:

See Material Safety Data Sheet for complete Health and Safety information.

ADDITIONAL DATA:

Complies with the requirements of MPI #11.

Not suitable for use on exterior doors. If mildew is present, the surface should be washed with a chlorine bleach solution (20% household bleach and 1% liquid detergent in warm water) and thoroughly rinsed prior to painting.

For optimum adhesion and application performance, ensure that the temperature and relative humidity are between 15-25°C and 40-60% respectively, at the time of application and for four hours afterward.

Drying time will vary depending on temperature, air circulation and humidity. The surface and air temperature must remain above 2°C while the humidity remains below 70%. If painting in cold conditions the temperature must not fall below freezing for at least 8 hours. Recoat time at lower temperatures requires a minimum of 24 hours when temperatures are below 10°C. Do not apply if snow, rain, frost, fog or damp conditions are expected within 24 hours after application.

Legal Details

The information contained herein is true and accurate to the best of our knowledge. However, no guarantee or warranty of any kind, express or implied, is given with respect to the accuracy or completeness of the said information and data or to the products described herein and we assume no risk or liability for the performance or coverage of or for injury resulting from the handling, use or application of the said information, data or products.