

85-140



Private Estate - Super Premium Acrylic Flat Latex

INTENDED USES:

Premium quick dry, non-spatter, flat latex enamel finish for interior use. Provides a high hide, durable finish having excellent flow and moderate soil resistance. For architectural service in living and dining rooms, etc., where a higher than average quality finish is required. This product has good stain resistance compared to other flat latexes.

PRODUCT DESCRIPTION

A high quality acrylic latex vehicle pigmented to produce a flat finish.

TECHNICAL INFORMATION:

Finish:

Flat

Tint Range:

Full range of colours

Theoretical Coverage:

31-40 m²/3.7L (320-430 ft²/3.7L)

Typical Specific Gravity:

1.4

Application Thinner:

Not normally required. Up to 10% water may be used, if required, for spraying.

Standard Colours:

White

Recommended # of coats:

1-2 at recommended coverage

Typical Volume Solids:

40%

Flash point:

Not Applicable

Clean-up Thinner:

Water

SURFACE PREPARATION:

Surfaces must be clean, dry and free from dust, grease, mildew and wax. Remove any loose and peeling paint and repair with patching compound. Prime as required below. Surface repairs should be spot primed.

New Drywall: Seal with Latex Super Seal.

New Wood: Prime with Latex wood Primer.

Previously Painted Surfaces: Glossy surfaces should be sanded to a dull finish or primed with Latex Plastic Primer to provide good adhesion.

Metal and Other Surfaces: Consult your GP Paint Pro.

APPLICATION:

Brush, Roller, Air Spray or Airless Spray

Airless Tips: .013" - .017"

Dry times at 21°C / 70°F and 40%-60% R.H.:

To Touch: 15 to 30 minutes

To Handle: 2 hours

To Overcoat: 4 hours minimum

PRODUCT HAZARDS AND SAFETY INFORMATION:

See Material Safety Data Sheet for complete Health and Safety information.

ADDITIONAL DATA:

For optimum adhesion and application performance, ensure that the temperature and relative humidity are between 15-25°C and 40-60% respectively, at the time of application and for four hours afterward. If mildew is present, the surface should be washed with a chlorine bleach solution (20% household bleach and 1% liquid detergent in warm water) and thoroughly rinsed prior to painting. A

Legal Details

The information contained herein is true and accurate to the best of our knowledge. However, no guarantee or warranty of any kind, express or implied, is given with respect to the accuracy or completeness of the said information and data or to the products described herein and we assume no risk or liability for the performance or coverage of or for injury resulting from the handling, use or application of the said information, data or products.

curing period of 7-10 days is required before the optimum properties are achieved. Consult your GP Paint Pro.

Legal Details

The information contained herein is true and accurate to the best of our knowledge. However, no guarantee or warranty of any kind, express or implied, is given with respect to the accuracy or completeness of the said information and data or to the products described herein and we assume no risk or liability for the performance or coverage of or for injury resulting from the handling, use or application of the said information, data or products.