



WOOD FINISHING SYSTEMS

M.L. Campbell
224 Catherine Street
Fort Erie, Ontario L2A 5M9 Canada
Tel: 1(800) 364-1359
Web: www.mlcampbell.com

Product Information (PI) Sheet

Product: Standard Lacquer Thinner

Code(s): C160 36

Description: Standard Lacquer Thinner is a high-quality special blend of solvents specifically designed to be an excellent reducer for nitro-cellulose, pre-catalyzed, post catalyzed, butyrate and acrylic lacquers. It is tolerant of a wide range of poor application conditions, and will maintain good dry, flow, and blush resistance. Standard Lacquer Thinner has a minimum tendency to raise the wood grain. This combination of properties minimizes the sanding required on lacquer sealer and between finish coats. Many finishing problems would not have occurred if a quality lacquer thinner had been used. No recycled solvents are used in the manufacturing of this product.

Other Products: When periods of excess humidity exist (over 50%) which can cause blushing (clouding of the finish), the use of up to 10% of Lacquer Retarder Thinner per gallon should be considered.

Physical Properties (packaged)
Weight per Gallon: 7.09 lbs.
Flash Point (PMCC): 53°F or 11.6°C
VOC: 851 g/l (7.11 lbs./gallon)
Photochemically Reactive: Yes

Application Procedure
Standard Lacquer Thinner may be used in cold spray, airless spray or hot spray applications, 110°F is recommended. Refer to specific products for recommended amounts. Do not use in waterborne coatings.

Packaging/Shipping
Available Units: Gallons, Pails and Drums.

Shelf Life and Storage
Store in cool, dry areas in the original sealed containers.
Do not store around any source of flames or sparks.
Spills should be cleaned up with non-sparking tools and inert absorbent material.

DOT Classification
Flammable Liquid Red Label UN1263

B/L Description
Paint UN 1263 3 PG II

Caution
THESE PRODUCTS ARE DESIGNED FOR SHOP APPLICATION AND PROFESSIONAL USE ONLY.
Use only after all safety information is understood.
Refer to the Material Safety Data Sheet (MSDS) for additional information.

Testing

Due to the wide variety of substrates, surface preparation methods, application methods, and environments, customers should test the complete system for adhesion and compatibility under their conditions prior to full-scale application.

Notes

The information, rating, and options stated here pertain to the material currently offered and represent the results of tests believed to be reliable. However, due to variations in customer handling and methods of application that are not known or under our control, M.L. Campbell cannot make any warranties as to the end result. *Thank you for using M.L. Campbell Wood Finishing products.*