



WOOD FINISHING SYSTEMS

M.L. Campbell
224 Catherine Street
Fort Erie, Ontario L2A 5M9 Canada
Tel: 1(800) 364-1359
Web: www.mlcampbell.com

Product Information (PI) Sheet

Product: B.C. Retarder

Code(s): C16336

Description: B.C. Retarder is a premium slow solvent retarder specially formulated for conditions of high heat and humidity. This product will effectively help enhance the flow of ML Campbell products and will help reduce bubbling and blushing caused by the effects of high heat and humidity during application.

Other Products: Can be used as a retarder in all M.L. Campbell solvent products. Consider using Flow Enhancer #2 in temperatures above 90 – 95 degrees as it allows the top layer of the coating to stay open longer to help prevent solvent evaporation pinholes.

Physical Properties (packaged)
Weight per Gallon: 7.49 ± .2 lbs
Flash Point (PMCC): 150°F (63°C)
Packaged VOC: 897 g/l (7.49 lbs/gallon)
Photochemically Reactive: No

Application Procedure
B.C. Retarder may be used in cold spray, airless spray or hot spray applications. The use of B.C. Retarder will slow the drying time in proportion to the amount used. Generally, the addition of 2-3% is adequate to solve most application issues. Maximum addition recommended is 5% per gallon. Do not use in water borne coatings.

Packaging/Shipping
Available Units: Gallons, Pails.

Shelf Life and Storage
Store in cool, dry areas in the original sealed containers.
Do not store around any source of flames or sparks.
Spills should be cleaned up with non-sparking tools and inert absorbent material.

DOT Classification
Flammable Liquid Red Label UN1263

B/L Description
Paint UN 1263 3 PG II

Caution

- **THESE PRODUCTS ARE DESIGNED FOR SHOP APPLICATION AND PROFESSIONAL USE ONLY.**
- Use only after all safety information is understood.
- Refer to the Material Safety Data Sheet (MSDS) for additional information.

Testing

Due to the wide variety of substrates, surface preparation methods, application methods, and environments, customers should test the complete system for adhesion and compatibility under their conditions prior to full-scale application.

Notes

The information, rating, and options stated here pertain to the material currently offered and represent the results of tests believed to be reliable. However, due to variations in customer handling and methods of application that are not known or under our control, M.L. Campbell cannot make any warranties as to the end result. *Thank you for using M.L. Campbell Wood Finishing products.*