

## Product Information (PI) Sheet

**Product:** ARROYO® 1K Waterborne White Pigmented Topcoat

<b>Code(s):</b>	<b>W140950</b> Flat	<b>W140952</b> Dull	<b>W140954</b> Satin	<b>W140958</b> Gloss
-----------------	------------------------	------------------------	-------------------------	-------------------------

**Description:** ARROYO® 1K Waterborne Pigmented Topcoat Tint Base White is a single-component hybrid WB urethane system for interior use. Arroyo has exceptional self-sealing, film-build and film formation properties resulting in an extremely smooth, durable finish. Arroyo is GREENGUARD® certified for low indoor emissions and VOC. Arroyo pass all KCMA tests and AWI System 2, Pre-catalyzed Lacquer and System 8, Water Base Acrylic Cross-Linking chemical and moisture resistance tests.

**Uses:** For use on kitchen and bathroom cabinets, dormitory, household, and office furniture. Also, for use on paneling and display fixtures.

**Other Products:** For Primer, use W41259 M.L. Campbell AquaFi™ Universal WB Primer or W140959 Arroyo® 1K Waterborne White Under-coater & Stain Blocking Primer. Apply 2 coats of primer to prevent possible tannin bleed reaction. C38277 WB Arroyo® Catalyst (optional)

Physical Properties (packaged)	
<b>Weight per Gallon</b>	9.62 ± 0.2
<b>Viscosity - Ford #4 at 77°F/25°C</b>	50 ± 5 seconds
<b>% Solids – by Weight</b>	42 ± 2.0%
<b>% Solids - by Volume</b>	31 ± 2.0%
<b>Theoretical Coverage at 1 Mil Dry</b> <small>(Coverage figures DO NOT INCLUDE spray loss. Also allow for surface irregularities and porosity of wood surface to be finished)</small>	490-530 sq. ft./gal.
<b>Flash Point (PMCC)</b>	Not Combustible
<b>Color</b>	White
<b>Sheen (60° Glossmeter)</b>	Flat 6-10, Dull 15±5, Satin 35±5, Gloss 70+
<b>Packaged VOC</b>	140-162 g/l (1.16-1.35 lbs./gal)
<b>Photochemically Reactive</b>	No

Surface Preparation	
<b>New Work:</b>	Remove any dirt, grease or other construction contamination from surface. Sand wood as required. No primer is required.
<b>Old Work:</b>	Remove any dirt, grease, or other contamination from surface. Sand well to improve adhesion. If cratering develops, WR4 Latex (W) Anti-Cratering Additive may remedy this problem, if the contamination is not too severe.

Reduction
Product does not require reducing but can be thinned with distilled water (use very small amounts at a time). Thinning should be limited to 5%. Over thinning can cause sags due to high

solids content of product.

**Mixing and Catalyzing (Optional)**

To improve product performance, **Arroyo® 1K Waterborne Clear Topcoat** can be catalyzed with the Water Borne 2K Catalyst **C38277-DP** at the ratio of 100 parts base product to five parts catalyst (5% catalyst by volume or weight). Weigh or measure catalyst then pour into product **while stirring**. The C38277-DP Catalyst should be added to Arroyo 1K products following similar mixing instructions as for the 2K products (see PDS for C3870X/W3870X). **It is recommended to allow a 5 -10 minute “sweat-in” time after addition of catalyst for best results.** Once catalyzed the product has **up to 8 hours pot-life** under normal conditions. Viscosity will not be impacted by the addition of catalyst, even after 8 hours. Be sure to dispose of any catalyzed material safely after exceeding pot life.

**Application Procedure**

Sand wood using 220 grit sandpaper, as required. **Arroyo 1K Waterborne White Topcoat** can be used as a self-sealing system or **W140959 Arroyo™ 1K Primer** can be used as a first prime coat. Apply **2 coats (3 if self-seal)** of **Arroyo 1K Waterborne White Topcoat** at 3-5 wet mils per coat. Sand with 320, Fre-cut (no fill) type sandpaper between first and second coat. Sand with 320 and then very fine scotch brite between second and third coat. Always sand just prior to recoating. The total dry film build should be at least 3 mils and should not exceed 6 dry mils.

*Refer to spray equipment suppliers, recommendations for fine lacquer atomizing spray guns, air caps, and fluid needles.*

**Note:** Hot spray application is not recommended. If hot spray equipment is used, temperature settings should never be over 110°F or 43° C. Apply using only stainless steel or plastic spray equipment. If aluminum equipment is used, some oxidation may occur. Before application material, surface and air temperatures should be a minimum of 65° F or 18° C.

**Equipment Clean Up**

- All equipment should be flushed with warm water immediately after use.
- A subsequent flush with alcohol will ensure all moisture is removed from the system.

**Drying Times (at 77° F or 25° C)**

<b>Dry to Touch:</b>	15-25 minutes
<b>Sanding Dry:</b>	35-45 minutes
<b>Stacking Dry:</b>	6 - 8 hours

**Packaging/Shipping**

<b>Available Units:</b>	Gallons and Pails.
<b>Shipping Caution:</b>	Restrictions for shipments of freezable materials.

**Shelf Life and Storage**

- Protect from freezing and other extreme temperatures. Product does pass freeze/thaw stability test but must be checked before use to ensure quality.
- Store in airtight containers.
- Shelf life is 18 months.

**DOT Classification**

Paint and Related Material	NOIBN	Protect from Freezing
----------------------------	-------	-----------------------

### Caution

- **THESE PRODUCTS ARE DESIGNED FOR PROFESSIONAL USE ONLY.**
- Use only after all safety information is understood.
- Refer to the Safety Data Sheet (SDS) or Material Safety Data Sheet (MSDS) for additional information.

### Testing

Due to the wide variety of substrates, surface preparation methods, application methods, and environments, customers should test the complete system for adhesion and compatibility under their conditions prior to full-scale application.

### Notes

The information, rating, and options stated here pertain to the material currently offered and represent the results of tests believed to be reliable. However, due to variations in customer handling and methods of application that are not known or under our control, M.L. Campbell cannot make any warranties as to the end result. *Thank you for using M.L. Campbell Wood Finishing products.*