

TECHNICAL DATA SHEET

TZ26**/13

2K POLYURETHANE TOPCOAT - BRIGHT WHITE

TZ2610 White (10 sheen) TZ2670 White (70 sheen) TZ2625 White (25 sheen) TZ2690 White (90 sheen) TZ2635 White (35 sheen)

Versions		10, 25, 35, 70	.90	
Area of use:		Flat parts, pro	files, fitted furnit	ure
Method of use:		Airmix, airless, spray guns.		
Mixing procedure:			By Weight	By Volume
			(kg)	
	Part A	TZ26**/13	100	100
	Part B (Max. Non-Yellowing)	THL072100	50	70
	Thinner / Reducer	DT Series*	25-30	25-30
	Slow - Retarder	DT6K35000	3-5	3-5

^(*) Fast = DT7KB2900 Medium = DT6K18000 Slow = DT6K35000.

See Sayerlack Thinner Reduction Guide for additional blends and blending guidance

Technical characteristics

Solids content (%): As packaged	Weight Solids 70 ± 1 / Volume Solids 50 ± 2		
Specific gravity (kg/l): As packaged	01.390 ± 0.030		
Viscosity (Zahn #3 at 68°F)*:	A + B: 58 ± 5 seconds		
Pot-life at 68°F:	3 hours		
Recommended wet film thickness:	3.0 - 7.0 mils		
Spread Rate:	802 sq. ft./gal @ 1.0 mil DFT, No loss		
Drying time (at 68°F):	Dust Free 10 minutes		
	Touch Dry 30 minutes		
	Stackable 5-6 hours		
Forced drying (at 3 mil WFT):	Flash off 15 minutes		
	Hot air at 120°F 60 minutes		
VOC (Theoretical as packaged, maximum):	3.68 lb./gal, 441 g/L (less exempt solvents)		
Shelf-life:	Part A: 36 months, unopened.		
	After long periods of storage, always check		
	homogeneity and stir well before use to eliminate		
	and possible sediment.		
Tint recommendation:	Can be tinted up to 5% by volume with TP2009/XX		
	Universal Solvent-Based Pastes Aromatic Free		

^{*}WARNING: Actual viscosity of some pigmented and/or thixotropic products may differ from the viscosity shown on the Technical Data Sheet. Differences are to be considered acceptable if within 30%.

TZ26/13 2K Polyurethane Topcoat – Bright White** is a white matt topcoat with excellent flow on flat parts and excellent hiding power on edges. White and pale shades in general are liable to yellow slightly over time.

TECHNICAL DATA SHEET

TZ26**/13

PIGMENTED WHITE POLYURETHANE TOPCOAT

Substrate preparation

Wood – New Work (interior only): Must be clean, dry and finish sanded. Substrate should be free of grease, oil, dirt, fingerprints and any contamination. Moisture content of wood should be 6-8%.

Previously finished wood (interior only): Strip old finishes completely and remove all contaminants from the surface. Make sure surface is dry. Finish as new work

Prime: Prime wood with white polyurethane primer such as TU0205/13 Polyurethane Basecoat White

Testing: The information, data, and recommendations set forth in this Product Data Sheet are based upon test results believed to be reliable. However, due to the wide variety of substrates, substrate properties, surface preparation methods, equipment and tools, application methods, and environments, the customer should test the complete system for adhesion, compatibility and performance prior to full scale application.

FOR INDUSTRIAL SHOP APPLICATION ONLY

Thoroughly review product label and Safety Data Sheet (SDS) for safety information and cautions prior to using this product. To obtain the most current version of the Environmental Data Sheet (EDS), Product Data Sheet (PDS), or Safety Data Sheet (SDS) please visit www.paintdocs.com. Please direct any questions or comments to your local M.L. Campbell® Distribution Partner, M.L. Campbell® Sales Manager or contact our technical service line at 1-800-364-1359

Note: All purchases of products from Sherwin-Williams are exclusively subject to Sherwin-Williams' terms and conditions of sale which can be found at www.sherwin.com. Please review these terms and conditions prior to the purchase of the products. Sherwin-Williams warrants the product to be free of manufacturing defect in accordance with Sherwin-Williams' quality control procedures. Except for the preceding sentence, due to factors that are outside of Sherwin-Williams' control, including substrate selection, and customer handling, preparation, and application, Sherwin-Williams cannot make any other warranties related to the product or the performance of the product. SHERWIN-WILLIAMS DISCLAIMS ALL WARRANTIES OF ANY KIND, EXPRESS OR IMPLIED, INCLUDING BUT NOT LIMITED TO THE IMPLIED WARRANTY OF MERCHANTABILITY, THE IMPLIED WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE. Liability for products proven to be defectively manufactured will be limited solely to replacement of the defective product or the refund of the purchase price paid for the defective product, as determined by Sherwin-Williams. Under no circumstances shall Sherwin-Williams be liable for indirect, special, incidental or consequential damages, lost profits or punitive damages arising from any cause whatsoever.