

TECHNICAL DATA SHEET

TZ99 **/NN
POLYURETHANE-NEUTRAL CONVERTOR/TOPCOAT

TZ9905/NN Neutral (05 sheen)
 TZ9935/NN Neutral (35 sheen)

TZ9910/NN Neutral (10 sheen) TZ9925/NN Neutral (25 sheen)
 TZ9950/NN Neutral (50 sheen) TZ9985/NN Neutral (85 sheen)

Versions:	5, 10, 25, 35, 50, 85 sheen		
Area of use:	Flat parts, furniture, profiles		
Method of use:	Airmix and airless spray guns		
Mixing procedure:		By Weight (kg)	By Volume
	Part A	TZ99**/NN	100
	Part B (Max. Non-Yellowing)	THL0721000	50
	Thinner / Reducer	DT Series*	30-50
	Slow - Retarder	DT6K35000	3-5

(*) **Fast** = DT7KB2900 **Medium** = DT6K18000 **Slow** = DT6K35000.

See Sayerlack Thinner Reduction Guide for additional blends and blending guidance

Technical characteristics

Solids content (%):	As packaged	Weight Solids 46 ± 1 / Volume Solids 38 ± 2
Specific gravity (kg/l):	As packaged	1.000 ± 0.030
Viscosity (Zahn #2 at 68°F)*:		A + B: 24 ± 3 seconds
Pot-life at 68°F:		3 hours
Recommended wet film thickness:		3.0 mils
Spread Rate:		850 – 994 sq. ft./gal @ 1.0 mil DFT, No loss
Drying time (at 68°F):	Dust free	5-10 minutes
	Touch dry	30-40 minutes
	Stackable	24 hours
Forced drying (at 3 mil WFT):	Flash off	15-20 minutes
	Hot air at 120°F	45-60 minutes
VOC (Theoretical as packaged, maximum):		4.45 lb./gal, 534 g/L (less exempt solvents)
VHAPS (Theoretical as packaged, maximum):		0.59 lb./lb. of solids
Shelf-life:	Part A: 36 months, unopened. Part B: 12 months, unopened. After long periods of storage, always check homogeneity and stir well before use to eliminate and possible sediment.	
Tint recommendation:	Can be tinted up to 20% by volume with TP2009/XX Universal Solvent-Based Pastes Aromatic Free	

*WARNING: Actual viscosity of some pigmented and/or thixotropic products may differ from the viscosity shown on the Technical Data Sheet. Differences are to be considered acceptable if within 30%.

TZ99/NN Polyurethane Neutral Convertor/Topcoat** is a neutral tint-base & topcoat with excellent flow on flat parts and excellent hiding power on edges.

TECHNICAL DATA SHEET

TZ99 **/NN

POLYURETHANE-NEUTRAL CONVERTOR/TOPCOAT

Substrate preparation

Wood – New Work (interior only): Must be clean, dry and finish sanded. Substrate should be free of grease, oil, dirt, fingerprints, and any contamination. Moisture content of wood should be 6-8%.

Previously finished wood (interior only): Strip old finishes completely and remove all contaminants from the surface. Make sure surface is dry. Finish as new work

Prime: Prime wood with white polyurethane primer such as **TU0205/13** Polyurethane Basecoat White

Testing: The information, data, and recommendations set forth in this Product Data Sheet are based upon test results believed to be reliable. However, due to the wide variety of substrates, substrate properties, surface preparation methods, equipment and tools, application methods, and environments, the customer should test the complete system for adhesion, compatibility, and performance prior to full scale application.

Tinting Notes:

TZ99**/BB has been specifically formulated for tinting systems. TZ99**/BB bases must be tinted and applied with solvent-based Universal Pigments; TP2009/XX added. The addition of organic pigmented pastes implies longer drying times, lower hardness as well as lower hiding power than inorganic pigmented pastes. Moreover, the addition of TP2009/XX pigmented pastes inevitably increases the gloss of final product, varying according to the quantity and type of pastes used: it is therefore advisable to always check if the desired gloss has been achieved.

FOR INDUSTRIAL SHOP APPLICATION ONLY

Thoroughly review product label and Safety Data Sheet (SDS) for safety information and cautions prior to using this product. To obtain the most current version of the Environmental Data Sheet (EDS), Product Data Sheet (PDS), or Safety Data Sheet (SDS) please visit www.paintdocs.com. Please direct any questions or comments to your local M.L. Campbell® Distribution Partner, M.L. Campbell® Sales Manager or contact our technical service line at 1-800-364-1359

Note: All purchases of products from Sherwin-Williams are exclusively subject to Sherwin-Williams' terms and conditions of sale which can be found at www.sherwin.com. Please review these terms and conditions prior to the purchase of the products. Sherwin-Williams warrants the product to be free of manufacturing defect in accordance with Sherwin-Williams' quality control procedures. Except for the preceding sentence, due to factors that are outside of Sherwin-Williams' control, including substrate selection, and customer handling, preparation, and application, Sherwin-Williams cannot make any other warranties related to the product or the performance of the product. **SHERWIN-WILLIAMS DISCLAIMS ALL WARRANTIES OF ANY KIND, EXPRESS OR IMPLIED, INCLUDING BUT NOT LIMITED TO THE IMPLIED WARRANTY OF MERCHANTABILITY, THE IMPLIED WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE.** Liability for products proven to be defectively manufactured will be limited solely to replacement of the defective product or the refund of the purchase price paid for the defective product, as determined by Sherwin-Williams. Under no circumstances shall Sherwin-Williams be liable for indirect, special, incidental or consequential damages, lost profits or punitive damages arising from any cause whatsoever.