


MULTI-PURPOSE SPRAY ADHESIVE



SP™ 7000



VOC Compliant



Max.-Min. Operational Temperature Range -20°F to 123°F (-29°C to 50°C)



Fast Tack



Foam Safe



Lap Shear 58.58



Peel Strength 6.186



HMIS Hazard Rating:
Health (2) • Flammability (4) • Reactivity (0)

- Dries quickly
- Controlled mist spray pattern
- VOC & MIR compliant
- Tack Range: 10-30 seconds



PRESERVE. PROTECT. PREVENT.™

Sprayon® SP™7000 Multi-purpose spray adhesive is great for bonding a variety of lightweight materials. Provides high coverage and has low soak-in factor. For long lasting, secure bonds whether your project is simple or complex. Does not contain ozone-depleting CFCs.

SPECIALTY PRODUCTS

USES

- Lightweight foams
- Cardboard
- Fabric
- Plastic
- Wood
- Foil
- (un)Painted metals
- Paper
- Cartons
- Carpets
- Metal
- Fiberglass
- Felt
- Cloth

APPLICATION

Use in a well ventilated area. Clean and dry surface, remove any soap, oil, dirt or moisture. Shake can well before use. Adhesive spray works best at room temperature. Hold can 6"-8" upright from surface for an even spray. Lightly spray both sides of substrate. Spraying too close can deliver too much adhesive, increase the drying time and weaken the bond. For best results spray two light coats versus one heavy coat. Wait 30seconds to 1 minute before securing two substrates together. To prevent clogged actuator after use, turn can upside down, spray until nothing else comes out.

PACKAGING

STOCK #: S0700000
UPC CODE: 0-23275-03577-5
FILL WT.: 16.75 oz.
PER CASE: 12
CARTON DIMENSIONS:
 L 11.13" x W 8.44" x H 8.38"

RESOURCES

MSDS/EDS/PRODUCT DATA SHEETS: Sprayon.com
CUSTOMER SERVICE:
 1-800-777-2966
TECHNICAL INFORMATION:
 1-800-251-2486

PROPERTIES

PROPELLANT: Butane/Propane Blend
COLOR: Off white
SPRAY PATTERN: Particle/Mist
TACK RANGE: 10-30 seconds
VOC/MIR: 63%
CARB COMPLIANT: Yes
WT/GAL: 5.83 lb/gal
HAZARD RATING: 2,4,0
COVERAGE: 15 sq. ft.
TEMPERATURE RESISTANCE: 123°F (50.6°C)
SHELF LIFE: 24 months from date of manufacture

	Peel Strength Strength (pli) ¹	Lap-Shear Failing Stress (psi) ²
Sprayon® SP™7000 Multi-Purpose Spray Adhesive	6.186 ± 0.761	58.58 ± 29.68
Leading National Brand A	2.453 ± 0.438	20.31 ± 9.72
Leading National Brand C	4.698 ± 0.969	97.54 ± 12.64

¹ASTM D903-98 Standard Test Method for Peel or Stripping Strength of Adhesive Bonds
²ASTM D1002-01 Standard Test Method for Apparent Shear Strength of Single-Lap-Joint Adhesively Bonded Metal Specimens by Tension Loading (Metal-to-Metal)

SHIPPING

Refer to section 14 of the material safety data sheet for proper transport information and labeling.



SP7000



© 2010 Sprayon® Products Made in U.S.A.

Distributed by:



Sprayon® Products
 101 Prospect Ave. NW
 Cleveland, OH 44115
Sprayon.com
 1-800-777-2966