



TECHNICAL INFORMATION

POWDURA® HYBRID POWDER COATING SATIN BLACK HBS2-C2932

CHEMICAL COATINGS

PRODUCT DESCRIPTION

HBS2-C2932, Satin Black POWDURA® Hybrid Powder Coating combines outstanding over bake and mechanical properties and is recommended for a broad range of interior functional and decorative applications.

Advantages:

- Flexible cure schedule
- Outstanding over bake properties
- Excellent film properties
- Excellent hardness
- Available in a wide range of colors, glosses and textures
- Can be formulated to minimize outgassing
- Many applications, including:
 - Tools
 - Hot Water Heaters
 - Office Furniture
 - Shelving
 - Power Tools
 - Toys
 - Oil Filters

Performance Tests:

(for smooth films only) Testing performed on Bonderite 1000 panels electrostatically applied and properly cured in an electric convection oven.

Adhesion: Pass 5B
(ASTM D-3359)

Flexibility: Pass 1/8" Mandrel
(ASTM D-522)

Pencil Hardness: 2H-3H
(ASTM D-3363)

Impact Resistance: 80 Dir/Rev
(ASTM D-2794)

Salt Spray Resistance: 1000 hrs
(ASTM-B117)

Humidity Resistance: 1000 hrs
(ASTM-D4585)

CHARACTERISTICS

60° Gloss: 15 – 25%

Cure Schedule: 10 min. at 392°F

Film Thickness Range: 2.0 – 3.0 mils

Specific Gravity: 1.528 ± .1

Spreading Rate: 125.8 sq. ft./lb @ 1 mil

Solvent Resistance:
(PCI Method)

Material Safety Data Sheet are available from your local Sherwin-Williams facility.

CHARACTERISTICS (continued)

Storage:

Powdura® Hybrid Powder Coatings should be kept in a dry and cool area at temperatures below 75°F (24° C). Shelf life ranges from 6 months to over 1 year. When not in use, store powder in sealed containers: fine powders are hygroscopic.

SPECIFICATIONS

General: Substrate should be free of grease, oil, dirt, fingerprints, drawing compounds, any contamination, and surface passivation treatments to ensure optimum adhesion and coating performance properties. The use of a chemical conversion coating prior to the application of a powder coating is strongly recommended. Consult Metal Preparation Brochure CC-T1 for additional details.

Aluminum: A minimum of a 5-stage chrome phosphate metal treatment, or equivalent, is required for good adhesion and optimum coating performance properties.

Testing: Due to the wide variety of substrates, surface preparation methods, application methods, and environments, the customer should test the complete system for adhesion and compatibility prior to full-scale application.

Product Limitations:

- For interior applications only.
- Contact your Sherwin-Williams Representative where use of this product at higher than recommended film thickness may be required.

Powder coatings must be applied using suitable electrostatic equipment. Consult your Sherwin-Williams Representative regarding unique applications.

CAUTIONS

Thoroughly review product label for safety and cautions prior to using this product. Please direct any questions or comments to your local Sherwin-Williams facility.

CAUTION! Causes eye irritation, causes skin irritation, may cause allergic skin reaction, respiratory irritant, dust may cause eye and respiratory irritation, dust may form explosive mixture in air. Avoid breathing dust. Avoid contact with eyes and prolonged or repeated contact with skin. Use protective clothing and NIOSH approved respirator. Do not use near sparks or open flame or any type of ignition source. Wash thoroughly after handling. Use only with adequate ventilation.

CAUTIONS (continued)

FIRST AID:

If on SKIN: Wash thoroughly with soap and water.
If in EYES: Flush with water immediately and procure medical attention. The area adjacent to the coating operation should be properly ventilated. Cure ovens must be exhausted to the outside atmosphere. All dusts are respiratory irritants, inhalation of the dust should be avoided. To avoid static electricity build-up, properly ground all equipment. Provide dust collection equipment with adequate explosion venting; dust clouds of any finely divided organic material can be ignited by open flame or electrical sparks.

DO NOT TAKE INTERNALLY.

KEEP OUT OF REACH OF CHILDREN.

FOR INDUSTRIAL USE ONLY.

REFER TO MATERIAL SAFETY DATA SHEET FOR ADDITIONAL INFORMATION.

Warranty Policy: The seller certifies that all coating delivered to the customer in unopened factory filled containers will meet all pertinent quality standards presented in our current published literature. Since matters of surface preparation, application procedures and other local factors that affect performance are beyond our control, we assume no liability for coating failure other than to supply replacement material for a coating shown to be outside our published quality standards. Manufacturer shall not be liable for any injuries, damages or other losses, deriving directly or in consequence of the purchaser's use of the product. Purchaser shall determine suitability of this product for his own use, and thereby assumes all risks and liabilities in connection therewith.

Note:

Product Data Sheets are periodically updated to reflect new information relating to the product. It is important that the customer obtain the most recent Product Data Sheet for the product being used. The information, rating and opinions stated above pertain to the material currently offered and represent the results of tests believed to be reliable. However, due to variations in customer handling and methods of application which are not known or under our control, The Sherwin-Williams Company cannot make any warranties or guaranties as to the end results.

Grimsby, Canada
February 9, 2003